

## รายการอ้างอิง

1. ชัยโรจน์ คุณพนิชกิจ. การตรวจสอบด้วยคลื่นอะคูสติก. วารสารเทคนิค 115 (กันยายน 2537): 133-139.
2. ชาโตะ ฟุจิอิ. การตรวจสอบแบบไม่ทำลาย. สมาคมส่งเสริมเทคโนโลยี (ไทย-ญี่ปุ่น) (2543):
3. P. Inacio, C. J. Dias and J. N. Marat-Mendes., Acoustic Emission Sensors Based on Ferroelectric Composites. 10<sup>th</sup> International Symposium on Electrets, IEEE, European Cultural Centre of Delphi, Greece. (1999)
4. S. Or, H. Chan and C. Choy., P(VDF-TrFE) copolymer acoustic emission sensors. J. Sensors and Actuators. 80 (2000): 237-241.
5. เรือโทอนุชา เรืองสวัสดิ์, การออกแบบและการเตรียมเพียโซอิเล็กทริกอัลตราโซนิกแทรนสดิวเซอร์. วิทยานิพนธ์ปริญญาโทบริหารธุรกิจ, สาขาวิชาเทคโนโลยีเซรามิก ภาควิชาวัสดุศาสตร์ จุฬาลงกรณ์มหาวิทยาลัย, 2548
6. ชัชชัย พุฒซ้อน, การพัฒนาแผ่นฟิล์มโพลีไวนิลลิดีนฟลูออไรด์เพื่อเป็นตัวทรานสดิวเซอร์. วิทยานิพนธ์ปริญญาโทบริหารธุรกิจ, ภาควิชาฟิสิกส์ จุฬาลงกรณ์มหาวิทยาลัย, 2546
7. L. Kinsler, A. Frey, A. Coppers and J. Sanders, Fundamentals of Acoustic, 3<sup>rd</sup> ed. John Wiley & Sons, Inc., 1999
8. H. Kuttruff, Ultrasonic Fundamentals and Applications, Elsevier Science Publishers, 1988
9. H. Pollard, Sound Waves in Solids. London: Pion Limited, 1977.
10. W. Smith, Materials Science and Engineering 2<sup>nd</sup> ed. Mcgraw-Hill, 1993
11. PVDF structure, Available from:  
<http://www.chemistry.helsinki.fi/polylab/research/labkuvat.html>

12. PVDF beta phase, Piezoelectric Polymer. Available from:  
<http://www.physics.montana.edu/piezopoly.htm>
13. Hysteresis loop, Available from:  
<http://www.epfl.ch/people/foeth/images/hysteresis.html>
14. APC International. Ltd. Piezo Theory [online]. Available from:  
[http://www.americanpiezo.com/piezo\\_theory/index.html](http://www.americanpiezo.com/piezo_theory/index.html)
15. W. Haifeng, R. Tim, C. Wenwu, and S. Kirk, High Frequency Properties Passive Materials for Ultrasonic Transducers. IEEE Trans. Ultrason. Ferroelect. Freq. Contr. 48 (2001): 78-84.
16. R. Selfridge., Approximate Material Properties in Isotropic Materials. IEEE Transactions on Sonics and Ultrasonic. 32 (1985): 381-384.
17. L. Dong and J. Mistry., Acoustic emission monitoring of composite cylinders. J. Composite Structures. 40 (1998): 43-53.
18. J. Park, J. Kong, D. Kim and D. Yoon., Nondestructive damage detection and interfacial evaluation of single-fibers/epoxy composites using PZT, PVDF and P(VDF-TrFE) copolymer sensors J.Composites Science and Technology. 65 (2005): 241-256.
19. M. Duncan and J. Whittaker., Acoustic Emission Calibration Instrumentation J. Instrumentation & Measurement. 38 (1989): 827-831.
20. Standard Guide for Determining the Reproducibility of Acoustic Emission Sensor Response, ASTM Standard (1984), No. E 976-84
21. S. Haykin and B. Veen., Signals and Systems (1999): 20-21.
22. T. Kaewkongka and Y. Joe, Application of acoustic emission to condition monitoring of rolling element bearings J. Measurement & Control. 32 (2001): 245-247

23. S. Anuphap-udom, K. Ratanathammapan and T. Kaewkongka., Fabricated PVDF Acoustic Emission Sensor for Lubrication Bearing Monitoring J. Scientific Research. Chulalongkorn 30 No. 2 (2006): 115-119
24. S. Anuphap-udom, T. Kaewkongka and K. Ratanathammapan., A novel fabricated acoustic emission sensors using PVDF film. 31<sup>st</sup> Congress on Science and Technology of Thailand at Suranaree University of Technology. (2005)
25. S. Anuphap-udom, K. Ratanathammapan, and T. Kaewkongka., Pipeline leak monitoring using PVDF acoustic emission sensor. 2<sup>nd</sup> Mathematics and Physical Sciences Graduate Congress, National University of Singapore. (2006)
26. S. Anuphap-udom, K. Ratanathammapan, N. Traiphol, P. Laoratanakul and T. Kaewkongka., A fabricated PZT acoustic emission sensor for pipeline leakage monitoring. 32<sup>nd</sup> Congress on Science and Technology of Thailand, Queen Sirikit National Convention Center. (2006)

## ผลงานตีพิมพ์

### วารสาร

1. S. Anuphap-udom, K. Ratanathammapan and T. Kaewkongka “Fabricated PVDF Acoustic Emission Sensor for Lubrication Bearing Monitoring” J. Scientific Research Chulalongkorn University Vol.31 No.2 (2006): 115-119

### การประชุมวิชาการ

1. S. Anuphap-udom, T. Kaewkongka and K. Ratanathammapan  
A novel fabricated acoustic emission sensors using PVDF film” 31<sup>st</sup> Congress on Science and Technology of Thailand at Suranaree University of Technology (2005).
2. S. Anuphap-udom, K. Ratanathammapan, N. Traiphol, P. Laoratanakul and T. Kaewkongka “A fabricated PZT acoustic emission sensor for pipeline leakage monitoring” 32<sup>nd</sup> Congress on Science and Technology of Thailand, Queen Sirikit National Convention Center (2006).
3. S. Anuphap-udom, K. Ratanathammapan, and T. Kaewkongka  
“Pipeline leak monitoring using PVDF acoustic emission sensor” 2<sup>nd</sup> Mathematics and Physical Sciences Graduate Congress, National University of Singapore (2006).

ภาคผนวก

ภาคผนวก ก. ตารางแสดงสมบัติของฟิล์ม PVDF

Table 1. Typical properties of piezo film

| Symbol                | Parameter                         | PVDF                     | Copolymer                | Units  |
|-----------------------|-----------------------------------|--------------------------|--------------------------|--|
| t                     | Thickness                         | 9, 28, 52, 110           | <1 to 1200               | $\mu\text{m}$ (micron, $10^6$ )  |
| $d_{31}$              | Piezo Strain Constant             | 23                       | 11                       | $10^{12} \frac{\text{m/m}}{\text{V/m}}$ or $\frac{\text{C/m}^2}{\text{N/m}^2}$ |
| $d_{33}$              |                                   | -33                      | -38                      |  |
| $g_{31}$              | Piezo Stress constant             | 216                      | 162                      | $10^3 \frac{\text{V/m}}{\text{N/m}^2}$ or $\frac{\text{m/m}}{\text{C/m}^2}$    |
| $g_{33}$              |                                   | -330                     | -542                     |  |
| $k_{31}$              | Electromechanical Coupling Factor | 12%                      | 20%                      |  |
| $k_t$                 |                                   | 14%                      | 25-29%                   |  |
| C                     | Capacitance                       | 380 for 28 $\mu\text{m}$ | 68 for 100 $\mu\text{m}$ | pF/cm <sup>2</sup> @ 1KHz  |
| Y                     | Young's Modulus                   | 2-4                      | 3-5                      | $10^9$ N/m <sup>2</sup>  |
| $V_0$                 | Speed of Sound                    | stretch:                 | 1.5                      | 2.3  |
|                       |                                   | thickness:               | 2.2                      | 2.4  |
|                       |                                   |                          |                          | $10^3$ m/s   |
| p                     | Pyroelectric Coefficient          | 30                       | 40                       | $10^6$ C/m <sup>2</sup> °K   |
| $\epsilon$            | Permittivity                      | 106-113                  | 65-75                    | $10^{12}$ F/m  |
| $\epsilon/\epsilon_0$ | Relative Permittivity             | 12-13                    | 7-8                      |  |
| $\rho_m$              | Mass Density                      | 1.78                     | 1.82                     | $10^3$ kg/m  |
| $\rho_0$              | Volume Resistivity                | $>10^{13}$               | $>10^{14}$               | Ohm meters   |
| $R_{\square}$         | Surface Metallization Resistivity | <3.0                     | <3.0                     | Ohms/square for NiAl   |
| $R_{\square}$         |                                   | 0.1                      | 0.1                      | Ohms/square for Ag Ink   |
| $\tan \delta_c$       | Loss Tangent                      | 0.02                     | 0.015                    | @ 1KHz   |
|                       | Yield Strength                    | 45-55                    | 20-30                    | $10^6$ N/m <sup>2</sup> (stretch axis)   |
|                       | Temperature Range                 | -40 to 80...100          | -40 to 115...145         | °C   |
|                       | Water Absorption                  | <0.02                    | <0.02                    | % H <sub>2</sub> O   |
|                       | Maximum Operating Voltage         | 750 (30)                 | 750 (30)                 | V/mil(V/ $\mu\text{m}$ ), DC, @ 25°C   |
|                       | Breakdown Voltage                 | 2000 (80)                | 2000 (80)                | V/mil(V/ $\mu\text{m}$ ), DC, @ 25°C   |

ภาคผนวก ข. สมการ  $AE_{RMS}$

$$AE_{RMS} = \sqrt{\frac{1}{T} \int_0^T v(t)^2 dt}$$

เมื่อ  $AE_{RMS}$  คือ พลังงานของคลื่นอะคูสติก  
 $v(t)$  คือ ค่าแอมพลิจูดของคลื่นอะคูสติก  
 $T$  คือ คาบของสัญญาณ

## ภาคผนวก ค. สมการ Fourier Transform และ algorithm ของ FFT

### สมการ Fourier Transform

$$Y(\omega) = \int_0^T y(t) e^{-j\omega t} dt$$

|       |             |                           |
|-------|-------------|---------------------------|
| เมื่อ | $Y(\omega)$ | คือ แอมพลิจูดในแกนความถี่ |
|       | $y(t)$      | คือ แอมพลิจูดในแกนเวลา    |
|       | $T$         | คือ คาบของสัญญาณ          |
|       | $\omega$    | คือ ความเร็วเชิงมุม       |

### รายละเอียดของ Algorithm ของ FFT

```
>> load test1.txt;           // โหลดข้อมูลชื่อ test1
>> fs = 500000;             // กำหนดค่า sampling rate เท่ากับ 500000
>> t = 0:1/fs:1.25;         // กำหนดตัวแปร t คือ เวลา
>> A = test1(:,2);          // กำหนดตัวแปร A คือ แอมพลิจูดจากข้อมูลชื่อ test1
>> subplot(121)
>> plot(1000*t(1:2500),A(1:2500)) // เขียนกราฟระหว่าง t กับ A โดยใช้ข้อมูลทั้งหมด 2500 จุด
>> title('Acoustic emission raw signal') // กำหนดชื่อเรื่อง
>> xlabel('time (ms)')      // กำหนดชื่อแกน x
>> ylabel('Amplitude(V)')  // กำหนดชื่อแกน y
>> n = length(A);           // กำหนดตัวแปร n คือจำนวนข้อมูลของตัวแปร A
>> Y = fft(A,n);            // กำหนดตัวแปร Y คือค่าที่ได้จากการแปลง FFT ของ A
>> Py = Y.*conj(Y)/n;       // กำหนดตัวแปร Py คือ ค่ากำลัง
>> f = (1:n/2)*fs/(n);      // กำหนดตัวแปร f คือค่าความถี่
>> subplot(122)
>> plot(f/1000,Py(1:n/2))   // เขียนกราฟระหว่าง f กับ Py
>> title('Power spectrum density')
>> xlabel('Frequency (kHz)')
>> ylabel('Power (V2/Hz)')
```



ภาคผนวก ง. ผลการวัดค่าความหนาแน่น อัตราเร็วเสียงและค่าอิมพีแดนซ์ทางเสียงใน  
วัสดุผสมกาวอีพอกซีและทังสเทน

| สัดส่วนปริมาตร<br>ของทังสเทน (%) | วัดครั้งที่ | ความหนาแน่น<br>(kg/m <sup>3</sup> ) | อัตราเร็วเสียง<br>(m/s) | อิมพีแดนซ์ทางเสียง<br>(MRayl) |
|----------------------------------|-------------|-------------------------------------|-------------------------|-------------------------------|
| 0                                | 1           | 1,125.40                            | 2,635.63                | 2.96614                       |
|                                  | 2           | 1,133.90                            | 2,631.71                | 2.98409                       |
|                                  | 3           | 1,138.41                            | 2,619.46                | 2.98201                       |
|                                  | 4           | 1,141.12                            | 2,605.01                | 2.97262                       |
|                                  | 5           | 1,123.25                            | 2,637.89                | 2.96301                       |
| 2                                | 1           | 1,988.34                            | 1,596.92                | 3.17522                       |
|                                  | 2           | 1,983.75                            | 1,603.81                | 3.18156                       |
|                                  | 3           | 1,941.20                            | 1,639.23                | 3.18207                       |
|                                  | 4           | 1,944.62                            | 1,639.06                | 3.18735                       |
|                                  | 5           | 1,917.87                            | 1,660.46                | 3.18455                       |
| 5                                | 1           | 2,939.45                            | 1,245.67                | 3.66158                       |
|                                  | 2           | 3,026.32                            | 1,221.45                | 3.69650                       |
|                                  | 3           | 2,955.87                            | 1,231.83                | 3.64113                       |
|                                  | 4           | 3,017.04                            | 1,226.64                | 3.70082                       |
|                                  | 5           | 2,966.15                            | 1,228.37                | 3.64353                       |

ภาคผนวก จ. ผลการวัดค่าพลังงาน AE<sub>RMS</sub> และค่าความถี่ต่อการตอบสนองที่ตรวจจับได้จากตัวตรวจจับ PVDF แต่ละตัว

| ตัวตรวจจับ | วัดครั้งที่ | ค่า AE <sub>RMS</sub> (V) | ความถี่ต่อการตอบสนอง (kHz) |
|------------|-------------|---------------------------|----------------------------|
| T1         | 1           | 0.0292                    | 48.34                      |
|            | 2           | 0.0261                    | 48.29                      |
|            | 3           | 0.0309                    | 48.35                      |
|            | 4           | 0.0244                    | 48.34                      |
|            | 5           | 0.0234                    | 48.42                      |
| T2         | 1           | 0.0155                    | 38.02                      |
|            | 2           | 0.0111                    | 37.88                      |
|            | 3           | 0.0088                    | 38.00                      |
|            | 4           | 0.0092                    | 38.15                      |
|            | 5           | 0.0105                    | 37.67                      |
| T3         | 1           | 0.0133                    | 29.15                      |
|            | 2           | 0.0170                    | 29.25                      |
|            | 3           | 0.0138                    | 28.99                      |
|            | 4           | 0.0198                    | 29.12                      |
|            | 5           | 0.0143                    | 28.87                      |

ภาคผนวก จ. ผลการวัดค่าพลังงาน AE<sub>RMS</sub> และค่าความถี่ต่อการตอบสนองที่ตรวจจับได้จากตัวตรวจจับ PZT แต่ละตัว

| ตัวตรวจจับ | วัดครั้งที่ | ค่า AE <sub>RMS</sub> (V) | ความถี่ต่อการตอบสนอง<br>(kHz) |
|------------|-------------|---------------------------|-------------------------------|
| T4         | 1           | 0.0334                    | 50.04                         |
|            | 2           | 0.0237                    | 50.05                         |
|            | 3           | 0.0256                    | 50.05                         |
|            | 4           | 0.0337                    | 49.98                         |
|            | 5           | 0.0383                    | 49.93                         |
| T5         | 1           | 0.0247                    | 105.25                        |
|            | 2           | 0.0343                    | 105.31                        |
|            | 3           | 0.0243                    | 105.77                        |
|            | 4           | 0.0409                    | 105.63                        |
|            | 5           | 0.0252                    | 105.40                        |
| T6         | 1           | 0.0216                    | 209.11                        |
|            | 2           | 0.0189                    | 209.03                        |
|            | 3           | 0.0156                    | 208.85                        |
|            | 4           | 0.0140                    | 209.54                        |
|            | 5           | 0.0086                    | 208.68                        |



## ประวัติผู้เขียนวิทยานิพนธ์

นายสิทธิชัย อนุภาพอุดม เกิดเมื่อวันที่ 26 กรกฎาคม พ.ศ. 2523 สำเร็จการศึกษาในระดับมัธยมศึกษาตอนปลายจากโรงเรียนบ้านฉางกาญจนกุลวิทยา จังหวัดระยอง ได้เข้าศึกษาต่อในระดับปริญญาตรีในปีการศึกษา 2542 ในหลักสูตรวิทยาศาสตรบัณฑิต สาขาวิชาฟิสิกส์ มหาวิทยาลัยธรรมศาสตร์ หลังจากจบการศึกษาในระดับปริญญาตรีแล้ว ได้ศึกษาต่อในหลักสูตรวิทยาศาสตรมหาบัณฑิต สาขาวิชาฟิสิกส์ คณะวิทยาศาสตร์ จุฬาลงกรณ์มหาวิทยาลัย ในปีการศึกษา 2546