

References

- American Pharmaceutical Association and The Pharmaceutical Society of Great Britain. 1986. Handbook of Pharmaceutical Exipient. USA : The Pharmaceutical Press.
- Bakan, J.A. 1986. Microencapsulation. In Lachman, L. et al (ed.), The theory and Practice of Industrial Pharmacy, pp.412 - 429 Philadelphia : Lea & Febiger.
- Bodmeier, R., Oh, K.H., and Pramar, Y. 1989. Preparation and evaluation of drug-containing chitosan beads. Drug Dev. Ind. Pharm. 15(9) : 1475-1494.
- _____, and Paeratakul, O. 1989. Spherical agglomerates of water-insoluble drugs. J. Pharm. Sci. 78(11) : 964-967.
- Burgess, D.J., Kwok, K.K., and Megremis, P.T. 1991. Characterization of albumin-acacia complex coacervation. J. Pharm. Pharmacol. 43 : 232-236.
- Chattaraj, S.C., Das, S.K., Karthikyan, M., Ghosal, S.K., and Gupta, B.K. 1991. Controlled theophylline release from microcapsules of acrylic & methalic acid ester copolymer. Drug Devel. Ind. Pharm. 17(4) : 551-560.
- Chowdary, K.P.R., and Murty, A.S.R. 1985. Controlled nitrofurantoin release through microencapsulation. Indian J. Pharm. Sci. 6-8 : 161-162.
- Deasy, P.B., ed. 1984. Microencapsulation and Related Drug Processes. USA:Marcel Dekker.

- Draget, K.I. et al. 1992. Chitosan cross-linked with Mo(VI) Polyoxyanions : a new gelling system. Biomaterial. 3(9) : 635-638
- Dukkuri, A., Schroeder, H.G., and Deluca, P.P. 1978. Sustained release from inert wax matrixesII : effect of surfactants on tripeleannamine hydrochloride release. J. Pharm. Sci. 67(3) : 354-357.
- Hecquet, B., Fournier, C., Depadt, G., Cappelaere, P. 1984. Preparation and release kinetics of microencapsulated with ethylcellulose. J. Pharm. Pharmacol. 36 : 803-807.
- Hou, W.M., Miyazaki, S., Takeda, M., and Komai, T. 1985. Sustained released of indomethacin from chitosan granules. Chem. Pharm. Bull. 33(9) : 3986-3992.
- John E.H., ed. 1990. Remington's Pharmaceutical Sciences 18th edition. USA : Mack Printing Company.
- John, F.M., Minatoya, H., and Rosenburg, F.J. 1979. Microencapsulation of Bitolterol for controlled release and its effect on bronchodilator and heart rate activity in dogs. J. Pharm. Sci. 68(4) : 475-480.
- Kanke, M., Katayama, H., Isuzuki, S., and Kuramoto, H. 1989. Application of chitin and chitosan to pharmaceutical preparations I. Film preparation and in vitro evaluation. Chem. Pharm. Bull. 37(2) : 523-525.
- Kawashima, Y., Handa, T., Kasai, A., Takenaka, H., Lin, S.Y., and Ando, Y. 1985. Novel method for the preparation of controlled-Delease theophylline granules coated with a polyelectrolyte complex of sodium polyphosphate-chitosan. J. Pharm. Sci. 74 : 264-268.

- Kim, J.H., Kim, J.Y., Lee, Y.M., and Kim, K.Y. 1992. Properties and swelling characteristics of cross-linked poly (vinyl alcohol) /chitosan blend membrane. J. Appl. Polym. Sci. 45 : 1711 - 1717.
- Kim, S.K., and Rha, C. 1989. Transmembrane permeation of proteins in chitosan capsules. In Anthonsen, T. et al (ed.), Chitin and chitosan : Source, Chemistry, Biochemistry, Physical Properties and Application, pp.635-642. Belfast : The universities.
- Klaus, F. ,ed. 1984. Analytical Profiles of Drug Substances. volume 13. USA : Academic Press.
- Koh, G.L., and Tucker, I.G. 1988. Characterization of sodium carboxymethylcellulose-gelatin complex coacervation by viscosity, turbidity and coacervate wet weight and volume measurements. J. Pharm. Pharmacol. 40 : 233-236.
- Kondo, A. 1979a. Application and studies of microcapsules. In Valkenberg, J.W.V. (ed.), Microcapsule Processing and Technology , pp. 19-26. New York : Marcel Dekker.
- _____, 1979b. History and classification of microencapsulation. ibid. pp. 27-34.
- Koyama, Y., and Taniguchi, A. 1986. Studies on chitin homogeneous cross-linking of chitosan for enhanced cupric ion adsorption. J. Appl. Polym. Sci. 31 : 1951-1954.
- Li, S.P., Kawasaki, C.R., Feld, K.M., and Grim, W.M. 1988. Recent advances in microencapsulation technology and equipment. Drug Dev. Ind. Pharm. 14(2&3) : 353-376.
- Lordi, N.G. 1986. Sustain release dosage forms. In Lachman, L. et al. (ed.), The Theory and Practice of Industrial Pharmacy 3th edition, pp.430-456. Philadelphia : Lea&Febiger.

Lower, E.S. 1984. Polymers from the sea chitin & chitosan. Manuf. Chem. 10: 47,49,52.

Luzzi, L.A. 1970. Microencapsulation. J. Pharm. Sci. 59(10) : 1367-1375.

Luzzi, L.A., and Gerraughthy, R.J. 1967. Effects of selected variable on the microencapsulation of solid. J. Pharm. Sci. 56(5) : 634 - 638.

Martin, A. 1993. Physical Pharmacy Fourth edition. USA.: Lea&Febiger.

Mayer et al. 1991. Method of forming a crosslinked chitosan polymer and product thereof. U.S.Patent 5 : 5,015,293.

Mc Evoy, G.K., ed. 1992. AHFS Drug Information 92. Bethesda, MD : American Society of Hospital Pharmacists.

Mc Mullen, J.N., Newton, D.W., and Becker, C.H. 1982. Pectin-gelatin complex coacervates I : determinants of microglobule size, morphology, and recovery as water-dispersible powder. J. Pharm. Sci. 71(6) : 628-633.

_____. 1984. Pectin-gelatin complex coacevates II : effect of microencapsulated sulfamerazine on size, morphology, recovery, and extraction of water dispersible microglobules. J. Pharm. Sci. 73(12) : 1799-1803.

Meshali, M.M. , El-Dien, E.Z. , Omar, S.A., and Luzzi, L.A. 1989. A new approach to encapsulating nonsteroidal antiinflamatory drug III. coating acidic as well as basic nonsteroidal anti inflammatory drug with cellulose derivatives having different functional groups. J. Microencapsulation, 6(3) : 339-353.

- Miyazaki, S., Ishii, K., and Nadai, T. 1981. The use of chitin and chitosan as drug carriers. Chem. Pharm. Bull. 29 : 3067-3069.
- Miyazaki, S., Yamaguchi, H., and Takada, M. 1990. Pharmaceutical application of biomedical polymers XXIX. Preliminary study on film dosage form prepared from chitosan for oral drug delivery. Acta Pharm. Nord. 2(6) : 401-406.
- Moffat, A.C., ed. 1986. Clarke's Isolation and Identification of drugs second edition. London : The Pharmaceutical Press.
- Muzzarelli. 1989. Substituted and crosslinked glucans, process and intermediates for preparing them and use thereof. U.S.Patent 5 : 4,835,265.
- Nakatsuka, S., and Andrade, A.L. 1992. Permeability of vitamin B-12 in chitosan membrane effect of crosslinking and blending with poly(vinyl alcohol) on permeability. J. Appl. Polym. Sci. 44 : 17-28.
- Nigalaye, A.G., Adusumilli, P., and Bolton, S. 1990. Investigation of prolonged drug release from matrix formulations of chitosan. Drug Dev. Ind. Pharm. 16(3) : 449-467.
- Nishioka, Y. et al. 1989. Preparation and release characteristics of cisplatin albumin microspheres containing chitin and treated with chitosan. Chem. Pharm. Bull. 37(11) : 3074-3077.
- Nixon, J.R. and Hassan, M. 1980. The effect of preparative technique on the particle size of thiabendazole microcapsules. J. Pharm. Pharmacol. 32 : 856-857.

Ohya, Y., Takei, T., Kobayashi, H., and Okuchi, T. 1993. Release behaviour of 5-fluouracil from chitosan-gel microspheres immobilizing 5-fluorouracil derivative coated with polysaccharides and their cell specific recognition. J. Microencapsulation. 10(1) : 1-9.

Olin, B.R., ed. 1987. Drug Facts and Comparisons. 1987 editions. USA : Facts and Comparisons Division.

Parichat Chomto. 1992. Application of Chitin and Chitosan as disintegrant in Paracetamol tablet. Master's thesis. Chulalongkorn University.

Sawayanagi, Y., Nambu, N., and Nagai, T. 1982. Direct compressed tablets containing chitin or chitosan in addition to lactose or potato starch. Chem. Pharm. Bull. 30(8) : 2935-2940.

Shioya, T. and Rha, C. 1989. Transmembrane permeability of chitosan/carboxymethylcellulose capsule. In Anthonsen, T. et al. (ed.), Chitin and Chitosan : Source, Chemistry, Biochemistry, Physical Properties and Application, pp. 627-633. Belfast : The universities.

Shirashi, S., Arahira, M., Imai, T., and Otagiri, M. 1990. Enhancement of dissolution rates of several drugs by low-molecular chitosan and alginate. Chem. Pharm. Bull. 38(1) : 185-187.

Skaugrud, O. 1989. Chitosan makes the grade. Manuf. Chem. 9 : 31,33.35.

_____, 1991. Chitosan. Drug Cosmet. Ind. 148(5) : 24,26,30.

Srichatrapimuk Pimporn. 1983. Study of microencapsulation technique for indomethacin. Chulalongkorn university.

Susan,B.,(ed.). 1989. The Merck Index 11th edition. USA : Merck & Co.,Inc.

Takenaka, H., Kawashima, Y., and Lin. S.Y. 1980. Micromeritic properties of sulfamethoxazole microcapsules prepared by gelatin-acacia coacervation. J. Pharm. Sci. 69(5) : 513-516.

Thanoo, B.C., Sunny, M.C., and Jayakrishnan, A. 1992. Cross-linked chitosan microspheres : preparation and evaluation as a matrix for the controlled release of pharmaceuticals. J. Pharm. Pharmacol. 44(6) : 283-286.

The United States Pharmacopeial Convention. 1992. USP XXII NF XVII. Rockville, MD.

Upadrashta, S. M., Katikaneni, P. R., and Nuessle, N. O. 1992. Chitosan as a tablet binder. Drug Dev. Ind. Pharm. 18 : 1701-1708.

Yisong, Y., Wenjun, L., and Tongyin, Y. 1990. Crossling chitosan membranes for pervaporation of alcohol-water mixture. Polymer Communications. 31(8) : 319-321.

APPENDIX

Table 17 : Absorbance of indomethacin in the mixture of methanol and pH 7.5 phosphate buffer (1:1) at 322 nm

Concentration (mcg/ml)	Absorbance
0.00	0.000
15.00	0.273
20.00	0.365
25.00	0.458
30.00	0.551
35.00	0.644
40.00	0.738

Correlation coefficient = 0.999977

$$Y = 0.01846X - 0.0023$$




Figure 67 : Calibration curve of indomethacin in the mixture of methanol and pH 7.5 phosphate buffer (1:1) at 322 nm

Table 18 : Absorbance of indomethacin in the pH 6.2 phosphate at 320 mn

Concentration (mcg/ml)	Absorbance
0.00	0.000
15.00	0.295
20.00	0.392
25.00	0.487
30.00	0.587
35.00	0.681
40.00	0.778

Correlation coefficient = 0.999981

$$Y = 0.01944X + 0.0018$$


**Figure 68 : Absorbance of indomethacin in the pH 6.2 phosphate at 320 mn**

Table 19 : Absorbance of pindolol in the mixture of methanol and chloroform (1:1) at 266 nm

Concentration (mcg/ml)	Absorbance
0.00	0.000
10.00	0.329
12.50	0.412
15.00	0.502
17.50	0.583
20.00	0.670

Correlation coefficient = 0.999916

$$Y = 0.03349X - 0.0026$$




Figure 69 : Absorbance of pindolol in the mixture of methanol and chloroform (1:1) at 266 nm

Table 22 : Cumulative % frequency undersize and Z value of indomethacin microcapsule prepared from various preparations (continue)

Size range (um)	Rx 19		Rx 21		Rx 22		Rx 24		Rx 25	
	CUM %	Z								
32-63	0.00	-	0.00	-	0.16	-2.9500	0.00	-	0.00	-
63-94	0.82	-2.4050	1.11	-2.2900	7.19	-1.4615	3.68	-1.7888	1.48	-2.1750
94-125	3.75	-1.7800	6.37	-1.5343	32.40	-0.4567	18.53	-0.8954	7.84	-1.4160
125-156	12.39	-1.1557	19.40	-0.8634	64.70	0.3773	44.18	-0.1461	22.87	-0.7430
156-187	23.86	-0.7106	35.83	-0.3627	82.25	0.9250	69.07	0.4978	49.24	-0.0190
187-218	43.45	-0.1649	50.67	0.0118	92.30	1.4257	85.29	1.0487	64.59	0.3743
218-249	56.32	0.1590	64.74	0.3784	100.00	-	89.22	1.2378	78.39	0.7855
249-280	69.57	0.5120	73.64	0.6322	-	-	91.12	1.3481	86.84	1.1095
280-311	76.09	0.7094	83.28	0.9652	-	-	96.42	1.8013	94.87	1.6327
311-342	89.29	1.2421	88.86	1.2189	-	-	100.00	-	97.09	1.8929
342-373	95.06	1.6510	93.74	1.5325	-	-	-	-	100.00	-
373-404	100.00	-	100.00	-	-	-	-	-	-	-

Size range (um)	Rx 28		Rx 29		Rx 30	
	CUM %	Z	CUM %	Z	CUM %	Z
32-63	0.00	-	0.00	-	0.04	-2.9971
63-94	1.20	-2.2567	4.15	-1.7333	6.83	-1.4885
94-125	12.67	-1.1420	17.02	-0.9535	27.50	-0.5979
125-156	31.87	-0.4715	40.54	-0.2395	54.43	0.1113
156-187	46.93	-0.0777	59.08	0.2295	67.00	0.4400
187-218	57.82	0.1973	73.17	0.6179	71.36	0.5638
218-249	68.95	0.4942	79.17	0.8124	81.38	0.8919
249-280	75.68	0.6961	86.14	1.0868	88.66	1.2085
280-311	83.20	0.9620	93.44	1.5091	98.43	1.6888
311-342	93.34	1.5015	100.00	-	100.00	-
342-373	100.00	-	-	-	-	-
373-404	-	-	-	-	-	-

Rx = Preparation, CUM % = Cumulative% Frequency Undersize

Table 22 : Cumulative % frequency undersize and Z value of indomethacin microcapsule prepared from various preparations (continue)

Size range (um)	Rx 4					
	batch I		batch II		batch III	
	CUM %	Z	CUM %	Z	CUM %	Z
32-63	-	-	-	-	-	-
63-94	1.25	-2.2400	1.78	-2.1020	3.50	-1.8114
94-125	12.18	-1.1660	19.93	-0.8441	18.98	-0.8782
125-156	35.03	-0.3846	44.61	-0.1355	48.53	-0.0368
156-187	65.19	0.3905	76.80	0.7326	64.18	0.3632
187-218	84.64	1.0213	75.64	1.0643	78.77	0.7986
218-249	94.93	1.6382	90.56	1.3144	87.99	1.1745
249-280	97.92	2.0380	94.14	1.5667	93.73	1.5325
280-311	100.00	-	96.63	1.8288	96.40	1.7988
311-342	-	-	100.00	-	100.00	-
342-373	-	-	-	-	-	-
373-404	-	-	-	-	-	-

Size range (um)	Rx 16					
	batch I		batch II		batch III	
	CUM %	Z	CUM %	Z	CUM %	Z
32-63	0.16	-2.9500	0.37	-2.6800	0.04	-2.9971
63-94	7.06	-1.4714	9.80	-1.2929	5.76	-1.5755
94-125	32.74	-0.4472	30.83	-0.5006	29.29	-0.5450
125-156	63.33	0.3405	48.04	-0.0492	59.03	0.2282
156-187	79.65	0.8293	64.05	0.3597	77.53	0.7563
187-218	90.64	1.3188	74.84	0.6694	88.80	1.2158
218-249	100.00	-	82.10	0.9227	93.98	1.5433
249-280	-	-	87.53	1.1519	96.50	1.8114
280-311	-	-	94.98	1.6430	100.00	-
311-342	-	-	100.00	-	-	-
342-373	-	-	-	-	-	-
373-404	-	-	-	-	-	-

Rx = Preparation, CUM % = Cumulative% Frequency Undersize

Table 23 : Geometric mean diameter (D_{50}) of indomethacin microcapsule prepared from various preparations

Preparation	D_{50} (micron)
1	187.15
2	151.11
3	170.46
4	151.14
5	166.47
6	163.2
7	170.69
8	155.78
11	194.75
13	174.35
14	146.93
15	204.24
16	128.26
17	143.8
18	184.95
19	212.23
21	199.77
22	126.17
24	149.21
25	174.76
28	185.5
29	160.4
30	150.3

Table 24 : Percentage amount of indomethacin release from microcapsule prepared from various preparations

Preparation	Time (hr)	Cumulative % of drug release			Mean	SD
		A	B	C		
1	0.00	0.00	0.00	0.00	0.00	0.00
	0.25	2.06	2.43	2.25	2.25	0.19
	0.50	2.72	3.00	2.54	2.75	0.23
	0.75	3.76	3.67	3.02	3.48	0.40
	1.00	4.61	4.80	4.33	4.58	0.24
	2.00	8.26	8.36	6.40	7.67	1.10
	3.00	11.64	11.37	10.05	11.02	0.85
	5.00	17.46	16.91	15.58	16.65	0.97
	7.00	22.11	21.36	22.07	21.85	0.42
	9.00	26.12	24.26	26.55	25.64	1.22
	12.00	31.18	28.48	32.08	30.58	1.87
2	0.00	0.00	0.00	0.00	0.00	0.00
	0.25	2.80	3.08	3.45	3.11	0.33
	0.50	3.47	3.75	3.66	3.63	0.14
	0.75	4.79	4.88	5.16	4.94	0.19
	1.00	6.11	6.12	6.49	6.24	0.22
	2.00	10.32	10.88	11.54	10.91	0.61
	3.00	15.30	15.77	16.61	15.89	0.66
	5.00	22.62	23.37	24.96	23.65	1.19
	7.00	29.61	29.81	31.59	30.34	1.09
	9.00	34.78	33.31	36.13	34.74	1.41
	12.00	38.13	37.67	41.33	39.04	1.99
3	0.00	0.00	0.00	0.00	0.00	0.00
	0.25	3.36	3.08	3.08	3.17	0.16
	0.50	4.40	4.31	4.03	4.25	0.19
	0.75	6.09	5.54	5.53	5.72	0.32
	1.00	7.89	6.96	7.05	7.30	0.51
	2.00	12.94	12.19	13.21	12.78	0.53
	3.00	17.10	17.18	17.83	17.37	0.40
	5.00	22.20	21.54	24.79	22.84	1.72
	7.00	28.91	29.45	33.10	30.49	2.28
	9.00	31.30	32.86	38.84	34.33	3.98
	12.00	37.41	38.61	45.46	40.49	4.34
6	0.00	0.00	0.00	0.00	0.00	0.00
	0.25	2.53	2.71	2.80	2.68	0.14
	0.50	3.56	4.12	4.40	4.03	0.43
	0.75	4.69	5.72	6.00	5.47	0.69
	1.00	6.11	6.96	7.33	6.80	0.63
	2.00	9.76	10.80	11.82	10.79	1.03
	3.00	13.81	14.94	15.69	14.81	0.95
	5.00	19.17	19.75	21.25	20.06	1.07
	7.00	24.10	24.13	25.82	24.68	0.98
	9.00	27.85	27.51	29.86	28.41	1.27
	12.00	32.18	31.74	34.66	32.86	1.57

SD = Standard deviation

Table 24 : Percentage amount of indomethacin release from microcapsule prepared from various preparations (continue)

Preparation	Time (hr)	Cumulative % of drug release			Mean	SD
		A	B	C		
7	0.00	0.00	0.00	0.00	0.00	0.00
	0.25	3.92	4.47	3.73	4.04	0.38
	0.50	5.05	5.15	4.68	4.96	0.25
	0.75	6.47	6.85	6.19	6.50	0.33
	1.00	7.53	8.18	7.34	7.68	0.44
	2.00	11.75	12.87	11.83	12.15	0.62
	3.00	15.61	17.39	16.26	16.42	0.90
	5.00	20.62	23.24	21.64	21.83	1.32
	7.00	25.28	28.93	28.25	27.49	1.94
	9.00	28.20	32.62	32.95	31.26	2.65
	12.00	32.34	37.62	39.53	36.50	3.72
8	0.00	0.00	0.00	0.00	0.00	0.00
	0.25	4.47	4.94	4.47	4.63	0.27
	0.50	6.45	6.54	6.73	6.57	0.14
	0.75	8.90	8.34	8.80	8.68	0.30
	1.00	11.36	10.06	10.89	10.77	0.66
	2.00	18.01	15.40	16.52	16.64	1.31
	3.00	23.49	19.85	21.34	21.56	1.83
	5.00	30.48	26.36	28.88	28.57	2.08
	7.00	36.31	31.23	34.52	34.02	2.58
	9.00	41.05	35.12	40.46	38.88	3.27
	12.00	43.97	39.67	42.53	42.06	2.19
17	0.00	0.00	0.00	0.00	0.00	0.00
	0.25	13.38	12.64	13.29	13.10	0.40
	0.50	15.31	15.21	16.52	15.68	0.73
	0.75	16.51	16.88	18.74	17.38	1.20
	1.00	18.83	18.36	20.24	19.14	0.98
	2.00	23.01	22.36	25.08	23.48	1.42
	3.00	27.22	25.36	28.74	27.11	1.69
	5.00	33.31	30.32	34.84	32.82	2.30
	7.00	38.22	34.66	37.63	36.84	1.91
	9.00	42.60	38.93	41.26	40.93	1.86
	12.00	48.22	43.50	44.46	45.39	2.49
25	0.00	0.00	0.00	0.00	0.00	0.00
	0.25	19.23	15.14	15.70	16.69	2.22
	0.50	24.16	19.50	19.31	20.99	2.75
	0.75	26.80	21.92	21.55	23.42	2.93
	1.00	28.43	23.71	23.34	25.16	2.84
	2.00	32.95	28.76	27.65	29.79	2.80
	3.00	36.09	32.35	31.32	33.25	2.51
	5.00	41.12	37.45	37.34	38.64	2.15
	7.00	45.51	41.45	43.30	43.42	2.03
	9.00	50.12	46.04	48.91	48.36	2.10
	12.00	54.38	49.26	55.86	53.17	3.46

SD = Standard deviation

Table 24 : Percentage amount of indomethacin release from microcapsule prepared from various preparations (continue)

Preparation	Time (hr)	Cumulative % of drug release			Mean	SD
		A	B	C		
4 batch I	0.00	0.00	0.00	0.00	0.00	0.00
	0.25	10.23	10.32	10.97	10.51	0.40
	0.50	15.94	15.02	15.02	15.33	0.53
	0.75	22.16	20.20	20.30	20.89	1.10
	1.00	27.75	24.21	24.68	25.55	1.92
	2.00	42.56	36.78	36.60	38.65	3.39
	3.00	52.63	47.28	47.19	49.03	3.12
	5.00	65.45	60.81	60.35	62.20	2.82
	7.00	72.39	67.63	69.31	69.78	2.41
	9.00	75.96	72.48	74.71	74.38	1.76
	12.00	85.28	79.92	83.66	82.95	2.75
	15.00	90.20	85.55	88.75	88.17	2.38
	18.00	94.77	90.84	93.31	92.97	1.99
	24.00	99.36	95.97	96.78	97.37	1.77
4 batch II	0.00	0.00	0.00	0.00	0.00	0.00
	0.25	9.86	8.93	11.43	10.07	1.26
	0.50	14.55	12.50	14.84	13.96	1.28
	0.75	18.06	16.10	18.63	17.60	1.33
	1.00	21.04	19.62	21.98	20.88	1.19
	2.00	35.07	31.23	33.23	33.18	1.92
	3.00	42.87	39.11	40.56	40.85	1.90
	5.00	53.59	49.34	50.25	51.06	2.24
	7.00	60.84	57.87	58.97	59.23	1.50
	9.00	66.56	64.59	65.60	65.58	0.99
	12.00	73.23	72.08	73.56	72.96	0.78
	15.00	79.03	79.82	79.73	79.53	0.43
	18.00	84.65	86.57	84.43	85.22	1.18
	24.00	97.17	97.80	95.84	96.94	1.00
4 batch III	0.00	0.00	0.00	0.00	0.00	0.00
	0.25	17.37	18.02	16.35	17.25	0.84
	0.50	20.81	21.09	19.97	20.62	0.58
	0.75	23.61	24.36	22.50	23.49	0.94
	1.00	26.99	27.46	26.23	26.89	0.62
	2.00	40.31	40.79	38.62	39.91	1.14
	3.00	50.37	51.50	48.67	50.18	1.42
	5.00	62.99	63.38	60.44	62.27	1.60
	7.00	69.18	69.57	66.90	68.55	1.44
	9.00	73.45	73.75	71.53	72.91	1.20
	12.00	78.42	78.63	76.67	77.91	1.08
	15.00	83.29	82.58	80.24	82.04	1.60
	18.00	88.57	88.22	85.31	87.37	1.79
	24.00	100.90	99.45	93.19	97.85	4.10

SD = Standard deviation

Table 24 : Percentage amount of indomethacin release from microcapsule prepared from various preparations (continue)

Preparation	Time (hr)	Cumulative % of drug release			Mean	SD
		A	B	C		
5	0.00	0.00	0.00	0.00	0.00	0.00
	0.25	9.67	11.06	11.06	10.60	0.80
	0.50	10.93	11.40	11.87	11.40	0.47
	0.75	14.79	14.80	16.48	15.36	0.97
	1.00	18.68	18.60	20.74	19.34	1.21
	2.00	30.10	29.28	31.53	30.30	1.14
	3.00	37.97	37.23	40.79	38.66	1.88
	5.00	48.11	46.25	50.30	48.22	2.03
	7.00	58.20	57.27	61.61	59.03	2.29
	9.00	63.72	61.66	66.59	63.99	2.48
	12.00	68.89	66.27	72.80	69.32	3.29
	15.00	73.64	69.15	76.37	73.05	3.65
	18.00	79.42	75.46	81.79	78.89	3.20
	24.00	86.90	81.99	86.68	85.19	2.77
11	0.00	0.00	0.00	0.00	0.00	0.00
	0.25	6.61	7.07	6.70	6.79	0.24
	0.50	11.47	10.92	11.01	11.13	0.30
	0.75	16.17	15.61	15.06	15.61	0.56
	1.00	20.53	19.97	19.04	19.85	0.75
	2.00	33.08	31.77	30.74	31.86	1.17
	3.00	42.44	41.32	40.09	41.28	1.18
	5.00	54.46	53.23	53.12	53.60	0.74
	7.00	61.72	60.11	60.37	60.73	0.86
	9.00	67.16	65.54	66.27	66.32	0.81
	12.00	72.63	70.73	71.82	71.73	0.95
	15.00	76.20	72.99	74.46	74.55	1.61
	18.00	81.80	78.95	80.06	80.27	1.44
	24.00	89.11	87.54	89.77	88.81	1.15
13	0.00	0.00	0.00	0.00	0.00	0.00
	0.25	9.48	9.39	10.50	9.79	0.62
	0.50	11.58	12.78	12.33	12.23	0.61
	0.75	13.31	14.99	14.06	14.12	0.84
	1.00	14.59	16.65	15.81	15.68	1.04
	2.00	18.66	21.38	19.80	19.95	1.37
	3.00	21.45	25.86	23.34	23.55	2.21
	5.00	27.14	31.75	33.67	30.85	3.36
	7.00	33.04	36.75	38.40	36.06	2.75
	9.00	40.64	41.59	41.30	41.18	0.49
	12.00	54.22	47.57	46.35	49.38	4.24
	15.00	65.28	52.83	52.73	56.95	7.22
	18.00	72.69	56.28	59.88	62.95	8.63
	24.00	87.30	64.39	71.63	74.44	11.71

SD = Standard deviation

Table 24 : Percentage amount of indomethacin release from microcapsule prepared from various preparations (continue)

Preparation	Time (hr)	Cumulative % of drug release			Mean	SD
		A	B	C		
14	0.00	0.00	0.00	0.00	0.00	0.00
	0.25	12.45	12.27	14.40	13.04	1.18
	0.50	12.99	13.36	15.50	13.95	1.36
	0.75	14.64	14.73	17.63	15.67	1.70
	1.00	16.39	16.11	19.95	17.48	2.14
	2.00	22.51	20.47	25.17	22.72	2.36
	3.00	27.55	24.10	29.11	26.92	2.56
	5.00	34.56	29.80	34.28	32.88	2.67
	7.00	39.58	33.77	37.99	37.11	3.00
	9.00	43.69	37.20	41.81	40.90	3.34
	12.00	55.71	46.12	48.91	50.25	4.93
	15.00	61.77	51.29	54.65	55.90	5.35
	18.00	74.35	56.49	59.58	63.47	9.55
	24.00	88.60	71.56	69.38	76.51	10.52
15	0.00	0.00	0.00	0.00	0.00	0.00
	0.25	8.46	10.13	8.74	9.11	0.89
	0.50	10.27	11.30	11.11	10.89	0.55
	0.75	12.84	13.59	13.31	13.25	0.38
	1.00	15.32	16.27	15.23	15.61	0.58
	2.00	24.59	24.61	21.72	23.64	1.66
	3.00	32.52	33.01	28.06	31.20	2.73
	5.00	49.30	52.21	39.53	47.01	6.64
	7.00	60.43	60.47	51.81	57.57	4.99
	9.00	67.63	67.67	63.04	66.11	2.66
	12.00	76.37	74.93	73.61	74.97	1.38
	15.00	82.16	80.71	81.43	81.43	0.73
	18.00	85.95	83.94	86.89	85.59	1.51
	24.00	91.43	90.33	92.37	91.38	1.02
16 batch I	0.00	0.00	0.00	0.00	0.00	0.00
	0.25	10.97	12.08	12.45	11.83	0.77
	0.50	13.26	13.63	13.08	13.32	0.28
	0.75	16.21	16.68	15.38	16.09	0.66
	1.00	19.26	19.83	18.99	19.36	0.43
	2.00	29.30	29.96	28.37	29.21	0.80
	3.00	36.79	37.92	36.51	37.07	0.75
	5.00	45.34	48.24	47.19	46.92	1.47
	7.00	55.42	58.53	58.49	57.48	1.78
	9.00	60.27	63.58	64.01	62.62	2.05
	12.00	67.84	69.12	70.01	68.99	1.09
	15.00	72.94	72.83	74.85	73.54	1.14
	18.00	77.90	76.31	79.82	78.01	1.76
	24.00	87.04	84.33	88.23	86.53	2.00

SD = Standard deviation

Table 24 : Percentage amount of indomethacin release from microcapsule prepared from various preparations (continue)

Preparation	Time (hr)	Cumulative % of drug release			Mean	SD
		A	B	C		
16 batch II	0.00	0.00	0.00	0.00	0.00	0.00
	0.25	11.06	9.86	9.11	10.01	0.98
	0.50	11.49	10.93	10.00	10.81	0.75
	0.75	14.06	13.03	12.28	13.12	0.89
	1.00	16.55	15.24	14.58	15.46	1.00
	2.00	25.83	24.23	22.45	24.17	1.69
	3.00	31.54	28.63	27.58	29.25	2.05
	5.00	40.80	36.67	35.81	37.76	2.67
	7.00	48.08	43.46	42.68	44.74	2.92
	9.00	54.74	48.99	48.11	50.61	3.60
	12.00	62.09	55.01	54.78	57.29	4.16
	15.00	68.65	60.50	60.73	63.29	4.64
	18.00	73.66	67.88	67.28	69.61	3.52
	24.00	81.03	76.15	76.66	77.95	2.68
16 batch III	0.00	0.00	0.00	0.00	0.00	0.00
	0.25	11.99	11.25	9.67	10.97	1.19
	0.50	14.28	13.63	12.79	13.57	0.75
	0.75	16.96	16.49	15.36	16.27	0.82
	1.00	19.47	19.18	18.42	19.02	0.54
	2.00	28.39	28.93	27.52	28.28	0.71
	3.00	35.69	36.79	33.98	35.49	1.42
	5.00	44.14	47.11	43.16	44.80	2.06
	7.00	50.13	54.04	50.82	51.66	2.09
	9.00	54.68	60.19	56.11	56.99	2.86
	12.00	60.82	67.66	62.45	63.64	3.57
	15.00	66.62	74.52	67.70	69.61	4.28
	18.00	71.08	79.58	71.61	74.09	4.76
	24.00	79.82	89.29	81.65	83.59	5.02
18	0.00	0.00	0.00	0.00	0.00	0.00
	0.25	17.83	16.16	16.72	16.90	0.85
	0.50	21.65	18.85	19.13	19.88	1.54
	0.75	24.08	21.55	21.65	22.43	1.43
	1.00	26.35	23.99	24.00	24.78	1.36
	2.00	33.55	30.16	31.00	31.57	1.77
	3.00	39.11	35.98	38.31	37.80	1.63
	5.00	47.03	44.53	45.57	45.71	1.26
	7.00	54.06	52.75	53.33	53.38	0.66
	9.00	58.99	59.35	59.56	59.30	0.29
	12.00	69.14	71.08	70.28	70.17	0.97
	15.00	73.44	77.24	74.48	75.05	1.96
	18.00	79.03	81.93	80.08	80.35	1.47
	24.00	86.69	88.68	86.08	87.15	1.36

SD = Standard deviation

Table 24 : Percentage amount of indomethacin release from microcapsule prepared from various preparations (continue)

Preparation	Time (hr)	Cumulative % of drug release			Mean	SD
		A	B	C		
19	0.00	0.00	0.00	0.00	0.00	0.00
	0.25	12.92	10.97	11.90	11.93	0.98
	0.50	15.40	13.07	14.00	14.16	1.17
	0.75	17.71	15.18	16.31	16.40	1.27
	1.00	20.22	17.03	18.25	18.50	1.61
	2.00	27.20	23.16	23.92	24.76	2.15
	3.00	32.82	28.57	28.88	30.09	2.37
	5.00	44.97	41.90	40.26	42.38	2.39
	7.00	53.10	50.85	58.92	54.29	4.16
	9.00	60.26	58.18	57.36	58.60	1.49
	12.00	68.20	66.94	65.93	67.02	1.14
	15.00	74.15	73.45	70.48	72.69	1.95
	18.00	79.57	78.30	76.80	78.22	1.39
	24.00	86.68	85.78	84.45	85.64	1.12
21	0.00	0.00	0.00	0.00	0.00	0.00
	0.25	14.96	14.22	12.55	13.91	1.23
	0.50	20.42	18.19	15.40	18.00	2.52
	0.75	21.09	20.06	17.34	19.50	1.94
	1.00	22.42	21.56	18.27	20.75	2.19
	2.00	25.69	25.02	21.90	24.20	2.02
	3.00	28.43	27.47	24.24	26.71	2.20
	5.00	32.76	31.61	28.18	30.85	2.38
	7.00	36.19	35.03	32.14	34.45	2.09
	9.00	40.46	39.21	36.49	38.72	2.03
	12.00	50.98	48.42	48.84	49.41	1.37
	15.00	60.07	57.03	58.94	58.68	1.54
	18.00	66.52	63.56	65.57	65.22	1.51
	24.00	75.07	73.29	74.85	74.40	0.97
22	0.00	0.00	0.00	0.00	0.00	0.00
	0.25	29.43	29.99	29.71	29.71	0.28
	0.50	31.08	32.94	31.08	31.70	1.07
	0.75	34.04	36.83	34.50	35.12	1.50
	1.00	36.36	39.08	36.27	37.24	1.60
	2.00	44.44	47.36	44.82	45.54	1.59
	3.00	48.77	51.43	48.87	49.69	1.51
	5.00	56.74	58.02	56.74	57.17	0.74
	7.00	60.57	62.04	61.41	61.34	0.74
	9.00	64.33	64.98	64.16	64.49	0.43
	12.00	69.04	69.87	69.42	69.44	0.42
	15.00	74.07	76.39	74.45	74.97	1.24
	18.00	78.18	80.70	78.75	79.21	1.32
	24.00	88.24	88.55	91.23	89.34	1.64

SD = Standard deviation

Table 24 : Percentage amount of indomethacin release from microcapsule prepared from various preparations (continue)

Preparation	Time (hr)	Cumulative % of drug release			Mean	SD
		A	B	C		
24	0.00	0.00	0.00	0.00	0.00	0.00
	0.25	27.30	23.12	23.03	24.48	2.44
	0.50	33.57	28.26	28.54	30.12	2.99
	0.75	37.01	33.60	32.04	34.22	2.54
	1.00	39.53	39.72	34.44	37.90	3.00
	2.00	45.78	43.00	40.01	42.93	2.89
	3.00	49.46	39.08	43.85	44.13	5.20
	5.00	54.74	56.59	50.21	53.85	3.28
	7.00	63.20	62.28	58.19	61.22	2.67
	9.00	69.20	70.50	62.58	67.43	4.25
	12.00	75.89	75.17	69.23	73.43	3.66
	15.00	80.86	80.00	74.45	78.44	3.48
	18.00	83.52	87.51	81.16	84.06	3.21
	24.00	92.69	87.54	89.57	89.93	2.59
28	0.00	0.00	0.00	0.00	0.00	0.00
	0.25	19.60	19.32	19.04	19.32	0.28
	0.50	19.80	20.82	20.35	20.32	0.51
	0.75	22.69	23.53	23.43	23.22	0.46
	1.00	25.42	26.72	26.07	26.07	0.65
	2.00	34.55	36.70	34.19	35.15	1.36
	3.00	40.87	43.96	39.11	41.31	2.46
	5.00	48.61	53.75	46.10	49.49	3.90
	7.00	54.07	60.17	51.36	55.20	4.51
	9.00	56.96	64.12	57.20	59.43	4.07
	12.00	65.99	69.57	65.68	67.08	2.16
	15.00	68.41	78.59	70.42	72.47	5.39
	18.00	72.86	84.03	77.29	78.06	5.62
	24.00	82.34	91.90	87.91	87.38	4.80
29	0.00	0.00	0.00	0.00	0.00	0.00
	0.25	12.64	10.60	10.50	11.25	1.21
	0.50	15.12	14.09	13.53	14.25	0.81
	0.75	18.36	17.23	16.11	17.23	1.13
	1.00	19.95	19.92	18.52	19.46	0.82
	2.00	27.66	26.90	25.49	26.68	1.10
	3.00	32.83	31.68	30.45	31.65	1.19
	5.00	40.71	39.93	39.06	39.90	0.83
	7.00	47.05	46.74	46.14	46.64	0.46
	9.00	52.60	54.23	52.61	53.15	0.94
	12.00	60.12	65.84	60.60	62.19	3.17
	15.00	71.79	75.31	70.78	72.63	2.38
	18.00	80.15	82.77	78.96	80.63	1.95
	24.00	94.69	95.28	92.56	94.18	1.43

SD = Standard deviation

Table 24 : Percentage amount of indomethacin release from microcapsule prepared from various preparations (continue)

Preparation	Time (hr)	Cumulative % of drug release			Mean	SD
		A	B	C		
30	0.00	0.00	0.00	0.00	0.00	0.00
	0.25	13.10	11.90	11.62	12.21	0.79
	0.50	13.83	13.45	12.98	13.42	0.43
	0.75	16.13	15.10	15.19	15.47	0.57
	1.00	18.44	17.41	18.05	17.97	0.52
	2.00	27.45	25.76	26.88	26.70	0.86
	3.00	33.36	32.21	34.26	33.28	1.03
	5.00	42.72	42.50	45.77	43.66	1.83
	7.00	48.80	49.60	54.74	51.05	3.22
	9.00	52.78	55.35	57.64	55.26	2.43
	12.00	67.08	72.07	73.07	70.74	3.21
	15.00	71.64	78.14	78.22	76.00	3.78
	18.00	77.96	84.88	85.14	82.66	4.07
	24.00	87.11	93.31	92.47	90.96	3.36

SD = Standard deviation

Table 25 : Percentage drug release of preparations which are conforming drug release of the USP specification

Time (hr.)	Rx 4 batch I		Rx 4*batch II		Rx 4 batch III		Rx 5	
	Mean	SD.	Mean	SD.	Mean	SD.	Mean	SD.
0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
0.25	10.50	0.40	10.07	1.26	17.25	0.84	10.60	0.80
0.50	15.33	0.53	13.96	1.28	20.62	0.58	11.40	0.47
0.75	20.89	1.10	17.60	1.33	23.49	0.94	15.36	0.97
1.00	25.55	1.92	20.88	1.19	26.90	0.62	19.34	1.21
2.00	38.65	3.39	33.18	1.92	39.91	1.14	30.30	1.14
3.00	49.03	3.12	40.85	1.90	50.18	1.42	38.66	1.88
5.00	62.20	2.82	51.06	2.24	62.27	1.60	48.22	2.03
7.00	69.78	2.41	59.23	1.50	68.55	1.44	59.03	2.29
9.00	74.39	1.76	65.58	0.99	72.91	1.20	63.99	2.48
12.00	82.95	2.75	72.96	0.78	77.90	1.08	69.32	3.29
15.00	88.17	2.38	79.53	0.43	82.04	1.60	73.05	3.65
18.00	92.97	1.99	85.22	1.18	87.37	1.79	78.89	3.20
24.00	97.37	1.77	96.93	1.00	97.85	4.10	85.19	2.77

Time (hr.)	Rx 11		Rx 15		Rx 16 batch I		Rx 16 batch II	
	Mean	SD.	Mean	SD.	Mean	SD.	Mean	SD.
0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
0.25	6.79	0.24	9.11	0.89	11.83	0.77	10.01	0.98
0.50	11.13	0.30	10.90	0.55	13.32	0.28	10.81	0.75
0.75	15.69	0.56	13.24	0.38	16.09	0.66	13.13	0.89
1.00	19.85	0.75	15.61	0.58	19.36	0.43	15.46	1.00
2.00	31.86	1.17	23.64	1.66	29.21	0.80	24.17	1.69
3.00	41.28	1.18	31.19	2.73	37.07	0.75	29.25	2.05
5.00	53.60	0.74	47.01	6.64	46.92	1.47	37.76	2.67
7.00	60.73	0.86	57.57	4.99	57.48	1.78	44.74	2.92
9.00	66.32	0.81	66.11	2.66	62.62	2.05	50.61	3.60
12.00	71.72	0.95	74.97	1.38	68.99	1.09	57.29	4.16
15.00	74.55	1.61	81.44	0.73	73.54	1.14	63.29	4.64
18.00	80.27	1.44	85.89	1.51	78.01	1.76	69.61	3.52
24.00	88.80	1.15	91.37	1.02	86.53	2.00	77.95	2.68

Mean of three determination

Rx = Preparation

SD = Standard deviation

Table 25 : Percentage drug release of preparations which are conforming drug release of the USP specification (continue)

Time (hr.)	Rx 16 batch III		Rx 18		Rx 19		Rx 22	
	Mean	SD.	Mean	SD.	Mean	SD.	Mean	SD.
0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
0.25	10.97	1.19	16.91	0.85	11.93	0.98	29.71	0.28
0.50	13.57	0.75	19.88	1.54	14.16	1.17	31.70	1.07
0.75	16.27	0.82	22.43	1.43	16.40	1.27	35.12	1.50
1.00	19.02	0.54	24.78	1.36	18.50	1.61	37.23	1.60
2.00	28.28	0.71	31.57	1.77	24.76	2.15	45.54	1.59
3.00	35.49	1.42	37.80	1.63	30.09	2.37	49.69	1.51
5.00	44.80	2.06	45.71	1.26	42.38	2.39	57.16	0.74
7.00	51.67	2.09	53.38	0.66	50.96	4.16	61.34	0.74
9.00	56.99	2.86	59.30	0.29 [*]	58.60	1.49	64.49	0.43
12.00	63.64	3.57	70.17	0.97	67.02	1.14	69.44	0.42
15.00	69.61	4.28	75.05	1.96	72.70	1.95	74.97	1.24
18.00	74.09	4.76	80.34	1.47	78.22	1.39	79.21	1.32
24.00	83.59	5.02	87.15	1.36	85.64	1.12	89.34	1.64

Time (hr.)	Rx 24		Rx 28		Rx 29		Rx 30	
	Mean	SD.	Mean	SD.	Mean	SD.	Mean	SD.
0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
0.25	24.48	2.44	19.32	0.28	11.25	1.21	12.21	0.79
0.50	30.12	2.99	20.32	0.51	14.25	0.81	13.42	0.43
0.75	34.22	2.54	23.22	0.46	17.23	1.13	15.47	0.57
1.00	37.90	3.00	26.07	0.65	19.46	0.82	17.97	0.52
2.00	42.93	2.89	35.15	1.36	26.68	1.10	26.70	0.86
3.00	44.13	5.20	41.31	2.46	31.65	1.19	33.28	1.03
5.00	53.85	3.28	49.49	3.90	39.90	0.83	43.66	1.83
7.00	61.22	2.67	55.20	4.51	46.64	0.46	51.05	3.22
9.00	67.43	4.25	59.43	4.07	53.14	0.94	55.25	2.43
12.00	73.43	3.66	67.08	2.16	62.19	3.17	70.74	3.21
15.00	78.44	3.48	72.47	5.39	72.63	2.38	76.00	3.78
18.00	84.06	3.21	78.06	5.62	80.63	1.95	82.66	4.07
24.00	89.90	2.59	87.39	4.80	94.18	1.43	90.96	3.36

Mean of three determination

Rx = Preparation

SD = Standard deviation

Table 26 : Percentage drug release of preparations which are not conforming drug release of the USP specification

Time (hr.)	Rx 1		Rx 2		Rx 3		Rx 6	
	Mean	SD.	Mean	SD.	Mean	SD.	Mean	SD.
0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
0.25	2.25	0.19	3.11	0.33	3.18	0.16	2.68	0.14
0.50	2.76	0.23	3.63	0.14	4.24	0.19	4.03	0.43
0.75	3.48	0.40	4.94	0.19	5.72	0.32	5.47	0.69
1.00	4.58	0.24	6.24	0.22	7.30	0.51	6.80	0.63
2.00	7.67	1.10	10.91	0.61	12.78	0.53	10.79	1.03
3.00	11.02	0.85	15.89	0.66	17.37	0.40	14.81	0.95
5.00	16.65	0.97	23.65	1.19	22.85	1.72	20.06	1.07
7.00	21.84	0.42	30.33	1.09	30.49	2.28	24.68	0.98
9.00	25.64	1.22	34.74	1.41	34.33	3.98	28.41	1.27
12.00	30.58	1.87	39.04	1.99	40.49	4.34	32.86	1.57

Time (hr.)	Rx 7		Rx 8		Rx 17		Rx 25	
	Mean	SD.	Mean	SD.	Mean	SD.	Mean	SD.
0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
0.25	4.04	0.38	4.63	0.27	13.10	0.40	16.69	2.22
0.50	4.96	0.25	6.57	0.14	15.68	0.73	20.99	2.75
0.75	6.50	0.33	8.68	0.30	17.38	1.20	23.43	2.93
1.00	7.68	0.44	10.77	0.66	19.14	0.98	25.16	2.84
2.00	12.15	0.62	16.64	1.31	23.48	1.42	29.78	2.80
3.00	16.42	0.90	21.56	1.83	27.11	1.69	33.26	2.51
5.00	21.83	1.32	26.57	2.08	32.82	2.30	38.63	2.15
7.00	27.49	1.94	34.02	2.58	36.84	1.91	43.42	2.03
9.00	31.26	2.65	38.88	3.27	40.93	1.86	48.36	2.10
12.00	36.50	3.72	42.06	2.19	45.39	2.49	53.17	3.46

Time (hr.)	Rx 13		Rx 14		Rx 21	
	Mean	SD.	Mean	SD.	Mean	SD.
0.00	0.00	0.00	0.00	0.00	0.00	0.00
0.25	9.79	0.62	13.04	1.18	13.91	1.23
0.50	12.23	0.61	13.95	1.36	18.00	2.52
0.75	14.12	0.84	15.66	1.70	19.50	1.94
1.00	15.68	1.04	17.48	2.14	20.75	2.19
2.00	19.95	1.37	22.71	2.36	24.20	2.02
3.00	23.55	2.21	26.92	2.56	26.72	2.20
5.00	30.85	3.36	32.88	2.67	30.85	2.38
7.00	36.06	2.75	37.11	3.00	34.45	2.09
9.00	41.18	0.49	40.90	3.34	38.72	2.03
12.00	49.38	4.24	50.25	4.93	49.41	1.37
15.00	56.95	7.22	55.90	5.35	58.68	1.54
18.00	62.95	8.63	63.47	9.55	65.22	1.51
24.00	74.44	11.71	76.51	10.52	74.40	0.97

Mean of three determination

Rx =Preparation

SD = standard deviation

Table 27 : Slope of Higuchi's plot of indomethacin microcapsules prepared from different concentration of chitosan solutions

Preparation	Chitosan soln. conc. (%w/v)	Slope			SD
		A	B	C	
28	0.25	18.14	21.94	17.42	2.43
16	0.50	18.32	16.12	16.10	1.28
29	0.75	17.11	17.43	16.92	0.26
30	1.00	17.88	18.48	20.02	1.19

SD = Standard deviation

Table 28 : Slope of Higuchi's plot of indomethacin microcapsules prepared from various batches of preparations 4 and 16

Preparation	Batch (no)	Slope			SD
		A	B	C	
4	I	31.67	27.73	27.54	2.33
	II	25.10	22.85	22.68	1.35
	III	28.19	28.66	27.26	0.71
16	I	18.32	16.12	16.10	1.28
	II	20.99	22.14	21.89	0.60
	III	18.43	20.87	19.15	1.25

SD = Standard deviation

137

Biography

Miss Waree Tiyaboonchai was born on October 24, 1966. She got her degree in Bachelor of Science in Pharmacy in 1990 from Faculty of Pharmaceutical Science, Chulalongkorn University, Thailand.

