

REFERENCES

1. Kamiyama, M.; Maeda, M.; Totsuka, H.; and Hamanaka, T. Properties of Polymerized Toners. J. Imaging Sci. and Techno. 39(5) (1995): 433-438.
2. Uchiyama, M.; Nakamura, T.; and Yachi, S. Toner for developing electrostatic image. U.S. Pat 5.795.694. (Aug. 18, 1998).
3. Koyama, M.; Hayashi, K.; Kikuchi, T.; and Tsujita, K. Synthesis and Characteristics of Non-Spherical Toner by Polymerization Method. Recent Progress in Toner Technology. IS & T, George Marshall, 1997, pp. 369-372.
4. Kiparissides, C. Polymerization Reactor Modeling: A Review of Recent Developments and Future Directions. Chem. Eng. Sci. 51 (1996): 1637-1659.
5. Odian, G. Principles of Polymerization. 3rd ed. New York: John Wiley & Sons, 1991, pp. 198-243.
6. Vivaldo-Lima, E.; Wood, P. E.; and Hamielec, A. E. An Updated Review on Suspension Polymerization. Ind. Eng. Chem. Res. 36 (1997): 939-965.
7. Kroschwitz, J. I. Concise Encyclopedia of Polymer Science and Engineering. New York: John Wiley & Sons, 1990, pp. 1066-1067.
8. Trommsdroff, E.; and Schildknecht, C. E. Polymer Process. Vol. X. New York: Wiley-interscience Publication, 1956, pp. 69-109.
9. Gruber, R. J.; and Julien, P. C. Dry Toner Technology in Handbook of Imaging Materials. New York, Marcel Dekker, 1991, pp. 159.

10. Gruber, R. J.; and Julien, P. C. Dry Toner Technology in Handbook of Imaging Materials. New York, Marcel Dekker, 1991, pp. 159.
11. Gruber, R. J.; and Julien, P. C. Dry Toner Technology in Handbook of Imaging Materials. New York, Marcel Dekker, 1991, pp. 159.
12. Gruber, R. J.; and Julien, P. C. Dry Toner Technology in Handbook of Imaging Materials. New York, Marcel Dekker, 1991, pp. 160.
13. Gruber, R. J.; and Julien, P. C. Dry Toner Technology in Handbook of Imaging Materials. New York, Marcel Dekker, 1991, pp. 160-170.
14. Kamiyama, M.; Koyama, K.; Matsuda, H.; and Sano, Y. Micron-Sized Polymeric Microsphere by Suspension Polymerization. J. Appl. Polym. Sci. 50 (1993): 107-113.
15. Winslow, F. H.; and Matreyek, W. Particle Size in Suspension Polymerization. Ind. Eng. Chem. 43(5) (1951): 1108-1112.
16. Almog, Y.; and Levy, M. Studies of Particle Size Distribution and Adsorption of Stabilizers in Dispersion Polymerization. J. Polym. Sci. A. 20 (1982): 417-429.
17. Barrett, K. E. J. Dispersion Polymerization in Organic Media. New York: John Wiley & Sons, 1974, pp. 1-6.
18. Ugelstad, J.; Mork, P. C.; Kaggerug, K. H.; Ellingseng, T.; and Berge, A. Adv. Colloid Interface Sci. 13 (1980): 101.
19. Ober, C. K.; and Lok, K. P. Formation of large monodisperse copolymer particles by dispersion polymerization. Macromolecules. 20 (1987): 268-273.

20. Ochiai, M.; Masui, M.; Asanae, M.; Tokunaga, M.; and Iimura, T. Magnetic Toner Prepared by the Suspension Polymerization Method. J. Imaging Sci. and Techno. 38(5) (1994): 415-420.
21. Kamiyama, M.; Maeda, M.; Totsuka, H.; and Hamanaka, T. Properties of Polymerized Toners. J. Imaging Sci. and Techno. 39(5) (1995): 433-438.
22. Yanagida, N.; Takasaki, T.; and Hasegawa, J. Polymerized Toners: Its Feature and Future. Proceedings of The Pan-Pacific Imaging Conference/Japan Hardcopy'98. SEPJ(The Society of Electrophotography of Japan), (July 15-17,1998): 46-49.
23. Koyama, M.; Hayashi, K.; Kikuchi, T.; and Tsujita, K. Synthesis and Characteristics of Non-Spherical Toner by Polymerization Method. Recent Progress in Toner Technology. IS & T, George Marshall, 1997, pp. 369-372.
24. Fukuda, M.; Takezawa, S.; Watanuki, T.; and Sawatari, N. Toner with Gradated Resin Composition Made by Suspension Polymerization Technique. Recent Progress in Toner Technology. IS & T, George Marshall, 1997, pp 393-395.
25. Watanuki, T.; Nagahara, A.; Sasaki, S.; Yamaguchi, Y.; and Sawatari, N. Cleanerless Electrophotographic Process Using Magnetic Polymerized Toner. Recent Progress in Toner Technology. IS & T, George Marshall, 1997, pp 377-380.
26. Anderson, J. H. An Electronic Model of Triboelectrification of Two-component Electrophotographic Developers. J. Imaging Sci. and Techno. 33(6) (1992): 200-203.
27. Schein, L. B. Theory of Toner Charging. J. Imaging Sci. and Techno. 37(1) (1993): 1-4.

28. Akagi, H. The Effects of Toner Charge, Size and Surface Structure on Its Adhesion Forces. Color Hard Copy and Graphic Arts. 1670(1992): 138-145.
29. Ming-Chu, W.; Der-Ray, H.; and Ji-Bin, H. Tribo-charge and Particle Size Characteristics of Toners in a Laser Printer. Proceedings of SPIE. 1670 (1990): 146-152.
30. Sasaki, F.; and Isoda, T. Toner Flow Dynamic-Simulation of Change in Triboelectric Charge of Developer in Consideration of Toner Supply and Consumption. Proceedings of The Pan-Pacific Imaging Conference/Japan Hardcopy'98. SEPJ(The Society of Electrophotography of Japan), (July 15-17,1998): 23-26.
31. Anderson, J. H.; and Bugner, D. E. An Electronic Model of Triboelectrification of Polymers, II. Proceedings of The Fourth International Congress on Advances in Non-impact Printing Technologies (March 20-25, 1988): 79-88.
32. Lee, W. S.; Omodani, M.; and Takahashi, Y. Dependence of Triboelectric Charging Characteristics of Two-Component Developers on Charge Control Agent (CCA). Proceedings of The Pan-Pacific Imaging Conference/Japan Hardcopy'98. SEPJ(The Society of Electrophotography of Japan), (July 15-17,1998): 293-296.
33. Aoike, M.; Lee, W. S.; Omodani, M.; and Takahashi, Y. Carrier Characterization and Related Toner Charging Property in Two Component Developers. Proceedings of The Pan-Pacific Imaging Conference/Japan Hardcopy'98. SEPJ(The Society of Electrophotography of Japan), (July 15-17,1998): 297-300.

34. Netpradit, S.; Ando, Y.; Ikeda, T.; and Kiatkamjornwong, S. Effect of Developer Properties on Print Quality. J. Particulate Sci & Technol. 16(4) (1999): 311-327.
35. Poomtien, C.; Hoshino, Y.; and Kiatkamjornwong, S. Effect of Relation between Charge Control Agent Distribution on Toner and Charging Characteristics on Print Quality. J. Particulate Sci & Technol. 16(4) (1999):295-310.
36. Noshiro, T.; Takeuchi, M.; Asanae, M.; and Ochiai, M. Influence of Toner Shape on Its Tribocharging. Proceedings of The Pan-Pacific Imaging Conference/Japan Hardcopy'98. SEPJ(The Society of Electrophotography of Japan), (July 15-17,1998): 215-218.
37. Kutsuwada, N.; and Nakamura, Y. A Measurement of Electrophotographic Toner Charge. Proceedings of The Fourth International Congress on Advances in Non-impact Printing Technologies (March 20-25, 1988) : 89-101.
38. Baur, R.; and Macholdt, H. T. Charge Control Agents For Triboelectric (Friction) Charging. J. Electrostatics. 30 (1992): 213-222.
39. Kiatkamjornwong, S.; Noppakundilograt, S.; Baba, Y.; and Nishide, K. Evaluation of Toner Charge with Newly Developed Non-chromium Containing Charge Control Agent. ASEAN J. Sci. Tech. Development. 13(12) (1996): 19-36.
40. Tsunemi, K.; Shinjo, Y.; Saito, M.; and Hosoya, M. Influence of Charge Control Agent and Development Roller Surface on Toner Charging. J. Imaging Sci. and Techno. 40(5) (1996): 472-477.

41. Takahashi, Y.; and Lee, W. S. Analysis of Triboelectric Charging Characteristics of Two-Component Developers on Carrier Surface Properties. IS&T's NIP 12: International Conference on Digital Printing Technologies. (1996): 526-533.
42. Yamamura, T.; Hoshino, Y.; Poomtien, C.; and Kiatkamjornwong, S. Dependence of Toner Charging Characteristics on Amount of CCA Addition. IS&T's NIP 13: International Conference on Digital Printing Technologies. (1997): 187-190.
43. Barton, J.; and Capek, I. Radical Polymerization in Dispersion Systems. New York: Ellis Horwood, 1994, pp. 295
44. Kiatkamjornwong, S.; and Anantapiphat, A. Syntheses of super-fine mono-dispersed particles of poly(styrene-*co*-methyl methacrylate) by dispersion copolymerization. J. Sci. Soc. Thailand. 24(1998): 169-192.
45. Barton, J.; and Capek, I. Radical Polymerization in Dispersion Systems. New York: Ellis Horwood, 1994, pp. 293-294.
46. Winslow, F. H.; and Matreyek, W. Particle Size in Suspension Polymerization. Ind. Eng. Chem. 43(5) (1951): 1108-1112.
47. Barton, J.; and Capek, I. Radical Polymerization in Dispersion Systems. New York: Ellis Horwood, 1994, pp. 295.
48. Barton, J.; and Capek, I. Radical Polymerization in Dispersion Systems. New York: Ellis Horwood, 1994, pp. 291.
49. Barrett, K. E. J. Dispersion Polymerization in Organic Media. New York: John Wiley & Sons, 1974, pp. 143-151.

50. Ober, C. K.; and Hair, M. L. The effect of temperature and initiator levels on the dispersion polymerization of styrene. J. Polym. Sci. A. 25(1987): 1395-1407.
51. Brandrup, J.; and Immergut, E. H. Polymer Handbook. 2nd ed. New York: John Wiley & Sons, 1975, pp. III-144.
52. Apiwattananon, S. Synthesis and Characterization of Novel super-fine Particle-sized Polymers. Master's Thesis Chulalongkorn University, 1994.
53. Lok, K. P.; and Ober, C. K. Stable polymeric dispersion and methods for making. U.S. Pat 4,524,199. (Nov. 9, 1983).
54. Saenz, J. M.; and Ausa, J. M. Kinetics of dispersion copolymerization of styrene and butyl acrylate. Macromolecules. 31(1998): 5125-5222.
55. Tseng, C. M.; Lu, Y. Y.; El-Aasser, M. S.; and Vanderhoff, J. W. Uniform polymer particles by dispersion polymerization in alcohol. J. Polym. Sci. A. 24(1986): 2995-3007.
56. Apiwattananon, S. Synthesis and Characterization of Novel super-fine Particle-sized Polymers. Master's Thesis Chulalongkorn University, 1994.
57. Gruber, R. J.; and Julien, P. C. Dry Toner Technology in Handbook of Imaging Materials. New York, Marcel Dekker, 1991, pp. 170-176.
58. Brandrup, J.; and Immergut, E. H. Polyrner Handbook. 2nd ed. New York: John Wiley & Sons, 1975, pp. III-144.
59. Thomson, B.; Rudin, A.; Lajoie, G. Dispersion copolymerization of styrene and divinylbenzene. II. Effect of crosslinker on particle morphology. J. Appl. Polym. Sci. 59(1996): 2009-2028.

60. Uchiyama, M.; Nakamura, T.; and Yachi, S. Toner for developing electrostatic image. U.S. Pat 5,795,694. (Aug. 18, 1998).
61. Vidal, A.; Riess, G.; and Donnet, J. B. Process for grafting polymers on carbon black through free radical mechanism. U.S. Pat. 4,014,844. (Mar. 29, 1977).
62. Odian, G. Principles of Polymerization. 3rd ed. New York: John Wiley & Sons, 1991, pp. 262-266.
63. Tsunemi, K.; Shinjo, Y.; Saito, M.; and Hosoya, M. Influence of Charge Control Agent and Development Roller Surface on Toner Charging. J. Imaging Sci. and Techno. 40(5) (1996): 472-477.
64. Kiatkamjornwong, S.; Noppakundilograt, S.; Baba, Y.; and Nishide, K. Evaluation of Toner Charge with Newly Developed Non-chromium Containing Charge Control Agent. ASEAN J. Sci. Tech. Development. 13(12) (1996): 19-36.
65. Birkett, K. L.; and Gregory, P. Dyes Pigments. (7)(1986): 341.
66. Birkett, K. L.; and Gregory, P. Dyes Pigments. (7)(1986): 341.
67. Anderson, J. H. Effects of Carbon Black on Toner Tribocharging in Two-Component Electrophotographic Developers. IS&T's NIP 15: International Conference on Digital Printing Technologies. (1999): 544-547.

APPENDIX

APPENDIX

DIFFERENTIAL SCANNING CALORIMETER

Differential scanning calorimeter was used to determine the glass transition temperature of polymers by looking for the change in heat capacity. For random copolymers, the glass transition temperature vary monotonically with the composition between those of the homopolymers. The DSC thermograms of the copolymer prepared with different monomer composition and carbon black feed level were shown in Figure A-1 to A-6, respectively.




Figure A-1 DSC thermogram of the copolymer prepared with St/nBA (90/10) mol%




Figure A-2 DSC thermogram of the copolymer prepared with St/nBA (85/15) mol%

15

Perkin-Elmer Thermal Analysis

14




Figure A-3 DSC thermogram of the copolymer prepared with St/nBA (80/20) mol%




Figure A-4 DSC thermogram of the copolymer prepared with St/nBA (80/20) mol% in the presence of carbon black feed level 1 wt%

15 -

Perkin-Elmer Thermal Analysis

14 -

12 -

10 -

Heat Flow Endo Up (mW)

Delta Cp = 0.211 J/g**C
Half Cp Extrapolated = 69.399 °C

8 -

6 -

4 -

2 -

0 -

0 20 40 60 80 100 120 140 150

Temperature (°C)

Figure A-5 DSC thermogram of the copolymer prepared with St/nBA (80/20) mol% in the presence of carbon black feed level 3 wt%

15 ..

Parkin-Elmer Thermal Analysis

14 ..

12 ..

10 ..




Figure A-6 DSC thermogram of the copolymer prepared with St/nBA (80/20) mol% in the presence of carbon black feed level 5 wt%



VITA

Mr. Pisnu Pomsanam was born on November 19, 1975, in Phuket, Thailand. He received his B.Sc. in Industrial Chemistry from Department of Chemistry, Faculty of Science, King Mongkut's Institute of Technology Ladkrabang in 1996. He began his master degree study in Imaging Technology, Department of photographic Science and Printing Technology, Faculty of Science, Chulalongkorn University in 2000.