

**MIXED MATRIX MEMBRANES FOR CO₂/CH₄ SEPARATION:
EFFECTS OF VARIOUS ZEOLITES INCORPORATED INTO CELLULOSE
ACETATE**



Pipat Singha-in

A Thesis Submitted in Partial Fulfilment of the Requirements
for the Degree of Master of Science
The Petroleum and Petrochemical College, Chulalongkorn University
in Academic Partnership with
The University of Michigan, The University of Oklahoma,
Case Western Reserve University and Institut Français du Pétrole

2008

511999

Thesis Title: Mixed Matrix Membranes for CO₂/CH₄ Separation:
Effects of Various Zeolites Incorporated into Cellulose
Acetate.
By: Pipat Singha-in
Program: Petrochemical Technology
Thesis Advisors: Assoc.Prof. Thirasak Rirksomboon
Dr. Santi Kulprathipanja

Accepted by the Petroleum and Petrochemical College, Chulalongkorn University, in partial fulfilment of the requirements for the Degree of Master of Science.

..... *Nantaya Yanumet* College Director
(Assoc. Prof. Nantaya Yanumet)

Thesis Committee:

..... *Thirasak Rirksomboon*
(Assoc.Prof. Thirasak Rirksomboon)

..... *Santi Kulprathipanja*
(Dr. Santi Kulprathipanja)

..... *Pramoch Rangsunvigit*
(Assoc.Prof. Pramoch Rangsunvigit)

..... *Khantong Soontarapa*
(Assoc.Prof. Khantong Soontarapa)

..... *Vissanu Meeyoo*
(Assoc.Prof. Vissanu Meeyoo)

บทคัดย่อ

พิพัฒน์ สิงห์อินทร์ : การศึกษาเยื่อเลือกผ่านเนื้อผสมสำหรับการแยกก๊าซคาร์บอนไดออกไซด์/ก๊าซมีเทน: ผลของซีโอไลต์ชนิดต่างๆในที่ผสมลงในเซลลูโลสอะซิเตต (Mixed Matrix Membranes for CO₂/CH₄ separation: Effects of Various Zeolite Incorporated into Cellulose Acetate) อ. ที่ปรึกษา : รศ. ดร. ชिरศักดิ์ ฤกษ์สมบูรณ์ และ ดร. สันติ กุลประทีปปัญญา 80 หน้า

เยื่อเลือกผ่านเนื้อผสมคือเยื่อเลือกผ่านที่สังเคราะห์ขึ้นจากการนำตัวกรองระดับโมเลกุลมากระจายตัวในเมทริกซ์ของโพลีเมอร์ เยื่อเลือกผ่านเนื้อผสมเหมาะสำหรับการแยกก๊าซเพราะมีศักยภาพในการแยกก๊าซที่สูงและยังมีต้นทุนต่ำ เยื่อเลือกผ่านเนื้อผสมได้นำข้อดีของวัสดุโพลีเมอร์และวัสดุตัวกรองระดับโมเลกุลเข้าไว้ด้วยกัน กล่าวคือเยื่อเลือกผ่านเนื้อผสมได้รวมคุณสมบัติการขึ้นรูปได้ง่ายของวัสดุโพลีเมอร์และคุณสมบัติการแยกก๊าซที่ดีของวัสดุตัวกรองระดับโมเลกุลเอาไว้ในวัสดุชนิดเดียว เยื่อเลือกผ่านเนื้อผสมได้ถูกเตรียมขึ้นในการทดลองนี้โดยการนำซีโอไลต์โซเดียมเอ็กซ์, โซเดียมวาย, ซิลิกาไลท์, โซเดียมเอ, ซิลเวอร์เอ, แคลเซียมเอ, โมเดไนต์, และบีตา ผสมกับกับโพลีเมอร์เซลลูโลสอะซิเตต แล้วจึงนำสารละลายผสมที่ได้ไปขึ้นรูป สัมประสิทธิ์ค่าให้ซึมผ่านได้ของก๊าซคาร์บอนไดออกไซด์ และก๊าซมีเทน วัดโดยวิธีการวัดโดยใช้ก๊าซเดี่ยว จากผลการทดลองพบว่า สำหรับซีโอไลต์ ซิลเวอร์เอ, โซเดียมเอ, แคลเซียมเอ, และโมเดไนต์ สัมประสิทธิ์ค่าให้ซึมผ่านได้ของก๊าซและสมรรถนะการเลือกของ CH₄/CO₂ ลดลงเมื่อเพิ่มปริมาณบรรจุของซีโอไลต์ ขณะที่ซีโอไลต์ชนิดอื่นจะพบปรากฏการณ์ที่ตรงข้ามกัน อย่างไรก็ตาม สมรรถนะการเลือกของ CO₂/CH₄ ของเยื่อเลือกผ่านเนื้อผสมที่สังเคราะห์ขึ้นจากซีโอไลต์โซเดียมเอ็กซ์และโพลีเมอร์เซลลูโลสอะซิเตต มีค่าเพิ่มขึ้นเนื่องมาจากก๊าซคาร์บอนไดออกไซด์มีความจุของการดูดซับที่สูง เมื่อเปรียบเทียบสมรรถนะการเลือกของ CO₂/CH₄ ของเยื่อเลือกผ่านเนื้อผสมโซเดียมเอ-เซลลูโลสอะซิเตตกับแคลเซียมเอ-เซลลูโลสอะซิเตต ผลการทดลองช่วยยืนยันว่าการปิดกั้นรูบางส่วนของซีโอไลต์โดยสายโซ่ของโพลีเมอร์และการแข็งเกร็งของสายโซ่ของโพลีเมอร์มีบทบาทสำคัญต่อประสิทธิภาพของการแยกก๊าซของเยื่อเลือกผ่านเนื้อผสม

ABSTRACT

4971012063: Petrochemical Technology Program

Pipat Singha-in: Mixed Matrix Membranes for CO₂/CH₄ Separation: Effects of Various Zeolites Incorporated into Cellulose Acetate

Thesis Advisors: Assoc. Prof. Thirasak Rirksomboon and Dr. Santi Kulprathipanja, 80 pp.

Keywords: Mixed matrix membrane, zeolite, Partial pore blockage, CO₂/CH₄ separation

Mixed matrix membranes (MMMs) comprised of molecular sieves in a polymer matrix have the potential to provide economical as well as high-performance gas separation. They combine the advantages of both materials: the processability of polymers and the superior gas transport properties of molecular sieves. MMMs have been successfully fabricated in this study by individually incorporating NaX, NaY, Silicalite, NaA, AgA, CaA, and Beta zeolites into cellulose acetate (CA) polymers following the solution-casting method. CO₂ and CH₄ permeances were determined using single gas measurements. The results showed that the gas permeance and CH₄/CO₂ selectivity were decreased as zeolite loading was increased for the MMMs incorporated with AgA, NaA, and CaA, while such phenomena were insignificantly observed for the other types of zeolite used. However, the enhancement of CO₂/CH₄ selectivity for NaX-CA MMMs was attributed to the high CO₂ sorption capacity of NaX. In comparison of CO₂/CH₄ separation performance of NaA-CA and CaA-CA MMMs, it can confirm that the partial pore blockage of zeolites by the polymer chains and polymer chain rigidification play significant roles in the gas separation performance of MMMs.

ACKNOWLEDGEMENTS

The author is grateful for the scholarship and funding of the thesis work provided by the Petroleum and Petrochemical College; and the National Center of Excellence for Petroleum, Petrochemicals, and Advance Materials, Thailand.

I would like to thank Dr. Santi Kulprathipanja for his keenness, support, and commitment towards my development as a researcher. He puts a great amount of effort in providing opportunities for students to visit UOP Company. Even his timetable is usually booked with activities; he always finds time for me to discuss ideas, troubleshoot problems, and to evaluate my results and presentations. I have better understanding the value of “telling a story” when presenting research results, due to his suggestion.

I also appreciate Assoc.Prof. Thirasak Rirksomboon, my Thai advisor for his advice, attention and support throughout this work. His attention to detail and coherent approach towards problem solving has a significant impact on my work.

I would like to thank my friends, staffs, and faculty members at The Petroleum and Petrochemical College for their kindness and help. Finally, I would like to thank my family for their understanding, encouragement, and support throughout my life.

TABLE OF CONTENTS

	PAGE
Title Page	i
Abstract (in English)	iii
Abstract (in Thai)	iv
Acknowledgements	v
Table of Contents	vi
List of Tables	viii
List of Figures	ix
CHAPTER	
I INTRODUCTION	1
II THEORETICAL BACKGROUND AND LITERATURE REVIEW	3
2.1 Theoretical Background	3
2.1.1 Theory of Gas Transport in Membranes	3
2.1.2 Effect of carbon dioxide on polymer Plasticization	6
2.1.3 Plasticization in asymmetric membranes	7
2.1.4 Permeation model of MMMs	9
2.2 Literature review	17
2.2.1 Polymeric Membranes	17
2.2.2 Mixed Matrix Membranes	21
III EXPERIMENTAL	27
3.1 Materials	27
3.2 Methodology	27
3.2.1 Preparation of Mixed Matrix Membrane	27
3.2.2 Gas Permeability Measurements	28

CHAPTER	PAGE
IV RESULTS AND DISCUSSION	30
4.1 Zeolite properties	30
4.2 CO ₂ and CO ₂ /CH ₄ separation performances of pure CA membranes	30
4.3 Effect of Si/Al ratio on CO ₂ /CH ₄ separation performances	31
4.4 Effect of cation ratio on CO ₂ /CH ₄ separation performances	35
4.5 Effect of pore size on CO ₂ /CH ₄ separation performances	37
4.6 Mordenite-CA MMMs	40
4.7 Modified Maxwell model	42
V CONCLUSIONS AND RECOMMENDATIONS	46
5.1 Conclusions	46
5.2 Recommendations	46
REFERENCES	47
APPENDICES	56
Appendix A Calculation of Gas Permeation Rate	56
Appendix B Experimental Data	57
Appendix C The modified Maxwell model	78
CURRICULUM VITAE	80

LIST OF TABLES

TABLE		PAGE
2.1	Summary of existing permeation model	16
3.1	Selected physical properties of zeolites used in this work	27

LIST OF FIGURES

FIGURE		PAGE
2.1	Solution-diffusion mechanism	3
2.2	Asymmetric membrane	4
2.3	Representation of the possible shapes of the permeability of several glassy polymers to CO ₂	6
2.4	Hypothetical explanation of CO ₂ conditioning effects on dense skin morphology of symmetric hollow fiber membrane	8
3.1	Schematic of the experimental setup for measuring gas permeability	29
3.2	Schematic of the membrane testing unit	29
4.1	Effects of NaY and NaX loadings on CO ₂ permeance at 50 and 100 psi feed	31
4.2	Effects of NaY and NaX loadings on CO ₂ /CH ₄ selectivity at 50 and 100 psi feed	33
4.3	Effects of silicalite and beta loadings on CO ₂ permeance at 50 and 100 psi feed	34
4.4	Effects of silicalite and beta loadings on CO ₂ /CH ₄ selectivity at 50 and 100 psi feed	35
4.5	Effects of NaA and AgA loadings on CO ₂ permeance at 50 and 100 psi feed	36
4.6	Effects of NaA and AgA loadings on CO ₂ /CH ₄ selectivity at 50 and 100 psi feed	37
4.7	Effects of NaA and CaA loadings on CO ₂ permeance at 50 and 100 psi feed	39
4.8	Effects of NaA and CaA loadings on CO ₂ /CH ₄ selectivity at 50 and 100 psi feed	39
4.9	Effect of mordenite loading on CO ₂ permeances at 50 and 100 psi feed	40

FIGURE		PAGE
4.10	Effect of mordenite loading on CO ₂ /CH ₄ selectivity at 50 and 100 psi feed feed	41
4.11	Schematic diagram of new modified Maxwell model	42
4.12	Comparison of O ₂ permeances of NaA-CA MMMs between experimental data and predictions from the new modified Maxwell model	44
4.13	Comparison of N ₂ permeances of NaA-CA MMMs between experimental data and predictions from the new modified Maxwell model	44
4.14	Comparison of O ₂ /N ₂ selectivity of NaA-CA MMMs between experimental data and predictions from the new modified Maxwell model	45