

**SEPARATION OF C₈ AROMATICS AND PARAFFINS USING A ZEOLITE
MIXED MATRIX MEMBRANE PERVAPORATOR**

Mr. Panuwat Wareewanit

A Thesis Submitted in Partial Fulfilment of the Requirements
for the Degree of Master of Science
The Petroleum and Petrochemical College, Chulalongkorn University
in Academic Partnership with
Case Western Reserve University, The University of Michigan,
The University of Oklahoma, and Institut Français du Pétrole
2004
ISBN 974-9651-32-4

I 21616413

Thesis Title: Separation of C₈ Aromatics and Paraffins Using a Zeolite Mixed Matrix Membrane Pervaporator
By: Mr. Panuwat Wareewanit
Program: Petrochemical Technology
Thesis Advisors: Asst. Prof. Pramoch Rangsunvigit
Assoc. Prof. Thirasak Rirksomboon
Dr. Santi Kulprathipanja

Accepted by the Petroleum and Petrochemical College, Chulalongkorn University, in partial fulfilment of the requirements for the Degree of Master of Science.

K. Bunyakiat.
..... College Director
(Assoc. Prof. Kunchana Bunyakiat)

Thesis Committee:

Pramoch R.
.....
(Asst. Prof. Pramoch Rangsunvigit)

Thirasak R.
.....
(Assoc. Prof. Thirasak Rirksomboon)

Santi K.
.....
(Dr. Santi Kulprathipanja)

Sumaeth C.
.....
(Assoc. Prof. Sumaeth Chavadej)

Apanee L.
.....
(Dr. Apanee Luengnaruemitchai)

ABSTRACT

4571011063: PETROCHEMICAL TECHNOLOGY PROGRAM

Panuwat Wareewanit: Separation of C₈ Aromatics and Paraffins Using a Zeolite Mixed Matrix Membrane Pervaporator

Thesis Advisors: Asst. Prof. Pramoch Rangsunvigit, Assoc. Prof. Thirasak Rirksomboon, and Dr. Santi Kulprathipanja, 35 pp. ISBN 974-9651-32-4

Keywords: C₈ Aromatics/ Paraffins/ Mixed matrix membrane/ Silicalite-1/ Polyimide/ Pervaporator

Membrane based separation processes have been recognized as an alternative for conventional separation processes. In this work, a polyimide membrane and polyimide-based mixed matrix membranes (MMM's) were prepared by solution casting and solvent evaporation methods. The membranes were used for separation of C₈ aromatics and paraffin mixtures by pervaporation. Three MMM's including polyimide and different loadings of silicalite (10, 20 and 30 wt%) in the polymer were used. The results showed that the permeabilities of *p*-xylene and *o*-xylene increased with the silicalite loading. In contrast, the permeability of n-heptane showed the opposite trend. The *p*-/*o*-xylene selectivity for the polyimide membrane, 10, 20, and 30 wt% silicalite/polyimide MMM's were 1.042, 1.032, 1.288, and 1.858, respectively. High C₈ aromatics and paraffins selectivities were obtained with the silicalite/polyimide MMM's. The results indicated that the polyimide membranes and silicalite/polyimide MMM's enhanced the C₈ aromatics and paraffins separation.

บทคัดย่อ

ภานุวัฒน์ วารินนิช: การแยกสารประกอบอะโรมาติกส์ที่มีคาร์บอนแปดอะตอมและพาราฟินส์โดยใช้เครื่องแยกไอแบบใช้เยื่อเลือกผ่านเนื้อผสม (Separation of C₈ Aromatics and Paraffins Using a Zeolite Mixed Matrix Membrane Pervaporator) อ.ที่ปรึกษา: ผศ. ดร. ปราโมช รังสรรค์วิจิตร รศ. ดร. ชีระศักดิ์ ฤกษ์สมบูรณ์ และ ดร. สันติ กุลประทีปปัญญา 35 หน้า ISBN 974-9651-32-4

กระบวนการแยกโดยใช้เยื่อเลือกผ่านเป็นอีกทางเลือกหนึ่งที่สามารถใช้แทนกระบวนการแยกที่ใช้อยู่ในการศึกษานี้ได้เตรียมเยื่อเลือกผ่านพอลิอิมิดและเยื่อเลือกผ่านพอลิอิมิดแบบเนื้อผสมโดยใช้การขึ้นรูปเป็นแผ่นบางแล้วระเหยตัวทำละลายออก แผ่นเยื่อเลือกผ่านที่เตรียมได้ถูกใช้ในกระบวนการแยกสารผสมระหว่างสารประกอบอะโรมาติกส์ที่มีคาร์บอนแปดอะตอมและพาราฟินส์โดยใช้เครื่องแยกไอ เยื่อเลือกผ่านเนื้อผสม 3 ชนิดที่เตรียมขึ้นประกอบด้วยเยื่อเลือกผ่านผสมระหว่างพอลิอิมิดและซิลิกาไลต์ ซึ่งเยื่อเลือกผ่านเนื้อผสมแต่ละชนิดมีปริมาณซิลิกาไลต์ที่เติมลงไปต่างกันดังนี้ 10 20 และ 30 เปอร์เซ็นต์โดยน้ำหนัก จากผลการทดลองพบว่าความสามารถในการผ่านเข้าไปในเยื่อเลือกผ่านเนื้อผสมของพาราไซลีนและออโรไซลีนเพิ่มขึ้นตามปริมาณของซิลิกาไลต์ที่เติมลงไป ในทางตรงกันข้ามความสามารถในการผ่านเข้าไปในเยื่อเลือกผ่านแบบผสมของนอร์มอลเฮปเทน (พาราฟินส์) ลดลงเมื่อเพิ่มปริมาณซิลิกาไลต์ที่เติมลงไป ค่าสัมประสิทธิ์การแยกระหว่างพาราไซลีนและออโรไซลีนในเยื่อเลือกผ่านพอลิอิมิดและเยื่อเลือกผ่านเนื้อผสมที่มีปริมาณซิลิกาไลต์คิดเป็น 10 20 และ 30 เปอร์เซ็นต์โดยน้ำหนักเป็นดังนี้ 1.042 1.032 1.288 และ 1.858 ตามลำดับ ในการศึกษาครั้งนี้ยังพบอีกว่าเยื่อเลือกผ่านเนื้อผสมซิลิกาไลต์ให้ผลดีมากในการแยกสารประกอบอะโรมาติกส์ที่มีคาร์บอนแปดอะตอมออกจากพาราฟินส์ จากผลการทดลองแสดงให้เห็นว่า เยื่อเลือกผ่านพอลิอิมิดและเยื่อเลือกผ่านเนื้อผสมซิลิกาไลต์เพิ่มความสามารถในการแยกสารดังกล่าว

ACKNOWLEDGEMENTS

This research work has been invaluable and rememberable experience. This work cannot be successful without the help of the following individuals and organization.

First of all, I would like to thank and express the deepest feeling of obligation to Dr. Santi Kulprathipanja, my US advisor, for his precious advice, comments and strong encouragement throughout this work. I would also like to thank Mrs. Apinya Kulprathipanja, Dr. Santi's wife, for her kindness.

I would like to thank Asst. Prof. Pramoch Rangsunvigit and Assoc. Prof. Thirasak Rirksomboon, my Thai advisors, for their guidance, reliable suggestions and making this thesis interesting.

I would also like to special thank to UOP LLC for providing budget and all facilities. Moreover, I would like to forward my appreciation to all UOP staff for their help, suggestions and making me happy during 3 months.

This thesis work is partially funded by Postgraduate Education and Research Programs in Petroleum and Petrochemical Technology (PTT Consortium).

Specially, I would like to thank General Electric International Operations Company Inc. for kindly providing polyimide (Ultem 1000) resin.

Finally, I would like to take this opportunity to thank PPC staff, my friends and my family for their help, cheerfulness and encouragement.

TABLE OF CONTENTS

| | PAGE |
|---|-------------|
| Title Page | i |
| Abstract (in English) | iii |
| Abstract (in Thai) | iv |
| Acknowledgements | v |
| Table of Contents | vi |
| List of Tables | viii |
| List of Figures | ix |
| | |
| CHAPTER | |
| I | |
| INTRODUCTION | 1 |
| | |
| II | |
| BACKGROUND AND LITERATURE SURVEY | 3 |
| 2.1 Background | 3 |
| 2.1.1 Pervaporator | 3 |
| 2.1.2 Selectivity | 4 |
| 2.1.3 Zeolites | 5 |
| 2.1.4 Zeolite Selection | 6 |
| 2.1.5 Polymer Selection | 7 |
| 2.2 Literature Review | 7 |
| | |
| III | |
| EXPERIMENTAL | 11 |
| 3.1 Materials | 11 |
| 3.1.1 Chemicals | 11 |
| 3.1.2 Other Materials | 11 |
| 3.2 Experiments | 11 |
| 3.2.1 Mixed Matrix Membrane Preparation | 11 |
| 3.2.2 Pervaporation Testing | 12 |
| 3.2.3 Single Component Adsorption Experiments | 13 |

| CHAPTER | | PAGE |
|----------------|--|-------------|
| IV | RESULTS AND DISCUSSION | 16 |
| | 4.1 Properties of Silicalite-1 | 16 |
| | 4.2 Morphological Change of MMM's | 16 |
| | 4.3 Pervaporation | 17 |
| | 4.4 Single Component Adsorption | 21 |
| V | CONCLUSIONS AND RECOMMENDATIONS | 23 |
| | REFERENCES | 24 |
| | APPENDICES | 27 |
| | Appendix A Calculation | 27 |
| | Appendix B Membrane pervaporation results | 28 |
| | CURRICULUM VITAE | 35 |

LIST OF TABLES

| TABLE | | PAGE |
|--------------|---|-------------|
| 3.1 | Chemicals used in the experiments | 11 |
| 3.2 | Sample preparation for <i>p</i> -xylene solution | 14 |
| 3.3 | Sample preparation for <i>o</i> -xylene solution | 14 |
| 3.4 | Sample preparation for n-hexane solution | 15 |
| 4.1 | Selectivity of polyimide and polyimide-based MMM's | 19 |
| 4.2 | Adsorption capacities of n-hexane, <i>p</i> -xylene and <i>o</i> -xylene on silicalite-1 | 22 |

LIST OF FIGURES

| FIGURE | | PAGE |
|---------------|--|-------------|
| 2.1 | A schematic of pervaporation process | 4 |
| 2.2 | Secondary building units and commonly occurring polyhedral units in zeolite framework structures | 6 |
| 3.1 | Schematics of pervaporation process | 13 |
| 4.1 | SEM images showing cross-sectional morphologies of MMM's | 17 |
| 4.2 | Permeability of each component through polyimide and polyimide-based MMM's | 20 |
| 4.3 | Selectivity for <i>p</i> -/ <i>o</i> -xylene of polyimide and polyimide-based MMM's | 21 |
| 4.4 | Selectivity for C ₈ aromatics/paraffins of polyimide and polyimide-based MMM's | 21 |