

การสังเคราะห์โซเดียมคาร์บอกซีเมทิลเซลลูโลส

นางสาว รานี ทาญพล



004260

วิทยานิพนธ์นี้เป็นส่วนหนึ่งของการศึกษาตามหลักสูตรปริญญาวิทยาศาสตรมหาบัณฑิต  
แผนกวิชาเคมี  
บัณฑิตวิทยาลัย จุฬาลงกรณ์มหาวิทยาลัย  
พ.ศ. 2519

**SYNTHESIS OF SODIUM CARBOXYMETHYLCELLULOSE (Na-CMC)**

**Miss Rance Hanpol**

**A Thesis Submitted in Partial Fulfillment of the Requirement**

**for the Degree of Master of Science**

**Department of Chemistry**

**Graduate School**

**Chulalongkorn University**

**1976**

Accepted by the Graduate School, Chulalongkorn  
University in Partial Fulfillment of the Requirements for the  
Degree of Master of Science.

*Yisid Prochnatromol.*  
.....

Dean of the Graduate School

Thesis Committee

*Salag D. Labanandana.*  
.....Chairman

*D. Shienthan.*  
.....

*M. Amorasit*  
.....

Thesis Supervisor Dr. Anamai Singhabhandhu

หัวข้อวิทยานิพนธ์	การสังเคราะห์โซเดียมคาร์บอกซีเมทิลเซลลูโลส
ชื่อ	นางสาวรานี หาญพล
แผนกวิชา	เคมี
ปีการศึกษา	2518

### บทคัดย่อ

การสกัดเซลลูโลสจากใยเมล็ดฝ้ายเพื่อใช้เป็นวัตถุดิบในการเตรียมโซเดียมคาร์บอกซีเมทิลเซลลูโลสที่มีสีกรของการแทนที่สูง สามารถทำได้โดยอาศัยกรรมวิธีขั้นตอน และเทคนิคต่าง ๆ ที่ใช้ในการบดขยี้ ตม และฟอกจาง การบดขยี้ด้วยเครื่องบดที่ใช้ในห้องปฏิบัติการและการล้างแยกสามารถทำให้ใยฝ้ายหลุดออกจากเมล็ดฝ้ายได้ เมื่อต้มใยฝ้ายที่แยกออกมาด้วยสารละลายค่างที่มีความเข้มข้นต่าง ๆ กัน คือ 1, 3, 5, 8 และ 10 เปอร์เซ็นต์ ภายใต้ความดัน 10 และ 20 ปอนด์ต่อตารางนิ้ว ในเวลา 2 และ 3 ชั่วโมง และโดยการฟอกจางโดยใช้สารละลายที่มีสารฟอกสีประมาณ 0.1 เปอร์เซ็นต์เป็นเวลาครึ่งชั่วโมง ปรากฏว่าปริมาณของแอลฟาเซลลูโลสที่เตรียมได้ขึ้นอยู่กับความเข้มข้นของสารละลายค่าง ความดัน เวลาที่ใช้ในการต้มใยฝ้าย และเทคนิคของการฟอกจาง จากการศึกษาค้นคว้าพบว่า สภาวะที่เหมาะสมในการสกัดเซลลูโลสจากใยเมล็ดฝ้าย คือ การต้มใยฝ้ายด้วยสารละลายค่าง 10 เปอร์เซ็นต์ ภายใต้ความดัน 10 ปอนด์ต่อตารางนิ้ว เป็นเวลา 2 ชั่วโมง แล้วฟอกจางด้วยสารละลายที่มีสารฟอกสีประมาณ 0.1 เปอร์เซ็นต์ เป็นเวลาครึ่งชั่วโมง เซลลูโลสที่เตรียมได้โดยวิธีนี้จะมีปริมาณแอลฟาเซลลูโลสประมาณ 60.99 เปอร์เซ็นต์

สำหรับวิธีการเตรียมโซเดียมคาร์บอกซีเมทิลเซลลูโลสสามารถทำได้โดยใช้  
 เซลลูโลสที่เตรียมได้เป็นวัตถุดิบและใช้ปฏิกิริยาอีเธอร์ฟิเคชัน จากเซลลูโลสที่เตรียม  
 ได้ด้วยกรรมวิธีดังกล่าวข้างต้นจะต้องเตรียมอัลคาไลน์เซลลูโลสซึ่งเชื่อว่าเป็นตัวกลาง  
 ที่จะช่วยทำให้เกิดอีเธอร์ฟิเคชันของเซลลูโลสก่อนในรีแอคชันมีเดียมที่มีส่วนผสมในอัตรา  
 ส่วนต่าง ๆ กันของเบนซีนกับเอทิลแอลกอฮอล์และเมทิลเอทิลคีโตนกับเอทิลแอลกอฮอล์  
 อัลคาไลน์เซลลูโลสจะทำปฏิกิริยาเคมีกับโซเดียมคลอโรอาซิเตทที่เตรียมได้ใหม่ ๆ ทำให้  
 เกิดปฏิกิริยาอีเธอร์ฟิเคชันขึ้น ผลที่เกิดขึ้นหลังจากปฏิกิริยาอีเธอร์ฟิเคชันก็คือ โซเดียม  
 คาร์บอกซีเมทิลเซลลูโลส โดยอาศัยเทคนิคที่เรียกว่า มัลติสเทปออฟอีเธอร์ฟิเคชัน  
 หรือ การทำปฏิกิริยาอีเธอร์ฟิเคชันซ้ำกันหลาย ๆ ครั้ง จะได้โซเดียมคาร์บอกซีเมทิล  
 เซลลูโลสซึ่งมีค่าของการแทนที่สูง จากผลการทดลองปรากฏว่าหลังจากทำปฏิกิริยา  
 อีเธอร์ฟิเคชันซ้ำกัน 5 ครั้ง แต่ละครั้งใช้เวลา 5 วัน ที่  $26 \pm 2^{\circ}\text{C}$  สามารถ  
 เตรียมโซเดียมคาร์บอกซีเมทิลเซลลูโลสที่มีค่าของการแทนที่เท่ากับ  $2.767 \pm 0.031$   
 โดยใช้รีแอคชันมีเดียมที่มีส่วนผสมของเมทิลเอทิลคีโตน 80 ส่วน กับเอทิลแอลกอฮอล์  
 20 ส่วน

Thesis Title        Synthesis of Sodium Carboxymethylcellulose  
                        (Na-CMC)  
Name                 Miss Rance Hanpol  
Department          Chemistry  
Academic Year       1975

## ABSTRACT

Suitable purified cellulose for using as source of cellulose in the preparation of sodium carboxymethylcellulose (Na-CMC) with degree of substitution (D.S.) higher than one of commercial grade (D.S.=0.4-1.4) can be obtained from waste derived from local cotton seed oil manufacture. Treatment techniques including in cotton fuzz separation, digestion and bleaching were studied and performed under various treatment conditions.

It was found that cotton fuzz can be easily obtained by common laboratory-mill and manual screen, and then, digested and bleached. Various conditions used for digestion and bleaching were conducted in accordance with

Sodium hydroxide concentration (%)	1, 3, 5, 8, 10
Pressure (lbs/in <sup>2</sup> )	10, 20
Time (hours)	2, 3
Bleaching agent concentration (%)	0.1
Bleaching time (hour)	0.5

It was also found that alkaline concentration, pressure, time for digestion and bleaching enhanced some effects especially on the yield of  $\alpha$ -cellulose containing in purified cellulose obtained.

Under suitable treatment conditions (Digestion the cotton fuzz with 10% sodium hydroxide under 10 lbs/in<sup>2</sup> pressure for 2 hours and then bleached with about 0.1% bleaching agent for 0.5 hour), most suitable purified cellulose for using as source of cellulose for Na-CMC preparation contains 60.99% of  $\alpha$ -cellulose.

Na-CMC can thus be prepared by using the purified cellulose mentioned above as starting material and by etherification reaction. Starting from purified cellulose, alkali cellulose, an intermediate for etherifying of cellulose, was prepared by alkali treatment in various mixing ratio of organic reaction medium (benzene-ethyl alcohol and methyl ethyl ketone-ethyl alcohol). The alkali cellulose was then etherified by immediately prepared sodium chloroacetate. In addition with techniques of multistep of etherification, Na-CMC with high D.S. was obtained. As a result, Na-CMC with D.S.  $2.767 \pm 0.031$  can be prepared by 5 steps (5 days for each step) and etherification at  $26 \pm 2^\circ\text{C}$  and by using 80:20 mixing ratio of methyl ethyl ketone-ethyl alcohol as reaction medium.

## ACKNOWLEDGEMENTS

The writer wishes to express her gratitude to Dr. Anamai Singhabhandhu for her guidance and assistance during the course of this work. Thank is also extended to Assistant Professor Mr. Maen Amorasit who serve as the writer's thesis committee and to Dr. Praprit Nagara (Director-General) and Dr. Chareon Vashararangsi (Director of Division of Physics and Engineering) in Department of Science, Ministry of Industry for their kind cooperation in order to use some scientific instruments needed for partial conducting the experiment. Appreciation is extended to Graduate School of Chulalongkorn University, Kasetsart University and National Research Council on granting the writer the scholarship in order to support the expense of this work.



## CONTENTS

	PAGE
Abstract (Thai) . . . . .	iv
Abstract (English) . . . . .	vi
List of Tables . . . . .	xi
List of Figures . . . . .	xii

## CHAPTER

1. INTRODUCTION . . . . .	1
2. BACKGROUND . . . . .	4
2.1 Purification of Cellulose . . . . .	4
2.2 Quantitative Analysis of $\alpha$ -cellulose . . . . .	7
2.3 Preparation of Sodium Carboxymethyl- cellulose (Na-CMC) . . . . .	12
2.3.1 Etherification reaction of cellulose . . . . .	12
2.3.2 Determination of degree of substitution of sodium carboxymethylcellulose . . . . .	16
a. Determination of moisture content . . . . .	18
b. Determination of degree of substitution . . . . .	18



	PAGE
3. EXPERIMENTS . . . . .	20
3.1 Purification of Cellulose . . . . .	20
3.2 Preparation of Sodium Carboxymethyl- cellulose . . . . .	21
3.3 Determination of Degree of Substitution of Sodium Carboxymethylcellulose . . .	24
4. RESULTS AND DISCUSSION . . . . .	26
5. CONCLUDING REMARKS . . . . .	50
REFERENCES . . . . .	54
VITA . . . . .	56

## LIST OF TABLES

TABLES	PAGE
1. Percentage of $\alpha$ -cellulose obtained from various batches of treated pulp . . . . .	22
2. A list of four highest percentages of $\alpha$ -cellulose in bleached samples of purified cellulose derived from various purifying conditions . . . . .	36
3. A list of degrees of substitution of sodium carboxymethylcellulose obtained from the first etherification step using various ratio of mixed reaction media . . . . .	38
4. A list of degrees of substitution of sodium carboxymethylcellulose obtained by multistep of etherification of purified cellulose derived from 10% NaOH, digestion at 10 lbs/in <sup>2</sup> pressure for 2 hours . . . . .	42
5. A list of degrees of substitution of sodium carboxymethylcellulose obtained after 5 days for each etherification step with 80:20 ME-EtOH as reaction medium . . . . .	47

## LIST OF FIGURES

FIGURE	PAGE
1. Graphical representation of alkali concentration vs. percentage of $\alpha$ -cellulose contained in both bleached and unbleached samples of purified cellulose (digestion for 2 hrs. with 10 lbs/in <sup>2</sup> pressure) ... ..	27
2. Graphical representation of alkali concentration vs. percentage of $\alpha$ -cellulose contained in both bleached and unbleached samples of purified cellulose (digestion for 2 hrs. with 20 lbs/in <sup>2</sup> pressure) ... ..	28
3. Graphical representation of alkali concentration vs. percentage of $\alpha$ -cellulose contained in both bleached and unbleached samples of purified cellulose (digestion for 3 hrs. with 10 lbs/in <sup>2</sup> pressure) ... ..	29
4. Graphical representation of alkali concentration vs. percentage of $\alpha$ -cellulose contained in both bleached and unbleached samples of purified cellulose (digestion for 3 hrs. with 20 lbs/in <sup>2</sup> pressure) ... ..	30

## FIGURE

## PAGE

5. Graphical representation of alkali concentration vs. percentage of  $\alpha$ -cellulose contained in bleached samples of purified cellulose (digestion under 10 lbs/in<sup>2</sup> pressure for 2 and 3 hrs.)... .. 31
6. Graphical representation of alkali concentration vs. percentage of  $\alpha$ -cellulose contained in bleached samples of purified cellulose (digestion under 20 lbs/in<sup>2</sup> pressure for 2 and 3 hrs.)... .. 32
7. Graphical representation of alkali concentration vs. percentage of  $\alpha$ -cellulose contained in bleached samples of purified cellulose (digestion for 2 hrs. under pressure 10 lbs/in<sup>2</sup> and 20 lbs/in<sup>2</sup>) ... .. 33
8. Histogram showing percentages of  $\alpha$ -cellulose in bleached samples of purified cellulose (digestion with 10% NaOH for 2 hrs.) ... .. 34
9. Graphical representation of various percentages of reaction media vs. degrees of substitution of etherification products ... .. 39

## FIGURE

## PAGE

10. Degrees of substitution of sodium carboxymethyl-cellulose obtained from multistep of etherification, using mixtures of benzene and ethyl alcohol as reaction media and 7 days for each etherification step ... .. 43
11. Degrees of substitution of sodium carboxymethyl-cellulose obtained from multistep of etherification, using mixtures of methyl ethyl ketone and ethyl alcohol as reaction media and 7 days for each etherification step ... .. 44
12. Degrees of substitution of sodium carboxymethyl-cellulose obtained from 80:20 ME-EtOH medium and with 5 days for each step of etherification..48