

**EFFECTIVENESS OF ELASTOMER MATRIX TYPE ON  
ELECTROMECHANICAL RESPONSE OF CONDUCTIVE  
POLYPYRROLE/ELASTOMER BLENDS**

Piyalarp Ludeelard

A Thesis Submitted in Partial Fulfilment of the Requirements  
for the Degree of Master of Science  
The Petroleum and Petrochemical College, Chulalongkorn University  
in Academic Partnership with  
The University of Michigan, The University of Oklahoma,  
Case Western Reserve University, and Institut Français du Pétrole

2006

ISBN 974-993-798-8

**Thesis Title:** Electroactive of Pure elastomers, and Polypyrrole/ elastomer Blends.  
**By:** Piyalarp Ludeelerd  
**Program:** Polymer Science  
**Thesis Advisors:** Assoc. Prof. Anuvat Sirivat  
Prof. Alexander M. Jamieson

---

Accepted by the Petroleum and Petrochemical College, Chulalongkorn University, in partial fulfilment of the requirements for the Degree of Master of Science.

.....*Nantaya Yanumet*..... College Director  
(Assoc. Prof. Nantaya Yanumet)

**Thesis Committee:**

.....*Anuvat Sirivat*.....  
(Assoc. Prof. Anuvat Sirivat)

.....*Alexander M. Jamieson*.....  
(Prof. Alexander M. Jamieson)

.....*Pitt Supaphol*.....  
(Asst. Prof. Pitt Supaphol)

.....*Ratana Rujiravanit*.....  
(Asst. Prof. Ratana Rujiravanit)

**ABSTRACT**

4772018063: Polymer Science Program

Piyalarp Ludeelard: Electroactive of Pure elastomers, and Polypyrrole/ elastomer Blends.

Thesis Advisors: Assoc. Prof. Anuvat Sirivat and Prof. Alexander M. Jamieson 151 pp. ISBN 974-993-798-8

Keywords: Electroactive polymer/ Poly(pyrrole)/ Elastomer/ Dynamic moduli/ Electrorheological properties

Electrorheological properties of pristine elastomers and polypyrrole/elastomer blends were investigated to identify the most suitable elastomer to be used for electroactive actuator applications. Seven types of elastomer: poly acrylate copolymers (AR70, AR71, AR72, and SAR), poly(dimethyl siloxane) (PDMS), poly(styrene butadiene) (SBR), and poly(styrene isoprene styrene) (SIS) were chosen as the candidate dielectric elastomers. Experiments were carried under the oscillatory shear mode and with applied electric field strength varying from 0 to 2 kV/mm. For pure elastomers, the dynamic modulus,  $G'$  response varied by 7 order of magnitude depending on the type of elastomer and electric field strength; the storage modulus ( $G'$ ) increased monotonically with increasing electric field. The storage modulus sensitivity,  $\Delta G'/G'_0$ , increased with electric field strength and attained maximum values of 97.15 % for SBR, 148.82 % for SAR, 232.64% for AR70, 12.78 %, for PDMS, 69.47% for AR71, 54.38% for AR72, and 10.00 % for SIS at the electric field strength of 2 kV/mm. There appear to be correlations between the elastomer storage modulus sensitivity and  $G'_0$  and/or electrical conductivity. For the undoped polypyrrole/elastomer blends with the particle concentrations of 1, 2, 3, 4 and 5 vol%, the storage modulus response increased linearly with concentration in the absence of electric field but nonlinearly with electric field on, possibly due to the obstruction of the matrix dipole interaction at small concentration and the non uniform polypyrrole particle dispersion in the matrix.

## บทคัดย่อ

ปีชะลาภ ฤดีเลิศ : ผลกระทบจากชนิดของยางที่ส่งผลถึงการตอบสนองเชิงกลภายใต้สนามไฟฟ้าของพอลิเมอร์ผสมระหว่างพอลิไพโรลและยางในสภาพของแข็ง (Electroactive of Pure elastomers, and Polypyrrole/ elastomer Blends) อ. ที่ปรึกษา รศ.ดร. อนุวัฒน์ ศิริวัฒน์ และ ศ. ดร. อเล็กซานเดอร์ เอ็ม เจมิชอัน 151 หน้า ISBN 974-993-798-8

ยางที่มีสมบัติเป็นฉนวนทางไฟฟ้าถูกใช้สำหรับเป็น ส่วนเคลื่อนไหวจากการที่มันมีการยืดตัวสูงที่ความเข้มกระแสไฟฟ้ามากในรายงานนี้ สมบัติของรีโอโลยีของยางหลายชนิด และพอลิเมอร์ ผสมถูกทดสอบเพื่อที่จะหาว่ายางชนิดใดที่จะมีความเหมาะสมมากที่สุดที่จะนำไปใช้เป็น ส่วนเคลื่อนไหวต่อไปเราสนใจศึกษายาง 7 ชนิดนั้นก็คือ พวกรubber อะคริลิกนั้นมี 4 เกรด (AR70, AR71, AR72, และ SAR) โพลีไดเมทิลซิลิโคน (PDMS), โพลีสไตรีนบิวตะไดอิน (SBR) และโพลีสไตรีน ไอโซพรีน สไตรีน (SIS) ใช้เป็นตัวช่วยในการทดลอง การทดลองดำเนินการโดยให้แรงเหวี่ยงกลับไปกลับมาและให้สนามไฟฟ้า ตั้งแต่ 0 ถึง 2 กิโลโวลต์ต่อมิลลิเมตรกับสารตัวอย่างทั้งยางบริสุทธิ์ และ พอลิเมอร์ผสม จากการศึกษาพบว่า สมบัติทางรีโอโลยีของพอลิเมอร์บริสุทธิ์ขึ้นอยู่กับ สมบัติเฉพาะตัวของพอลิเมอร์แต่ละชนิด และ ความเข้มสนามไฟฟ้าจากค่าสต่อแรง และ ลอสมอดูลัสเพิ่มขึ้น แปรผันตรงกับความเข้มของสนามไฟฟ้าโดยจะมีค่าสูงสุดอยู่ที่ 2 กิโลโวลต์ต่อมิลลิเมตร ยางพอลิอะคริลิก ชนิด AR70 จะมีค่าความไวต่อการเปลี่ยนแปลงค่าสต่อแรงมากที่สุด เท่ากับ 232.64 เปอร์เซ็นต์ จากการทดลองที่ผ่านมาสามารถ พิสูจน์ได้ว่าค่าที่ได้นั้นเกี่ยวข้องกับสูตรโครงสร้าง และค่าความแข็งแรงของยางอะคริลิก

สำหรับ โพลิเมอร์ผสมระหว่าง พอลิไพโรลกับพอลิอะคริลิก AR70 นั้น ถูกกำหนดให้มีความเข้มข้นของผงพอลิไพโรลเท่ากับ 1, 2, 3, 4 และ 5 เปอร์เซ็นต์ ค่าความตอบสนองต่อการเปลี่ยนแปลงค่าสต่อแรงมอดูลัสของพอลิเมอร์ผสมนั้นเพิ่มขึ้นเป็นเส้นตรงไปในทางเดียวกันกับความเข้มข้นของผงพอลิไพโรลในขณะที่ไม่ได้ใส่กระแสไฟฟ้า แต่เมื่อได้ใส่กระแสไฟฟ้าแล้วความสัมพันธ์ที่ได้จะไม่เป็นเส้นตรง เนื่องจากความไม่สม่ำเสมอของผงพอลิไพโรล และ ผงพอลิไพโรลที่มีความเข้มข้นน้อยนั้นไปขัดขวางกันการเกิดไดโพล ของยางอะคริลิก

## ACKNOWLEDGEMENTS

The author would like to express sincere gratitude to my advisors Assoc. Prof. Anuvat Sirivat for their assistances. He has provided the very useful guidance throughout this research. This thesis work is partially funded by Postgraduate Education and Research Programs in Petroleum and Petrochemical Technology (PPT Consortium)

The author would like to thank the Petroleum and Petrochemical College, Chulalongkorn University where the author have gained the invaluable knowledge in the Polymer Science program and the author greatly appreciates all professors, lecturers and staffs who have tendered knowledge and technical support during her stay in this college.

He would like to express his sincere appreciation to Asst. Prof. Pitt Supaphol and Asst. Prof. Ratana Rujiravanit for being on his committee and to thank due to Ms. Ladawan Ruandchuay, Ms Piyanoot Hiumtup and his excellence friends Mr. Ruksapong Kunanuruksapong for their various suggestions and discussion on this work and the oral presentations.

Finally he special thanks to the Dow Chemicals (Thailand) co.ltd, and Zeon polymix co.ltd for supplying the valuable samples rubber and to my family for their love, understanding, constant encouragement, and financial support during studying and thesis work.

## TABLE OF CONTENTS

	<b>PAGE</b>	
Title Page	i	
Abstract (in English)	iii	
Abstract (in Thai)	iv	
Acknowledgements	v	
Table of Contents	vi	
List of Tables	ix	
List of Figures	x	
 <b>CHAPTER</b>		
<b>I</b>	<b>INTRODUCTION</b>	<b>1</b>
<b>II</b>	<b>LITERATURE SURVEY</b>	<b>3</b>
	2.1 Conductive Polymer	3
	2.2 Conduction Mechanism	4
	2.3 Ppy Synthesis	7
	2.4 Concept of Doping	8
	2.5 Polymer Actuator	9
	2.6 Acrylic Elastomer (ACM)	12
	2.7 Styrenics	14
	2.8 Silicones (Polysiloxanes)	16
	2.9 Polypyrrole Synthesis	17
	2.10 Doping Ppy	19
	2.11 Actuator or Artificial Muscle	20
	2.12 Ppy Composites	24
<b>III</b>	<b>EXPERIMENTAL</b>	<b>27</b>
	3.1 Materials and Instruments	27
	3.1.1 Materials	27

<b>CHAPTER</b>	<b>PAGE</b>
3.1.2 Instrument	27
3.2 Experiment Methods	28
3.2.1 Preparation of Poly(pyrrole) Ppy	28
3.2.2 Characterization Method	29
<b>IV EFFECTIVENESS OF THE ELASTOMER MATRIX TYPE ON ELECTROMECHANICAL CONDUCTIVE POLYPYRROLE/ELASTOMER BLENDS</b>	33
4.1 Abstract	33
4.2 Introduction	34
4.3 Experimental Part	35
4.4 Results and Discussion	38
4.5 Conclusions	44
4.6 Acknowledgements	44
4.7 Reference	44
<b>V CONCLUSIONS</b>	54
<b>REFERENCES</b>	55
<b>APPENDICES</b>	60
<b>Appendix A</b> Identification of Characteristic FT-IR Spectrum of Undoped and Doped Poly(Pyrrole)	60
<b>Appendix B</b> Identification of Characteristic Peaks of Undoped and Doped Poly(Pyrrole) from UV-Visible Spectroscopy	62
<b>Appendix C</b> Determination of Particle Sizes of Undoped and Doped Polypyrrole	64
<b>Appendix D</b> Density Measurement	67

<b>CHAPTER</b>	<b>PAGE</b>
<b>Appendix E</b> Identification Thermal Property of Undoped, doped Ppy and Pure Elastomer.	69
<b>Appendix F</b> Specification of the elastomer matrices	72
<b>Appendix G</b> Determination of the Correction Factor (K)	76
<b>Appendix H</b> Conductivity Measurement	80
<b>Appendix I</b> Identification of Crystallinity of Undoped and Doped Ppy	96
<b>Appendix J</b> Scanning Electron Micrograph of Undoped Ppy, Doped Ppy and Polypyrrole/ Polyacrylate rubber Blends (Ppy_U/AR70)	98
<b>Appendix K</b> Electrorheological Properties Measurement of Pure Elastomer Matrix	102
<b>Appendix L</b> Electrorheological Properties Measurement of Polymer Blends between Ppy and AR70 at Various ratio of Ppy	129
<b>CURRICULUM VITAE</b>	151



**LIST OF TABLES**

<b>TABLE</b>		<b>PAGE</b>
<b>CHAPTER IV</b>		
4.1	Rheology properties of various matrices	46
4.2	Rheology properties of various particle concentrations.	47
4.3	Induction time and recovery time of pure polyacrylate (AR70) polypyrrole/ polyacrylate (AR70) elastomer blends.	48

## LIST OF FIGURES

FIGURE		PAGE
<b>CHAPTER II</b>		
2.1	Schematic diagram of conjugated polymers in their neutral forms	3
2.2	Schematic diagram of the band structure of metals, semiconductors, and insulators ( $E_g$ is the energy gap between the valence band (VB) and the conduction band (CB)).	5
2.3	Schematic diagram of soliton of polyacetylene, and polaron, bipolaron of poly(thiophene).	6
2.4	Polymeric system with actuator properties	10
2.5	A bimorph based on the conducting polymer polyaniline (PAni)	11
2.6	Dielectric elastomer actuator unit.	12
2.7	Electroactive respond of Acrylic Elastomer	12
2.8	Structural Formula of a Chlorine-Containing ACM.	13
2.9	The monomer for Acrylic Elastomer.	13
2.10	Structures of three common styrenic block copolymer TPEs a) poly(styrene butadiene styrene, SBS), b) poly (styrene isoprene styrene, SIS) and c) poly (styrene rthylene/butylene styrene, SEBS).	14
2.11	Polydimethylsiloxane synthesis.	16
<b>CHAPTER III</b>		
3.1	Flow chart of polypyrrole chemical polymerization	28

FIGURE		PAGE
<b>CHAPTER IV</b>		
4.1	The morphology of polypyrrole and polypyrrole/polyacrylate blends a) synthesized polypyrrole at magnification of 7,500; b) synthesized doped polypyrrole at magnification of 1,500, AR70;1_un c) AR70;3_un and d) AR70;5_un at magnification of 350.	49
4.2	Effect of matrices on: storage modulus sensitivity ( $\Delta G'/G'_0$ ) vs. electric fields strength: 0 to 2 KV/mm at frequency 1 rad/s, strain 1%(except PDMS strain = 700%), and at 27 °C.	50
4.3	Sensitivity vs. $G'_0$ , strain 1.0%(except PDMS was tested at 700%), frequency 1.0 rad/s, and 27 °C at: (a) solid line, 2 kV; (b) dash line, 1 kV.	51
4.4	Sensitivity vs. conductivity, strain 1.0% (except PDMS was tested at 700%), frequency 1.0 rad/s, and 27°C at: (a) solid line, 2 kV; (b) dash line, 1 kV.	51
4.5	Frequency sweep test of polymer blend between Ppy and AR70 at 4% v/v of Ppy (AR70:4_un), strain 1%, 27° C, gap 0.295 mm at various electric field strengths.	52
4.6	Sensitivity of the polymer blends between AR70 and Ppy ( $G'$ and $\Delta G'_{2kV}/G'_0$ ), versus Ppy various concentrations at 27°C, frequency 1 rad/s.	52
4.7	Temporal response of storage modulus ( $G'$ ) of AR70 matrix at electric field strength of 1 and 2 KV/mm, frequency 1.0 rad/s, strain 0.1%, and at 27 °C.	53
4.8	Temporal response of storage modulus ( $G'$ ) of polymer blend between AR70 and undoped Ppy 4% v/v (AR71:4_un) at electric field strength of 1 and 2 KV/mm, frequency 1.0 rad/s, strain 1.0%, and at 27 °C.	53