

**FABRICATION OF POLY(*P*-PHENYLENE)/ZEOLITE COMPOSITES  
AS AMMONIA SENSOR**

Pimchanok Phumman

A Thesis Submitted in Partial Fulfillment of the Requirements  
for the Degree of Master of Science  
The Petroleum and Petrochemical College, Chulalongkorn University  
in Academic Partnership with  
The University of Michigan, The University of Oklahoma,  
Case Western Reserve University and Institute Français du Pétrole

2007

501996

**Thesis Title:** Fabrication of Poly(*p*-phenylene)/Zeolite Composites  
as Ammonia Sensor  
**By:** Pimchanok Phumman  
**Program:** Polymer Science  
**Thesis Advisors:** Assoc. Prof. Anuvat Sirivat  
Prof. Johannes W. Schwank

---

Accepted by the Petroleum and Petrochemical College, Chulalongkorn University, in partial fulfillment of the requirements for the Degree of Master of Science.

..... *Nantaya Yanumet* ..... College Director  
(Assoc. Prof. Nantaya Yanumet)

**Thesis Committee:**

..... *Anuvat Sirivat* .....  
(Assoc. Prof. Anuvat Sirivat)

..... *Johannes W. Schwank* .....  
(Prof. Johannes W. Schwank)

..... *Sujitra Wongkasemjit* .....  
(Assoc. Prof. Sujitra Wongkasemjit)

..... *Thirasak Rirksomboon* .....  
(Assoc. Prof. Thirasak Rirksomboon)

## ABSTRACT

4872016063: Polymer Science Program  
 Pimchanok Phumman: Fabrication of a Poly(*p*-phenylene)/Zeolite  
 Composites as Ammonia Sensor.  
 Thesis Advisors: Assoc. Prof. Anuvat Sirivat, and  
 Prof. Johannes W. Schwank 116 pp.  
 Keywords: Conductive polymer/ Gas sensor/ Poly(*p*-phenylene)/ Ammonia/  
 ZSM-5

Poly(*p*-phenylene) (PPP) is a one type of conductive polymers that has a potential as a gas sensing material because its optical and electrical property changes when exposed to particular gases. PPP was chemically synthesized via the oxidative polymerization of benzene and doped with FeCl<sub>3</sub>. Electrical conductivity response of doped PPP (dPPP) towards CO, H<sub>2</sub> and NH<sub>3</sub> was investigated. dPPP showed no response towards CO and H<sub>2</sub>, but it showed a definite negative response to NH<sub>3</sub>. The electrical conductivity sensitivity of dPPP increased with increasing NH<sub>3</sub> concentration. In order to improve sensitivity of the sensor, ZSM-5 zeolite was added into the conductive polymer matrix. The sensitivity of the sensor increased with increasing zeolite content up to 30%. Moreover, an effect of cation type containing in the zeolite pore was investigated, including Na<sup>+</sup>, K<sup>+</sup>, NH<sub>4</sub><sup>+</sup> and H<sup>+</sup>. The sensitivity of the composite with different cation containing in zeolite were organized; 50:1dPPP(90)/KZ23 < 50:1dPPP < 50:1dPPP(90)/NaZ23 < 50:1dPPP(90)/NH<sub>4</sub>Z23 < 50:1dPPP(90)/HZ23. The sensitivity increase with changing cation type can be described in term of acidic properties. The 50:1dPPP(90)/HZ23 possessed highest sensitivity of -0.36 due to H<sup>+</sup> has highest acidity which induces more favorable NH<sub>3</sub> adsorption and interaction with the conductive polymer.

## บทคัดย่อ

พิมพ์ชนก พุ่มมัน : การสร้างคอมโพสิตของพอลิพาราฟีนิลีนและซีโอไลต์เพื่อใช้ในการตรวจวัดก๊าซแอมโมเนีย (Fabrication of Poly(p-phenylene)/Zeolite composites as Ammonia Sensor) อ. ที่ปรึกษา : รศ.ดร. อนุวัฒน์ ศิริวัฒน์ และ ศ.ดร. โจแฮนเนส ดับบลิว ชเวงค์ 116 หน้า

พอลิพาราฟีนิลีนเป็นพอลิเมอร์นำไฟฟ้าชนิดหนึ่งที่มีความสามารถใช้เป็นวัสดุที่ใช้สำหรับงานตรวจวัดก๊าซได้เนื่องจากสามารถเปลี่ยนแปลงคุณสมบัติทางแสงและทางไฟฟ้าได้เมื่ออยู่ภายใต้สภาวะของก๊าซชนิดพิเศษ พอลิพาราฟีนิลีนถูกสังเคราะห์โดยวิธีพอลิเมอร์ไรเซชันแบบออกซิเดชันและเพิ่มความสามารถทางการนำไฟฟ้าด้วยสารละลายเฟอร์ริกคลอไรด์ จากนั้นได้ศึกษาการตอบสนองทางคุณสมบัติการนำไฟฟ้าของพอลิพาราฟีนิลีนเมื่อสัมผัสกับก๊าซคาร์บอนมอนอกไซด์ ไฮโดรเจนและแอมโมเนีย จากการทดลองพบว่าพอลิพาราฟีนิลีนไม่มีการตอบสนองทางคุณสมบัติการนำไฟฟ้าเมื่อสัมผัสกับก๊าซคาร์บอนมอนอกไซด์และไฮโดรเจน แต่มีการตอบสนองทางคุณสมบัติการนำไฟฟ้าทางลบกับก๊าซแอมโมเนีย ซึ่งความว่องไวทางคุณสมบัติการนำไฟฟ้าของพอลิพาราฟีนิลีนเพิ่มขึ้นเมื่อความเข้มข้นของก๊าซแอมโมเนียเพิ่มขึ้น และเพื่อเพิ่มความว่องไวดังกล่าว จึงผสมซีโอไลต์ซีเอสเอ็มไฟฟ้าเข้ากับเมทริกซ์ของพอลิพาราฟีนิลีน พบว่าความว่องไวในการจับก๊าซแอมโมเนียเพิ่มขึ้นเมื่อปริมาณซีโอไลต์เพิ่มขึ้นจนถึง 30% นอกจากนี้ได้ศึกษาปัจจัยของชนิดของแคทไอออนในซีโอไลต์ ซึ่งประกอบด้วย โซเดียมไอออน โพแทสเซียมไอออน แอมโมเนียมไอออน และไฮโดรเจนไอออน พบว่าความว่องไวทางคุณสมบัติการนำไฟฟ้าของคอมโพสิตเนื่องจากชนิดของไอออนสามารถลำดับจากมากไปน้อยได้ ดังนี้ ไฮโดรเจน แอมโมเนียม โซเดียม และโพแทสเซียมไอออน ความว่องไวในการจับแอมโมเนียของคอมโพสิตที่มีแคทไอออนในซีโอไลต์แตกต่างกันสามารถอธิบายโดยเหตุผลของความเป็นกรด ซึ่งคอมโพสิตของพอลิพาราฟีนิลีนกับซีโอไลต์ที่มีไฮโดรเจนไอออนมีความว่องไวในการจับก๊าซแอมโมเนียมากที่สุดถึง -0.36 อาจเป็นผลมาจากความเป็นกรดสูงสุดของซีโอไลต์ซึ่งมีส่วนช่วยในการเหนี่ยวนำการดูดซับแอมโมเนียของคอมโพสิต

## ACKNOWLEDGEMENTS

The author is thankful for the scholarship and partial of the thesis work provided by the Petroleum and Petrochemical College; and the National Excellence Center for Petroleum, Petrochemicals, and Advanced Materials, Thailand.

The author would like to thank all faculties who have offered valuable knowledge, especially, Assoc. Prof. Anuvat Sirivat who is her advisor with offering several enlightening suggestions, discussions and problem solving direction entirely the course of his work. She also would like to thank Prof. Johannes W. Schwank for being an advisor.

She would like to express thanks to Assoc. Prof. Sujitra Wongkasemjit and Assoc. Prof. Thirasak Rirksomboon for kindly being on her thesis committee

Special thanks for all EACP group members for their various helpful discussions and suggestions on this work.

She would like to thank Mr. Robert Wright for the encouragement and the suggestions on both writing and all presentations.

Extraordinary thanks Mr. Surapas and his advisor who are very kind to allow me to use  $\text{NH}_3$ -TPD system.

Finally, she really would like to thank with sincerest appreciation for her parents and family for the love, understanding, and encouragement, for friends of hers for suggestions, helping and cheering.

## TABLE OF CONTENTS

	PAGE
Title Page	i
Abstract (in English)	iii
Abstract (in Thai)	iv
Acknowledgements	v
Table of Contents	vi
List of Tables	ix
List of Figures	x

### CHAPTER

<b>I</b>	<b>INTRODUCTION</b>	1
<b>II</b>	<b>LITERATURE REVIEW</b>	3
	2.1 Conductive Polymer	
	2.1.1 Mechanism of Polymer Conductivity and Doping	3
	2.1.2 Poly( <i>p</i> -phenylene)	6
	2.2 Zeolite	8
	2.3 Poly( <i>p</i> -phenylene) Synthesis	10
	2.4 Conductive Polymer as Sensors	11
	2.5 Zeolite as Gas Adsorbents	14
	2.6 Conductive Polymer/Zeolite composite as Sensors	17
	2.7 Poly( <i>p</i> -phenylene) as a Gas Sensor	18
<b>III</b>	<b>EXPERIMENTAL</b>	
	3.1 Materials	20
	3.2 Equipments	20
	3.3 Methodology	21

CHAPTER	PAGE
3.3.1 Preparation of Poly( <i>p</i> -phenylene)	21
3.3.1.1 Preparation of Poly( <i>p</i> -phenylene) Synthesis	21
3.3.1.2 Preparation of Poly( <i>p</i> -phenylene) Doping	21
3.3.2 Preparation of Zeolitic Materials	22
3.3.3 Composite Preparation	22
3.3.4 Characterization	22
3.3.5 Gas Measurement	25
<b>IV FABRICATION OF A POLY(P-PHENYLENE)/ZEOLITE COMPOSITES AS AMMONIA SENSOR</b>	
4.1 Abstract	28
4.2 Introduction	29
4.3 Experiment	30
4.4 Results and Discussion	32
4.5 Conclusions	37
4.6 Acknowledgement	38
4.7 References	45
<b>V CONCLUSIONS</b>	49
<b>REFERENCES</b>	50
<b>APPENDICES</b>	
<b>Appendix A</b> Investigation of Characteristic Peaks of FT-IR Spectrum of Undoped and Doped Poly( <i>p</i> -phenylene)	57
<b>Appendix B</b> Thermal Property of uPPP and 50:1 dPPP	59
<b>Appendix C</b> Identification of Crystallinity of uPPP and 50:1 dPPP and Structure of Zeolite	61

<b>CHAPTER</b>	<b>PAGE</b>
<b>Appendix D</b> Determination of Particle Size and Particle Size Distribution of PPP and Zeolite Powder	63
<b>Appendix E</b> Density Measurement	66
<b>Appendix F</b> Morphology	67
<b>Appendix G</b> Identification of Si/Al and Cation Exchange Level of Zeolite	70
<b>Appendix H</b> Surface Area and Pore Volume of Zeolite	71
<b>Appendix I</b> Correction Factor Measurement	72
<b>Appendix J</b> Conductivity Measurement	78
<b>Appendix K</b> Electrical Conductivity Sensitivity Measurement	82
<b>Appendix L</b> Ammonia Temperature Programmed Desorption	107
<b>Appendix M</b> Investigation of Interaction between dPPP, dPPP Composites, NaZSM-5(23) and NH <sub>3</sub> by using FTIR Technique	109
<b>CURRICULUM VITAE</b>	116



## LIST OF TABLES

TABLE		PAGE
<b>CHARPTER IV</b>		
4.1	The cation exchange level of $\text{NH}_4\text{ZSM-5(23)}$ with $\text{Na}^+$ and $\text{K}^+$	38
4.2	Surface area and pore volume of zeolite	38
4.3	dPPP samples with electrical conductivity responses, sensitivities and temporal responses to $\text{CO}$ , and $\text{H}_2$	39

## LIST OF FIGURES

FIGURE	PAGE
<b>CHAPTER II</b>	
2.1 $\pi$ -conjugation in poly(acetylene)	3
2.2 Different band gap of an insulator, a semiconductor and a metal	4
2.3 Repeat unit of electrically conductive polymers	5
2.4 Simplified polaron-bipolaron of PPP	7
2.5 Zeolite constructions	8
<b>CHAPTER III</b>	
3.1 Conductivity detectors with gas chamber.	24
<b>CHAPTER IV</b>	
4.1 $\text{NH}_3$ -TPD thermogram of ZSM-5(23) with various cation types	39
4.2 The morphology of dPPP particles, ZSM-5(23) powders and dPPP/zeolite composites	40
4.3 $\sigma$ vs. ZSM-5(23) content by volume of 50:1dPPP/NaZSM-5(23) in air and $\text{N}_2$	41
4.4 $\Delta\sigma / \sigma_{\text{N}_2}$ of 50:1dPPP at various $\text{NH}_3$ concentrations	41
4.5 Proposed mechanism of the 50:1dPPP- $\text{NH}_3$ interaction	42
4.6 $\Delta\sigma / \sigma_{\text{N}_2}$ of 50:1dPPP/NaZSM-5(23) composites to $\text{NH}_3$ at various NaZSM-5(23) contents	42
4.7 $\Delta\sigma / \sigma_{\text{N}_2}$ of 50:1 dPPP and 50:1 dPPP(90)/ZSM-5(23) composites to 0.625%v $\text{NH}_3$ at various cation types	43
4.8 FT-IR spectra of 50:1 dPPP before, during and after $\text{NH}_3$ exposure	43
4.9 FT-IR spectra of NaZSM-5(23) before, during and after $\text{NH}_3$ exposure	44