

**PHOTOCATALYTIC DEGRADATION OF 4-CHLOROPHENOL
USING Pt/TiO₂-SiO₂ PREPARED BY THE SOL-GEL METHOD**



Ms. Rungnuch Tharathonpisutthikul

A Thesis Submitted in Partial Fulfilment of the Requirements
for the Degree of Master of Science
The Petroleum and Petrochemical College, Chulalongkorn University
in Academic Partnership with
The University of Michigan, The University of Oklahoma,
and Case Western Reserve University

2001

ISBN 974-13-0682-2

Thesis Title : Photocatalytic Degradation of 4-Chlorophenol using
Pt/TiO₂-SiO₂ Prepared by the Sol-Gel Method
By : Ms. Rungnuch Tharathonpisutthikul
Program : Petrochemical Technology
Thesis Advisors : Prof. Erdogan Gulari
Assoc. Prof. Sumaeth Chavadej
Dr. Pramoch Rangsunvigit

Accepted by the Petroleum and Petrochemical College, Chulalongkorn University, in partial fulfilment of the requirements for the Degree of Master of Science.

K. Bunyakiat.
..... College Director
(Assoc.Prof. Kunchana Bunyakiat)

Thesis Committee:

Erdogan Gulari
.....
(Prof. Erdogan Gulari)

Sumaeth Chavadej
.....
(Assoc. Prof. Sumaeth Chavadej)

Pramoch
.....
(Dr. Pramoch Rangsunvigit)

Thirasak Rirksomboon
.....
(Assist. Prof. Thirasak Rirksomboon)

บทคัดย่อ

รุ่งนุช ธรรมชาติพิสุทธิกุล : การสลาย 4-คลอโรฟีนอลด้วยวิธีโฟโตคะตะไลซิสโดยใช้ตัวเร่งปฏิกิริยาแพลทินัมบนไททานี-ซิลิกาที่เตรียมโดยวิธีโซล-เจล (Photocatalytic Degradation of 4-Chlorophenol using Pt/TiO₂-SiO₂ Prepared by the Sol-Gel Method) อ. ที่ปรึกษา : ศ. เออโดแกน กุลารี, รศ. สุเมธ ชวเดช และ ดร. ปราโมช รังสรรค์วิจิตร 87 หน้า ISBN 974-13-0682-2

งานวิจัยนี้ศึกษาการสลายสาร 4-คลอโรฟีนอล ด้วยวิธีโฟโตคะตะไลซิสโดยใช้ตัวเร่งปฏิกิริยา ไททานี-แพลทินัมบนไททานี ไททานี-ซิลิกา และ แพลทินัมบนไททานี-ซิลิกา ที่เตรียมโดยวิธีโซล-เจล ได้ทำการศึกษาปัจจัยต่างๆ ที่มีผลต่ออัตราการสลายของสาร 4-คลอโรฟีนอล ได้แก่ ปริมาณของตัวเร่งปฏิกิริยา อุณหภูมิที่ใช้ในการแคลไซน์ และ ค่าความเป็นกรดต่างของสารละลายเริ่มต้น ในการทดลอง ตัวเร่งปฏิกิริยาใช้แสงถูกนำไปกระจายตัวในสารละลาย 4-คลอโรฟีนอลภายใต้การฉายแสงจากหลอดไฟฟ้าปรอทขนาด 11 วัตต์ ที่มีความยาวคลื่น 100-280 นาโนเมตร ผลการทดลองแสดงว่า อัตราการสลายค่าที่ไอซีหรือ ปริมาณสารอินทรีย์ในสารละลายเพิ่มขึ้น เมื่อปริมาณตัวเร่งปฏิกิริยาเพิ่มขึ้น และปริมาณที่เหมาะสมของตัวเร่งปฏิกิริยาไททานีคือ 0.7 กรัมต่อลิตร อัตราการสลายตัวของค่าที่ไอซีลดลงเมื่อเพิ่มอุณหภูมิในการแคลไซน์ตัวเร่งปฏิกิริยา เนื่องจากเกิดการเปลี่ยนแปลงโครงสร้างผลึกของไททานีจากอนาเทสไปเป็นรูไทล์เมื่ออุณหภูมิในการแคลไซน์เพิ่มสูงขึ้น ส่วนค่าพีเอชของสารละลายเริ่มต้นไม่มีผลต่ออัตราการสลายตัวของค่าที่ไอซี สำหรับตัวเร่งปฏิกิริยาแพลทินัมบนไททานีพบว่า การเติมแพลทินัมบนไททานีสามารถเพิ่มประสิทธิภาพของตัวเร่งปฏิกิริยาได้ และปริมาณของแพลทินัมบนไททานีที่มีประสิทธิภาพดีที่สุด คือ 1 เปอร์เซ็นต์โดยโมล สำหรับตัวเร่งปฏิกิริยาไททานี-ซิลิกา พบว่า ปริมาณซิลิกา 10 เปอร์เซ็นต์โดยโมลในไททานีมีประสิทธิภาพดีที่สุด เนื่องจากมีค่าคงที่ของการดูดซับสูงสุด สำหรับแพลทินัมบนไททานี-ซิลิกา พบว่า ถึงแม้ว่าการเติมแพลทินัม 1 เปอร์เซ็นต์ หรือ ซิลิกา 10 เปอร์เซ็นต์อย่างใดอย่างหนึ่ง ในไททานีจะสามารถปรับปรุงประสิทธิภาพของตัวเร่งปฏิกิริยาได้ แต่ไม่พบการเสริมประสิทธิภาพกัน เมื่อเติมทั้ง แพลทินัม 1 เปอร์เซ็นต์ และ ซิลิกา 10 เปอร์เซ็นต์ในไททานี เนื่องจากเกิดการรวมตัวกันของตัวเร่งปฏิกิริยา ทำให้ประสิทธิภาพของตัวเร่งปฏิกิริยาลดลง

ABSTRACT

4271019063: PETROCHEMICAL TECHNOLOGY PROGRAM

Rungnuch Tharathonpisutthikul: Photocatalytic Degradation of 4-Chlorophenol using Pt/TiO₂-SiO₂ Prepared by the Sol-Gel Method. Thesis Advisors: Prof. Erdogan Gulari, Assoc. Prof. Sumaeth Chavadej and Dr. Pramoch Rangsunvigit, 87 pp ISBN 974-13-0682-2

Keywords: Photocatalysis/4-Chlorophenol/Sol-gel/Pt/TiO₂

Photocatalytic degradation of 4-chlorophenol was studied using TiO₂, Pt/TiO₂, TiO₂-SiO₂ and Pt/TiO₂-SiO₂ prepared by the sol-gel method. The effects of catalyst amount, calcination temperature and initial pH of solution on the degradation were investigated. In the experiment, a photocatalyst was suspended in the 4-chlorophenol solution under irradiation from an 11 W low-pressure mercury lamp producing wavelengths of 100-280 nm. The results showed that the reduction rate of total organic carbon (TOC) increased with increasing the amount of TiO₂ catalyst and the optimum amount of TiO₂ was found to be 0.7 g/l. The TOC reduction rate decreased with increasing calcination temperature because of the transformation of TiO₂ from anatase to rutile at higher calcination temperatures. The initial pH of solution did not significantly affect the TOC reduction rate. For Pt/TiO₂ catalyst, addition of small amount of Pt into TiO₂ improved the catalyst activity and the highest activity was obtained with 1%Pt/TiO₂. For TiO₂-SiO₂ catalyst, the highest activity was achieved at 10%SiO₂-TiO₂ because of its highest adsorption capacity. For Pt/TiO₂-SiO₂ catalyst with 1 %Pt and 10 %SiO₂, although 1 %Pt or 10 %SiO₂ alone in TiO₂ could improve the catalyst activity, the synergistic effect of adding both 1 %Pt and 10 %Si was not observed due to the agglomeration of the catalyst which, in turn, lowered the catalyst activity.

ACKNOWLEDGEMENTS

The author would like to express the deepest gratitude to Assoc. Prof. Sumaeth Chavadej and Dr. Pramoch Rangsunvigit, her Thai advisors, who have tendered invaluable guidance, constructive advice and intensive attention throughout this research work.

She would like to especially thank Prof. Erdogan Gulari, her US advisor, who originated this thesis and provided useful recommendation, encouragement, vital opportunities throughout this research work.

She would like to give special thank to Mr. Siriphong Roatluechai and Ms. Chalothorn Sophonvuttikul for giving encouragement and invaluable suggestions throughout this research work.

Finally, She greatly appreciates her family for their love, understanding and partially financial support.

TABLE OF CONTENTS

	PAGE
Title Page	i
Abstract (in English)	iii
Abstract (in Thai)	iv
Acknowledgements	v
Table of Contents	vi
List of Tables	ix
List of Figures	x
CHAPTER	
I INTRODUCTION	1
II BACKGROUND AND LITERATURE SURVEY	3
2.1 Principle of Photocatalysis Reaction	3
2.2 Types and Forms of Catalyst	6
2.2.1 Types of Semiconductor	6
2.2.2 Supported TiO ₂	7
2.2.3 Metal-Loaded TiO ₂	9
2.3 Parameters Influencing the Rate of Degradation	10
2.3.1 Light Source	10
2.3.2 Initial Concentration	13
2.3.3 Amount of Catalyst	14
2.3.4 pH of Solution	14
2.3.5 Dissolved Oxygen	15
2.3.6 Temperature	16
III EXPERIMENTAL	17
3.1 Photocatalytic Preparation by Sol-Gel Method	17

CHAPTER	PAGE
3.1.1 Materials	17
3.1.2 Preparation Procedures	17
3.1.3 Catalyst Characterization	18
3.2 Photocatalytic Study	18
3.2.1 Materials	18
3.2.2 Experimental Setup	19
3.2.3 Experimental Procedure	20
3.2.4 Analytical Method	20
3.3 Adsorption of 4-Chlorophenol on Photocatalysts	20
IV RESULTS AND DISCUSSION	22
4.1 Characterization of Studied Photocatalysts	22
4.1.1 Crystal Structures of Studied Photocatalysts	22
4.1.1.1 Crystal Structure of TiO ₂	22
4.1.1.2 Crystal Structure of Pt/TiO ₂	25
4.1.1.3 Crystal Structure of TiO ₂ -SiO ₂	27
4.1.1.4 Crystal Structure of Pt/TiO ₂ -SiO ₂	32
4.1.2 Surface Structures of Studied Photocatalysts	34
4.1.2.1 Surface Structure of TiO ₂	34
4.1.2.2 Surface Structure of Pt/TiO ₂	35
4.1.2.3 Surface Structure of TiO ₂ -SiO ₂	35
4.1.2.4 Surface Structure of Pt/TiO ₂ -SiO ₂	37
4.1.3 Chemical Bond of TiO ₂ -SiO ₂	38
4.1.4 Morphology of Studied Photocatalysts	40
4.2 Photocatalytic Degradation of 4-Chlorophenol with TiO ₂	44

CHAPTER	PAGE
4.2.1 Effect of TiO ₂ Loading on 4-Chlorophenol Degradation	44
4.2.2 Effect of Calcination Temperature on 4-Chlorophenol Degradation	46
4.2.3 Effect of Initial Solution pH on 4-Chlorophenol Degradation	48
4.2.4 Comparison between Degussa P25 and Sol-Gel TiO ₂ for 4-Chlorophenol Degradation	48
4.3 Photocatalytic Degradation of 4-Chlorophenol with Pt/TiO ₂	51
4.4 Photocatalytic Degradation of 4-Chlorophenol with TiO ₂ -SiO ₂	53
4.5 Photocatalytic Degradation of 4-Chlorophenol with Pt/TiO ₂ -SiO ₂	60
V CONCLUSIONS AND RECOMMENDATIONS	64
REFERENCES	66
APPENDICES	69
CURRICULUM VITAE	87

LIST OF TABLES

TABLE	PAGE
2.1 The band positions of some common semiconductor photocatalysts	7
4.1 The crystallite sizes of Degussa P25 and sol-gel TiO ₂ calcined at different temperatures	25
4.2 The crystallite sizes of Pt/TiO ₂ calcined at 400 °C	27
4.3 The crystallite sizes of TiO ₂ -SiO ₂ at different %SiO ₂ and calcination temperatures	32
4.4 The crystallite sizes of Pt/TiO ₂ -SiO ₂ at the calcination temperature of 400-700 °C	34
4.5 The surface areas, pore sizes and pore volumes of Degussa P25 and sol-gel TiO ₂ at different calcination temperatures	35
4.6 The surface areas, pore sizes and pore volumes of Pt/TiO ₂ catalyst having different Pt loadings	36
4.7 The surface areas of TiO ₂ -SiO ₂ catalyst having different mol% of SiO ₂ calcined at different temperatures	36
4.8 The pore volumes of TiO ₂ -SiO ₂ catalyst having different mol% of SiO ₂ and calcined at different temperatures	37
4.9 The pore sizes of TiO ₂ -SiO ₂ catalyst having different mol% of SiO ₂ and calcined at different temperatures	37
4.10 The surface areas, pore sizes and pore volumes of Pt/TiO ₂ -SiO ₂ at different calcination temperatures (1 mol% Pt and 10 mol% SiO ₂)	38

LIST OF FIGURES

FIGURE	PAGE
2.1 Promotion of an electron from the valence band to the conductance band on illumination of a semiconductor	4
2.2 Theoretical regimes for rate dependence on the light intensity	11
3.1 Schematic of the photocatalytic reactor used in this experiment	19
4.1 X-ray diffraction pattern of Degussa P25	23
4.2 X-ray diffraction patterns of TiO ₂ prepared at different calcination temperatures	24
4.3 X-ray diffraction patterns for Pt/TiO ₂ catalysts at different Pt loadings prepared at calcination temperature of 400 °C	26
4.4 X-ray diffraction patterns of 5%SiO ₂ -TiO ₂ at different calcination temperatures	28
4.5 X-ray diffraction patterns of 10%SiO ₂ -TiO ₂ at different calcination temperatures	29
4.6 X-ray diffraction patterns of 20%SiO ₂ -TiO ₂ at different calcination temperatures	30
4.7 X-ray diffraction patterns of 30%SiO ₂ -TiO ₂ at different calcination temperatures	31
4.8 X-ray diffraction patterns of Pt/TiO ₂ -SiO ₂ at different calcination temperatures	33
4.9 FT-IR spectra of TiO ₂ and TiO ₂ -SiO ₂ having different SiO ₂ contents at the calcination temperature of 400 °C	39
4.10 FT-IR spectra of 10%SiO ₂ -TiO ₂ at different calcination temperatures	41

FIGURE	PAGE
4.11 SEM photographs of studied catalysts (a) TiO ₂ , (b) 1%Pt/TiO ₂ , (c) 10%SiO ₂ - TiO ₂ and (d) 1%Pt/10%SiO ₂ -TiO ₂	42
4.12 SEM photographs of catalysts surfaces (a) TiO ₂ , (b) 1%Pt/TiO ₂ , (c) 10%SiO ₂ TiO ₂ and (d) 1%Pt/10%SiO ₂ -TiO ₂	43
4.13 Photocatalytic degradation of 4-chlorophenol as a function of reaction time at different TiO ₂ loadings (a) remaining 4-chlorophenol fraction (b) remaining TOC fraction	45
4.14 Photocatalytic degradation of 4-chlorophenol as a function of reaction time at different calcination temperature of TiO ₂ catalyst (a) remaining 4-chlorophenol fraction (b) remaining TOC fraction	47
4.15 Photocatalytic degradation of 4-chlorophenol as a function of reaction time at different solution pH (a) remaining 4-chlorophenol fraction (b) remaining TOC fraction	49
4.16 Comparison of commercial TiO ₂ and sol-gel TiO ₂ prepared For photocatalytic degradation of 4-chlorophenol (a) remaining 4-chlorophenol fraction (b) remaining TOC fraction	50
4.17 Photocatalytic degradation of 4-chlorophenol by Pt/TiO ₂ having different Pt loadings (a) remaining 4-chlorophenol fraction (b) remaining TOC fraction	52
4.18 TOC/TOC ₀ at 360 minutes for different %Pt loadings on TiO ₂	53
4.19 Photocatalytic degradation of 4-chlorophenol by 5%SiO ₂ - TiO ₂ catalysts calcined at different temperatures (a) remaining 4-chlorophenol fraction (b) remaining TOC fraction	54

FIGURE	PAGE
4.20 Photocatalytic degradation of 4-chlorophenol by 10%SiO ₂ -TiO ₂ catalysts calcined at different temperatures (a) remaining chlorophenol fraction (b) remaining TOC fraction	55
4.21 Photocatalytic degradation of 4-chlorophenol by 20%SiO ₂ -TiO ₂ catalysts calcined at different temperatures (a) remaining chlorophenol fraction (b) remaining TOC fraction	56
4.22 Photocatalytic degradation of 4-chlorophenol by 30%SiO ₂ -TiO ₂ catalysts calcined at different temperatures (a) remaining chlorophenol fraction (b) remaining TOC fraction	57
4.23 The TOC/TOC ₀ value at 360 min by TiO ₂ -SiO ₂ catalyst having different mol% SiO ₂ and calcined at different temperatures	58
4.24 The relationship between mol% SiO ₂ and adsorption constant	59
4.25 Photocatalytic degradation of 4-chlorophenol as a function of time by 1%Pt/10%SiO ₂ -TiO ₂ catalysts calcined at different temperatures (a) remaining chlorophenol fraction (b) remaining TOC fraction	61
4.26 TOC/TOC ₀ value at 360 minutes for 1%Pt/10%SiO ₂ -TiO ₂ and 10%SiO ₂ -TiO ₂ catalyst calcined at different temperatures	62
4.27 TOC/TOC ₀ value at 360 minutes for different catalysts	62