

CHAPTER VI

Recommendations

1. Light fastness rating of modified dyed fabrics compared to those of unmodified dyed fabrics is quite low because of the effect of the modifying agent itself. To cope with this problem, cotton fabric should be modified with as low concentration of the modifying agent as possible.
2. Mechanical properties such as tear strength and elongation of modified fabrics should be investigated.
3. The improvement in dyeability of modified cotton fabric may be accomplished when mercerized cotton fabric is used in instead of unmercerized cotton fabric.