

REFERENCES

- Andrade, A. L. and Xu, P. (1997). Elastic behavior of chitosan films. Journal of Polymer Science: Part B: Polymer Physics, 35, 517-521.
- Blair, H. S., Guthrie, J., Law, T., and Turkington, P. (1987). Chitosan and modified chitosan membranes I. Preparation and characterization. Journal of Applied Polymer Science, 33, 641-656.
- Brack, H. P., Tirmizi, S. A., and Risen, W. M. (1997). Spectroscopic and viscometric study of the metal ion-induced gelation of biopolymer. Polymers, 38(10), 2351-2362.
- Chandy, T. and Sharma, C. P. (1992). Prostaglandin E1-immobilized poly(vinyl alcohol)-blended chitosan membranes: blood compatibility and permeation properties. Journal of Applied Polymer Science, 44, 2145-2156.
- Chen, J., and Minoura, N. (1994). Transport of pharmaceuticals through silk fibroin membrane. Polymers, 35(13), 2853-2856.
- Chen, X., Li, W., and Yu, T. (1997). Conformation transition of silk fibroin induced by blend chitosan. Journal of Polymer Science: Part B: Polymer Physics, 35, 2293-2296.
- Chen, X., Li, W., Zhang, W., Lu, Y., and Yu, T. (1997). pH-sensitivity and ion-sensitivity of hydrogels based on complex forming chitosan/silk fibroin interpenetrating polymer network. Journal of Applied Polymer Science, 65, 2257-2262.
- Fang, H., Han, Y., and Huang, L. (eds.) (1991). Developing collagen-chitosan composite hydrogel for contact lens application. Polymer and Biomaterials. Amsterdam: Elsevier Science.

- Freddi, G., Romano, M., Massafra, M. R., and Tsukada, M. (1995). Silk fibroin/cellulose blend films: Preparation, structure, and physical properties. Journal of Applied Polymer Science, 56, 1537-1545.
- Gillespie, R. J., Hamphreys, D. A., Baird, N. G., Robinson, E. A. (Eds.) (1989). Chemistry. Massachusetts , Prentice International, Inc.
- Gong, P., Zhang, L., and Lu, J. (1998). Synthesis and characterization of polyurethane-chitosan interpenetrating polymer networks. Journal of Applied Polymer Science, 68, 1321-1329.
- Gotoh, Y. and Tsukada, M. (1997). Physical properties and structure of poly (ethylene glycol)-silk fibroin conjugate films. Polymers, 38(2), 487-490.
- Guan, Y., Liu, X., Zhang, Y., Yao, K. (1998). Study of phase behavior on chitosan/viscose rayon blend film. Journal of Applied Polymer Science. 67, 1965-1972.
- Hasegawa, M., Isogai, A., Kuga, S., and Onabe, F. (1994). Preparation of cellulose-chitosan blend film using chloral/dimethylformamide. Polymers, 35(5), 983-987.
- Hasegawa, M., Isogai, A., Onabe, F., Usuda, M., and Atalla, R. H. (1992). Characterization of cellulose and chitosan blend films. Journal of Applied Polymer Science, 45, 1873-1879.
- Hosogawa, J., Nishiyama, M., Yoshihara, K., and Kubo, T. (1991). Biodegradable film derived from chitosan and homogenized cellulose. Ind. Eng. Chem. Res., 29(5), 800-807.
- Hugerth, A., Caren-Lelhan, N., and Sundelöf, L. (1997). The effect of charge density and conformation on the polyelectrolyte complex between carrageenan and chitosan. Carbohydrate Polymers, 34, 149-156.

- Kim, J. H., Kim, J. Y., and Lee, Y. M. (1992). Controlled release of riboflavin and insulin through crosslinked poly(vinyl alcohol)/chitosan blend membrane. Journal of Applied Polymer Science, 44, 1823-1828.
- Knorr, D. (1991). Recovery and utilization of chitin and chitosan in food processing management. Food Technology, 114-120.
- Lee, V., University Microfilm Ann Arbor 74/29, 446.
- Liang, C. X. and Hirabayashi, K. (1992). Improvements of the physical properties of fibroin membrane with sodium alginate. Journal of Applied Polymer Science, 45, 1937-1943.
- Li, J., Revol, J. F., and Marchessault, R. H. (1997). Effect of degree of deacetylation of chitin on the properties of chitin crystallites. Journal of Applied Polymer Science, 65, 373-380.
- Li, Q., Dunn, E. T., Grandmaison, E. W., and Goosen, M. F. A. (1992). Applications and properties of chitosan. Journal of Bioactive and Compatible Polymers, 7, 370-397.
- Lloyd, L. L., Kennedy, J. F., Methacanon, P., Paterson, M., and Knill, C. J. (1998). Carbohydrate polymers as wound management aids. Carbohydrate Polymers, 37, 315-322.
- Mathur, N. K., Narang, C. K. (1990). Products of chemistry. Journal of Chemical Education, 67(11), 936-942.
- Mi, F., He, N., Kuan, C., Wang, T., and Shyu, S. (1997). Chitosan tablets for controlled release of theophylline: Effect of polymer-drug wet or dry blending and anionic-cationic interpolymer complex. Journal of Applied Polymer Science, 66, 2495-2505.
- Nakatsuka, S. and Andrade, A. L. (1992). Permeability of vitamin B-12 in chitosan membranes. Effect of crosslinking and blending with poly(vinyl alcohol) on permeability. Journal of Applied Polymer Science, 44, 17-28.

- Park, T. G. and Hoffman, A. S. (1992). Synthesis and characterization of pH- and /or temperature-sensitive hydrogels. Journal of Applied Polymer Science, 46, 659-671.
- Qurashi, M. T., Blair, H. S., and Allen, S. L. (1992). Studies on modified chitosan membranes. I. Preparation and characterization. Journal of Applied Polymer Science, 46, 255-261.
- Ratto, J. A., Chen, C. C., and Blumstein, R. B. (1996). Phase behavior study of chitosan/polyamide blends. Journal of Applied Polymer Science, 59, 1451-1461.
- Remunan, C. and Bodmeier, R. (1997). Mechanical, water uptake and permeability properties of crosslinked chitosan glutamate and algenate films. Journal of Controlled Release, 44, 215-225.
- Shen, Y., Johnson, M. A., and Martin, D. C. (1998). Microstructural characterization of *bombyx mori* silk fibers. Macromolecules, 31, 8857-8864.
- Shimahara, K. and Takigashi, Y. (1988). Preparation of crustacean chitin. In Wood, W.A., and Kellogg, S.T. (eds.) (1988). Methods in enzymology volume 161. Biomass part B: Lignin, Pectin, and Chitin. New York: Academic Press.
- Suto, S. and Ui, N. (1996). Chemical crosslinking of hydroxypropyl cellulose and chitosan blends. Journal of Applied Polymer Science, 61, 2273-2278.
- Tsukada, M., Freddi, G., and Kasai, N. (1994). Physical properties and phase separation structure of *Antheraea pernyi/Bombyx mori* silk fibroin blend films. Journal of Applied Polymer Science, 32, 1175-1182.
- Tsukada, M., Goto, Y., Freddi, G., Shiozaki, H., and Ishikawa, H. (1992). Chemical modification of silk fibroin with itaconic anhydride. Journal of Applied Polymer Science, 45, 1719-1725.

- Wang, H., Li, W., Lu, W. L., and Wang, Z. (1997). Studies on chitosan and poly(acrylic acid) interpolymer complex. I. Preparation, structure, and salt sensitivity of complex-forming poly(acrylic acid):chitosan semi-interpenetrating polymer network. Journal of Applied Polymer Science. 65, 1445-1450.
- Yamaura, K., Kuranuki, N., Suzuki, M., Tanigami, T., and Matsuzawa, S. (1990). Properties of mixtures of silk fibroin/ syndiotactic-rich poly(vinyl alcohol). Journal of Applied Polymer Science, 41, 2409-2425.
- Yao, K. D., Liu, J., Cheng, G. X., Lu, X. D., and Tu, H. L. (1996). Swelling behavior of pectin/chitosan complex films. Journal of Applied Polymer Science, 60, 279-283.
- Yao, K. D., Peng, T., Feng, H. B., and He, Y. Y. (1994). Swelling kinetics and release characteristic of crosslinked chitosan: polyether polymer network (Semi-IPN) hydrogels. Journal of Polymer Science.:Part A: Polymer Chemistry, 32, 1213-1223.
- Yao, K. D., Peng, T., Goosen, M. F. A., Min, J. M., and He, Y. Y. (1993). pH-sensitivity of hydrogels based on complex forming chitosan: polyether interpenetrating polymer network. Journal of Applied Polymer Science, 48, 343-354.
- Yoshimizu, H. and Asakara, T. (1990). The structure of *Bombyx mori* silk fibroin membrane swollen by water studied with ESR, ¹³C-NMR, and FT-IR spectroscopies. Journal of Applied Polymer Science, 40, 1745-1756.

APPENDIX A

Effect of pH

Table A 1 The data of degree of swelling of blend films in pH buffer solution pH = 3.

Chitosan content (%)	Degree of swelling (%)			Average	Standard deviation
	X1	X2	X3		
0	44.16	43.75	49.23	45.71	3.05
20	635.42	616.82	616.83	623.02	10.74
40	1960.25	1899.04	1949.21	1936.17	32.62
50	dissolved	dissolved	dissolved	-	-
60	dissolved	dissolved	dissolved	-	-
80	dissolved	dissolved	dissolved	-	-
100	dissolved	dissolved	dissolved	-	-

Table A 2 The data of degree of swelling of blend films in pH buffer solution pH=4.

Chitosan content (%)	Degree of swelling (%)			Average	Standard deviation
	X1	X2	X3		
0	41.01	42.11	44.32	42.48	1.69
20	505.79	498.63	499.79	501.40	3.84
40	1567.05	1432.78	1508.91	1502.91	67.34
50	dissolved	dissolved	dissolved	-	-
60	dissolved	dissolved	dissolved	-	-
80	dissolved	dissolved	dissolved	-	-
100	dissolved	dissolved	dissolved	-	-

Table A 3 The data of degree of swelling of blend films in pH buffer solution pH = 5.

Chitosan content (%)	Degree of swelling (%)			Average	Standard deviation
	X1	X2	X3		
0	50.00	50.66	51.02	50.56	0.52
20	67.80	61.80	76.20	68.60	7.23
40	103.66	99.90	105.61	103.06	2.90
50	105.38	108.41	113.93	109.24	4.34
60	128.07	121.57	115.88	121.84	6.10
80	140.00	145.54	154.55	146.70	7.34
100	158.67	153.85	160.75	157.76	3.54

Table A 4 The data of degree of swelling of blend films in pH buffer solution pH = 6.

Chitosan content (%)	Degree of swelling (%)			Average	Standard deviation
	X1	X2	X3		
0	47.58	48.08	44.52	46.73	1.93
20	65.10	65.68	66.01	65.60	0.46
40	73.40	67.86	70.14	70.47	2.78
50	80.06	76.26	78.65	78.32	1.92
60	72.84	70.83	70.98	71.55	1.12
80	91.47	88.38	93.25	91.03	2.46
100	82.998	74.39	81.09	79.49	4.51

Table A 5 The data of degree of swelling of blend films in pH buffer solution pH = 7.

Chitosan content (%)	Degree of swelling (%)			Average	Standard deviation
	X1	X2	X3		
0	50.75	54.43	52.21	52.06	1.12
20	56.25	50.00	52.01	52.75	1.29
40	72.65	68.66	69.92	70.41	1.73
50	79.83	76.34	76.82	77.66	1.15
60	85.37	80.31	84.99	83.56	1.67
80	85.39	81.26	82.07	82.91	0.84
100	97.01	91.07	93.74	93.94	1.56

Table A 6 The data of degree of swelling of blend films in pH buffer solution pH = 8.

Chitosan content (%)	Degree of swelling (%)			Average	Standard deviation
	X1	X2	X3		
0	43.16	45.31	43.69	44.05	1.12
20	68.93	68.71	66.59	68.08	1.29
40	76.08	79.04	76.01	77.04	1.73
50	70.55	72.66	70.82	71.34	1.15
60	63.43	66.58	65.99	65.33	1.67
80	65.87	66.98	65.33	66.06	0.84
100	57.14	60.25	58.97	58.79	1.56

Table A 7 The data of degree of swelling of blend films in pH buffer solution pH = 9.

Chitosan content (%)	Degree of swelling (%)			Average	Standard deviation
	X1	X2	X3		
0	31.86	31.65	32.44	31.98	0.41
20	31.25	32.86	32.02	32.04	0.81
40	39.84	43.90	41.51	41.75	2.04
50	38.32	41.12	41.20	40.21	1.64
60	39.44	41.71	41.28	40.81	1.21
80	41.86	40.58	42.01	41.15	0.98
100	42.33	43.42	42.87	42.87	0.55

Table A 8 The data of degree of swelling of blend films in pH buffer solution pH = 11.

Chitosan content (%)	Degree of swelling (%)			Average	Standard deviation
	X1	X2	X3		
0	55.86	62.88	65.41	61.38	4.95
20	74.37	72.80	76.29	74.49	1.75
40	71.03	71.84	72.59	71.82	0.78
50	73.91	74.81	73.68	74.13	0.60
60	77.95	74.16	76.99	76.37	1.97
80	76.92	74.26	76.52	76.13	1.56
100	79.02	80.51	79.79	79.77	0.75

Table A 9 The data of degree of swelling of crosslinked blend films in pH buffer solution pH = 3.

Chitosan content (%)	Degree of swelling (%)			Average	Standard deviation
	X1	X2	X3		
0	44.16	43.75	49.23	45.71	3.05
20	376.05	380.95	390.31	382.44	7.25
40	759.85	767.76	811.83	779.81	28.01
50	742.42	761.74	780.89	761.68	19.24
60	973.96	1016.78	997.92	996.22	21.46
80	1046.67	1047.75	1131.18	1068.07	42.08
100	940.54	1090.79	1120.54	1050.62	96.49

Table A 10 The data of degree of swelling of crosslinked blend films in pH buffer solution pH = 4.

Chitosan content (%)	Degree of swelling (%)			Average	Standard deviation
	X1	X2	X3		
0	41.01	42.11	44.32	42.48	1.69
20	356.35	389.86	365.87	370.69	17.27
40	691.95	810.44	771.01	757.80	60.34
50	647.06	714.86	729.63	697.18	44.03
60	827.78	813.19	822.27	821.08	7.37
80	1711.32	1671.28	1599.71	1660.77	56.54
100	1119.28	1069.33	1200.41	1129.67	66.16

Table A 11 The data of degree of swelling of crosslinked blend films in pH buffer solution pH=5.

Chitosan content (%)	Degree of swelling (%)			Average	Standard deviation
	X1	X2	X3		
0	50.00	50.66	51.02	50.56	0.52
20	102.25	89.33	94.74	95.44	6.49
40	135.62	119.77	125.30	126.90	8.04
50	135.44	120.19	134.20	129.94	8.47
60	150.91	139.46	148.27	146.21	6.00
80	149.23	150.79	151.79	150.60	1.29
100	154.90	164.18	159.26	159.45	4.64

Table A 12 The data of degree of swelling of crosslinked blend films in pH buffer solution pH = 6.

Chitosan content (%)	Degree of swelling (%)			Average	Standard deviation
	X1	X2	X3		
0	47.58	48.08	44.52	46.73	1.93
20	66.16	65.12	67.04	66.12	0.96
40	82.91	90.87	88.53	87.44	4.09
50	100.77	105.28	102.43	102.83	2.28
60	98.52	110.89	108.78	106.06	6.62
80	113.68	110.29	109.85	111.27	2.10
100	127.54	132.52	124.48	128.18	4.06

Table A 13 The data of degree of swelling of crosslinked blend films in pH buffer solution pH = 7.

Chitosan content (%)	Degree of swelling (%)			Average	Standard deviation
	X1	X2	X3		
0	50.75	54.43	52.21	52.46	1.85
20	62.23	75.00	68.58	68.60	6.39
40	76.74	81.82	79.93	79.50	2.57
50	87.01	88.52	89.69	88.41	1.34
60	81.91	77.97	78.55	79.48	2.13
80	83.87	90.51	88.47	87.62	3.40
100	87.04	81.48	89.26	85.93	4.01

Table A 14 The data of degree of swelling of crosslinked blend films in pH buffer solution pH = 8.

Chitosan content (%)	Degree of swelling (%)			Average	Standard deviation
	X1	X2	X3		
0	43.16	45.31	43.69	44.05	1.12
20	74.65	75.12	75.48	75.08	0.42
40	72.99	74.98	75.96	74.64	1.51
50	73.51	72.01	70.89	72.14	1.31
60	73.48	73.59	74.24	73.77	0.41
80	69.74	74.82	73.26	72.61	2.60
100	61.36	68.59	69.58	66.51	4.49

Table A 15 The data of degree of swelling of crosslinked blend films in pH buffer solution pH = 9.

Chitsan content (%)	Degree of swelling (%)			Average	Standard deviation
	X1	X2	X3		
0	31.86	31.65	32.44	31.98	0.41
20	44.07	36.76	43.57	41.47	4.08
40	43.04	43.84	43.02	43.30	0.47
50	47.22	44.54	44.58	45.45	1.54
60	53.13	56.76	54.27	54.72	1.86
80	48.28	47.44	46.59	47.44	0.85
100	45.58	41.58	44.05	43.74	2.02

Table A 16 The data of degree of swelling of crosslinked blend films in pH buffer solution pH = 11.

Chitosan content (%)	Degree of swelling (%)			Average	Standard deviation
	X1	X2	X3		
0	55.86	62.88	65.41	61.38	4.95
20	86.31	85.69	86.97	86.32	0.64
40	70.34	79.58	80.24	76.72	5.54
50	68.75	76.52	72.51	72.59	3.89
60	76.62	75.82	80.09	77.51	2.27
80	74.56	78.92	75.37	76.28	2.32
100	81.91	79.56	80.07	80.51	1.24

APPENDIX B

Effect of salt type

Table B 1 The data of degree of swelling of blend films in 0.25 M LiCl solution.

Chitosan content (%)	Degree of swelling (%)			Average	Standard deviation
	X1	X2	X3		
0	50.60	47.14	44.26	47.33	3.17
20	50.57	41.84	49.46	47.29	4.75
40	61.95	55.88	62.35	60.06	3.63
50	52.09	57.75	53.38	54.41	2.97
60	61.14	78.91	79.43	73.16	10.41
80	93.69	78.81	65.98	79.49	13.87
100	63.49	67.61	65.31	65.47	2.06

Table B 2 The data of degree of swelling of crosslinked blend films in 0.25 M NaCl solution.

Chitosan content (%)	Degree of swelling (%)			Average	Standard deviation
	X1	X2	X3		
0	38.12	36.52	38.24	37.63	0.96
20	47.29	50.89	46.27	48.15	2.43
40	62.15	63.29	62.28	62.57	0.62
50	64.92	65.71	60.99	63.87	2.53
60	79.17	80.24	79.05	79.49	0.66
80	83.75	80.63	83.86	82.75	1.83
100	65.55	70.51	68.84	68.30	2.52

Table B 3 The data of degree of swelling of blend films in 0.25 M CaCl₂ solution.

Chitosan content (%)	Degree of swelling (%)			Average	Standard deviation
	X1	X2	X3		
0	38.62	34.44	36.52	36.53	2.09
20	54.32	56.11	53.25	54.56	1.45
40	63.96	63.28	65.77	64.34	1.29
50	71.54	73.19	73.27	68.50	4.68
60	70.59	73.58	72.01	72.06	1.50
80	66.67	68.29	69.08	68.01	1.23
100	83.75	87.32	88.23	86.43	2.37

Table B 4 The data of degree of swelling of blend films in 0.25 M AlCl₃ solution.

Chitosan content (%)	Degree of swelling (%)			Average	Standard deviation
	X1	X2	X3		
0	43.62	38.84	43.62	42.03	2.76
20	200.83	199.57	210.39	203.60	5.92
40	435.06	480.83	458.21	458.03	22.89
50	696.40	691.8	725.14	704.45	18.07
60	-	-	-	-	-
80	-	-	-	-	-
100	-	-	-	-	-

Table B 5 The data of degree of swelling of blend films in 0.25 M FeCl₃ solution.

Chitosan content (%)	Degree of swelling (%)			Average	Standard deviation
	X1	X2	X3		
0	37.27	32.08	34.02	34.68	3.67
20	150.23	148.32	143.36	147.30	3.55
40	370.69	395.20	371.24	379.04	19.99
50	690.85	701.25	679.58	690.56	10.84
60	-	-	-	-	-
80	-	-	-	-	-
100	-	-	-	-	-

Table B 6 The data of degree of swelling of crosslinked blend films in 0.25 M LiCl solution.

Chitosan content (%)	Degree of swelling (%)			Average	Standard deviation
	X1	X2	X3		
0	50.60	40.14	44.26	45.00	5.27
20	66.13	70.22	74.31	70.22	4.09
40	65.06	68.33	70.37	67.92	2.68
50	69.70	75.00	72.09	72.22	2.17
60	86.24	88.64	87.50	87.46	1.20
80	81.25	91.55	93.90	88.90	6.73
100	76.56	81.19	79.25	79.00	2.33

Table B 7 The data of degree of swelling of crosslinked blend films in 0.25 M NaCl solution.

Chitosan content (%)	Degree of swelling (%)			Average	Standard deviation
	X1	X2	X3		
0	38.52	37.25	39.41	38.39	1.09
20	69.50	68.86	64.83	67.73	2.53
40	75.90	74.51	76.25	75.55	0.92
50	74.55	74.23	75.36	74.71	0.58
60	76.63	78.59	77.52	77.58	0.98
80	68.75	72.14	73.19	71.36	2.32
100	71.697	73.26	73.95	72.97	1.16

Table B 8 The data of degree of swelling of crosslinked blend films in 0.25M CaCl₂ solution.

Chitosan content (%)	Degree of swelling (%)			Average	Standard deviation
	X1	X2	X3		
0	38.51	34.52	37.74	36.92	2.12
20	54.12	55.69	53.35	54.39	1.19
40	63.96	60.28	59.67	61.30	2.32
50	71.54	68.52	70.24	70.10	1.51
60	70.59	73.98	70.99	71.85	1.85
80	66.67	70.28	69.64	68.86	1.93
100	83.75	80.32	79.65	81.24	2.20

Table 9 The data of degree of swelling of crosslinked blend films in 0.25 M AlCl₃ solution.

Chitosan content (%)	Degree of swelling (%)			Average	Standard deviation
	X1	X2	X3		
0	43.62	38.84	43.62	42.03	2.76
20	196.23	193.05	190.83	193.37	2.71
40	333.15	299.38	286.48	306.34	24.10
50	398.73	372.00	351.38	374.04	23.74
60	370.09	406.79	394.94	390.61	18.73
80	597.72	565.04	566.67	576.48	18.42
100	402.63	416.41	429.29	416.11	13.33

Table B 10 The data of degree of swelling of crosslinked blend films in 0.25 M FeCl_3 solution.

Chitosan content (%)	Degree of swelling (%)			Average	Standard deviation
	X1	X2	X3		
0	37.27	32.08	34.02	34.46	2.62
20	116.55	115.23	115.94	115.91	0.66
40	236.51	240.29	239.58	238.79	2.01
50	284.21	288.38	288.78	287.12	2.53
60	440.66	451.21	444.47	445.45	5.34
80	490.28	500.25	495.57	495.37	4.99
100	450.19	461.27	455.53	455.66	5.54

APPENDIX C

Effect of AlCl₃ concentration

Table C 1 The data of degree of swelling of crosslinked blend films in 0.5 M AlCl₃ solution.

Chitosan content (%)	Degree of swelling (%)			Average	Standard deviation
	X1	X2	X3		
0	34.52	34.06	34.20	34.29	0.0325
20	131.19	128.57	130.36	130.04	1.34
40	139.53	133.73	134.92	136.06	3.06
50	165.48	151.69	164.04	160.40	7.58
60	158.33	148.89	151.52	152.91	4.87
80	187.10	187.72	192.73	189.18	3.09
100	181.03	179.75	166.67	175.82	7.95

Table C 2 The data of degree of swelling of crosslinked blend films in 0.25 M AlCl₃ solution.

Chitosan content (%)	Degree of swelling (%)			Average	Standard deviation
	X1	X2	X3		
0	43.62	38.84	43.62	42.03	2.76
20	196.23	193.05	190.83	193.37	2.71
40	333.15	299.38	286.48	306.34	24.10
50	398.73	372.00	351.38	374.04	23.74
60	370.09	406.79	394.94	390.61	18.73
80	597.72	565.04	566.67	576.48	18.42
100	402.63	416.41	429.29	416.11	13.33

Table C 3 The data of degree of swelling of crosslinked blend films in 0.1 M AlCl₃ solution.

Chitosan content (%)	Degree of swelling (%)			Average	Standard deviation
	X1	X2	X3		
0	35.85	37.31	37.10	36.75	0.79
20	300.00	270.08	286.90	285.66	14.99
40	492.86	485.00	487.37	488.41	4.03
50	590.10	529.76	529.03	549.63	35.05
60	547.22	529.75	514.74	530.57	16.25
80	678.57	649.23	621.52	649.77	28.53
100	819.35	811.43	842.57	824.45	16.18

Table C 4 The data of degree of swelling of crosslinked blend films in 0.01 M AlCl₃ solution.

Chitosan content (%)	Degree of swelling (%)			Average	Standard deviation
	X1	X2	X3		
0	35.62	36.36	37.93	36.64	1.18
20	291.21	298.72	283.67	291.20	7.53
40	716.81	661.90	647.62	675.44	36.53
50	877.5	820.00	887.04	861.51	36.27
60	854.90	847.25	858.06	853.40	5.56
80	1364.86	1300.00	1485.53	1383.46	94.15
100	804.76	813.91	861.22	826.63	30.30

Table C 5 The data of degree of swelling of crosslinked blend films in 0.001 M AlCl₃ solution.

Chitosan content (%)	Degree of swelling (%)			Average	Standard deviation
	X1	X2	X3		
0	32.67	34.72	38.01	35.13	2.69
20	187.37	214.58	191.94	197.96	14.57
40	271.43	305.56	327.14	301.38	28.09
50	626.32	578.65	588.54	597.84	25.16
60	462.50	592.41	553.77	536.23	66.71
80	565.75	518.31	569.86	551.31	28.65
100	510.33	514.29	501.43	508.68	6.59

Table C 6 The data of degree of swelling of crosslinked blend films in 0.0001M AlCl₃ solution.

Chitosan content (%)	Degree of swelling (%)			Average	Standard deviation
	X1	X2	X3		
0	36.36	37.41	35.94	36.57	0.76
20	71.92	92.59	78.26	80.92	10.59
40	62.69	92.17	94.17	83.01	17.62
50	76.60	72.17	79.17	75.98	3.54
60	101.49	100.00	87.14	96.21	7.89
80	108.97	115.19	115.67	113.28	3.74
100	95.56	86.76	98.57	93.63	6.14

APPNDIX D

Effect of FeCl₃ concentration

Table D 1 The data of degree of swelling of crosslinked blend films in 0.5 M FeCl₃ solution.

Chitosan content (%)	Degree of swelling (%)			Average	Standard deviation
	X1	X2	X3		
0	42.42	40.74	33.33	38.83	4.84
20	62.02	62.02	68.47	64.17	3.72
40	111.29	107.09	124.10	114.16	8.86
50	128.32	111.63	113.04	117.66	9.26
60	147.79	147.06	151.75	148.87	2.52
80	194.79	177.55	189.02	187.12	8.78
100	217.57	215.00	207.25	213.27	5.37

Table D 2 The data of degree of swelling of crosslinked blend films in 0.25 M FeCl₃ solution.

Chitosan content (%)	Degree of swelling (%)			Average	Standard deviation
	X1	X2	X3		
0	37.27	32.08	34.02	34.46	2.62
20	116.55	115.23	115.94	115.91	0.66
40	236.51	240.29	239.58	238.79	2.01
50	284.21	288.38	288.78	287.12	2.53
60	440.66	451.21	444.47	445.45	5.34
80	490.28	500.25	495.57	495.37	4.99
100	450.19	461.27	455.53	455.66	5.54

Table D 3 The data of degree of swelling of crosslinked blend films in 0.1 M FeCl₃ solution.

Chitosan content (%)	Degree of swelling (%)			Average	Standard deviation
	X1	X2	X3		
0	35.59	39.31	39.67	38.19	2.26
20	216.57	187.38	197.26	200.40	14.85
40	343.68	340.0	359.02	347.57	10.09
50	442.03	430.43	444.30	438.92	7.44
60	721.05	681.12	663.33	688.50	29.56
80	980.95	887.30	948.44	938.90	47.55
100	585.71	579.52	596.51	587.25	8.60

Table D 4 The data of degree of swelling of crosslinked blend films in 0.01 M FeCl₃ solution.

Chitosan content (%)	Degree of swelling (%)			Average	Standard deviation
	X1	X2	X3		
0	35.94	32.61	34.65	34.40	1.68
20	156.25	153.85	150.00	153.37	3.15
40	727.97	742.34	762.50	744.27	17.35
50	748.68	711.94	828.33	762.98	59.50
60	928.89	1063.25	1069.83	1020.66	79.54
80	1639.71	1689.33	1730.08	1686.37	45.26
100	859.72	872.22	804.61	845.52	35.97

Table D 5 The data of degree of swelling of crosslinked blend films in 0.001 M FeCl₃ solution.

Chitosan content (%)	Degree of swelling (%)			Average	Standard deviation
	X1	X2	X3		
0	38.46	38.30	42.67	39.81	2.48
20	153.06	155.65	136.91	148.54	10.15
40	578.52	578.17	564.29	573.66	8.12
50	674.38	657.38	619.74	650.50	27.96
60	824.46	895.56	872.22	864.08	36.24
80	1170.67	1112.20	1272.22	1185.03	80.97
100	689.29	635.84	628.04	651.06	33.34

Table D 6 The data of degree of swelling of crosslinked blend films in 0.0001 M FeCl₃ solution.

Chitosan content (%)	Degree of swelling (%)			Average	Standard deviation
	X1	X2	X3		
0	37.21	38.00	37.36	37.52	0.42
20	54.37	56.45	52.59	54.47	1.93
40	72.22	72.79	74.67	73.23	1.28
50	92.12	87.67	90.91	90.23	2.30
60	104.82	106.47	106.90	106.06	1.10
80	113.51	114.06	110.61	112.73	1.85
100	103.45	111.11	109.76	108.11	4.09

CURRICULUM VITAE

Name: Jantip Suesat
Date of Birth: 29th of November, 1976
Nationality: Thai
University Education:
1994-1998 Bachelor degree of Science in Petrochemicals and
Polymeric Materials,
Silpakorn University,
Nakorn Pathom
Thailand