

REFERENCES

- Abu-Z.M., Rudra, R.P., and Dickinson, W.T. (2003). Effect of application of surfactants on hydraulic of soils. Biosystem Engineering, 84(3), 363-372.
- Ana M.G., Anita T. and Tanja P. (2005). Electro properties of textile fabrics. Coloration Technology, 121, 221-227.
- Andrew J. Milling. (1999). Surface Characterization Method Principles, Techniques and Applications. New York: Marcel Dekker, Inc.
- Barbara Simončič and Veronika Rozman. (2007). Colloids and Surfaces A: Physicochem. Eng. Aspects, 292, 236–245.
- Ashish Batra, Santanu Paria, C. Manohar, and Kartic C. Khilar. (2001). Removal of Surface Adhered Particles by Surfactants and Fluid Motions. AIChE Journal, 47, No. 11, 2557–2565.
- Chunhee Kim and You-Lo Hsieh. (2001). Wetting and absorbency of nonionic surfactant solutions on cotton fabrics. Colloids and Surfaces A: Physicochemical and Engineering Aspects, 187–188, 385–397.
- Cipriano, B.H., Raghavan, S.R., and McGuigan, P.M. (2005). Surface tension and contact angle measurements of a hexadecyl imidazolium surfactant adsorbed on a clay surface. Colloids and Surfaces, 262, 8-13.
- Cutler, W.G. (1987). Detergency Theory and Technology. New York: Marcel Dekker.
- Drew Myers. (1999). Surfaces, Interfaces, and Colloids: Principles and Applications. New York: John Wiley & Sons, Inc.
- Ernest W. Flick. (1993). Industrial surfactants. New Jersey: Noyes Publications.
- Floyd E. Friedli. (Eds.). (2001). Detergency of Specialty Surfactants. New York: Marcel Dekker, Inc.
- Fuangswasdia, A., Krajangpana, S. and Sabatinib,Coutinho, D.A. (2007). Effect of admicellar properties on adsolubilization: Column studies and solute transport. Water Research, 41, 1343 – 1349.
- Fytianos, K., Voudrias, E., and Papamichali, A. (1998). Behavior and fate of linear alkylbenzene sulfonate in different soils. Chemosphere, 36 (13), 2741-2746.

- Gallardo-Moreno, A.M., González-García, C.M., and González-Martínez, M.L. (2004). Arrangement of SDS adsorbed layer on carbonaceous particles by zeta potential determinations. *Colloids and Surfaces*, 249, 57–62.
- González-García, C. M., González-Martínez, M. L., Gallardo-Moreno A. M., (2002). Free Energy of Interaction of Sodium Dodecyl sulfate in aqueous solution with carbon black surfaces. *Journal of Colloid and Interface Science* 248, 13–18.
- González-García, C. M., González-Martínez, M. L., Gallardo-Moreno A. M. (2005). Adsorption enthalpies of sodium dodecyl sulphate onto carbon blacks in the low concentration range. *Carbon*, 43, 567–572.
- Guy Broze. (1999). *Hand book of Surfactants Part A: Properties*. New York: Marcel Dekker, Inc.
- H. Yıldırım Erbil. (2006). *Surface Chemistry Of Solid and Liquid Interfaces*. Oxford: Blackwell Publishing Ltd.
- Hansjoachim Stechemesser and Bohulav Dobiás. (2005). *Coagulation and Flocculation*. New York: CRC Press Taylor & Francis Group.
- HERA. (Organization.). (2007). *Human & Environmental Risk Assessment on ingredients of European household cleaning products :Alcohol Ethoxylates*. Brussels: HERA Secretariat.
- Hoeft,C.E., and Zollars, R.L. (1996). Adsorption of single anionic Surfactants on hydrophobic surfaces. *Journal of Colloid and Interface Science*, 177, 171–178.
- Ivan Gitsov. (2002). *Nonionic Surfactants: GPC–SEC Analysis*. New York: Marcel Dekker, Inc.
- J. W. Goodwin. (2004). *Colloids and Interfaces with Surfactants and Polymers – An Introduction*. West Sussex: John Wiley & Sons Ltd.
- Jaehyeon P. and John R.R. (1995). A simple accurate determination of oxide PZC and the strong buffering effect of oxides surface at incipient wetness. *Colloid and Interface Science*, 175, 239–252.
- Jakobi, G. and Lohr, A. (1987). *Detergents and Textile Washing*. Germany: VCH Verlagsgesellschaft.

- K. Dao, A. Bee, and C. Treiner. (1998). Adsorption Isotherm of Sodium Octylbenzenesulfonate on Iron Oxide Particles in Aqueous Solutions. Journal of Colloid and Interface Science, 204, 61–65.
- K.S. Birdi. (Eds.). (2002). Handbook of surface and colloid chemistry. New York: CRC Press LLC.
- Kaya, A., and Yukselen, Y. (2005). Zeta potential of soils with surfactants and its relevance to electrokinetic remediation. Journal of Hazardous Materials, B120, 119–126.
- Kaufmann, T.C., Engel, A., and Remigy, H. (2006). A Novel Method for Detergent Concentration Determination. Biophysical Journal, 90, 310–317.
- Keith Hovda. (2007). The Challenge of Methyl Ester Sulfonation. Seattle: The Chemithon Corporation Chemithon Surface Finishing, Inc.
- Krister Holmberg. (Eds.) (2002). Handbook of applied surface and colloid chemistry. West Sussex: John Wiley & Sons Ltd.
- Krister Holmberg, Bo Jönsson, Bengt Kronberg and Björn Lindman. (2002). Surfactants and Polymers in Aqueous Solution. West Sussex: John Wiley & Sons Ltd.
- Kun Yang , Lizhong Zhu and Baowei Zhao. (2005). Minimizing losses of nonionic and anionic surfactants to a montmorillonite saturated with calcium using their mixtures. Journal of Colloid and Interface Science, 291, 59–66.
- Kun Yang, Lizhong Zhu and Baoshan Xing. (2006). Sorption of sodium dodecylbenzene sulfonate by montmorillonite. Environmental Pollution, 145, 571–576.
- Kunio Esumi. (2001). Interactions between Surfactants and Particles: Dispersion, Surface Modification, and Adsolubilization. Journal of Colloid and Interface Science, 241, 1–17.
- L. Fras-Zemljic P. Stenius, J. Laine and K. Stana-Kleinschek. (2006). The effect of adsorbed carboxymethyl cellulose on the cotton fibre adsorption capacity for surfactant. Cellulose, 13,655–663.
- Lang, K.R. (1994). Detergents and Cleaners. New York: Handser/Gardner.
- Laurier L. Schramm. (2005). Emulsions, Foams, and Suspensions: Fundamentals and Applications. Weinheim: WILEY-VCH Verlag GmbH & Co.

- Lee, D., Cody, R., and Kima, D. (2002). Effect of soil texture on surfactant-based remediation of hydrophobic organic-contaminated soil. Environment International, 27, 681-688.
- M.S. Rodriguez-Cruz, M.J. Sanchez-Martin and M. Sanchez-Camazano. (2005). A comparative study of adsorption of an anionic and a non-ionic surfactant by soils based on physicochemical and mineralogical properties of soils. Chemosphere, 65, 56–64.
- Martin J. Schick. (1987). Nonionic surfactants. New York: Marcel Dekker, Inc.
- Masliyah, Jacob H. and Bhattacharjee, Subir. (2006). Electrokinetic and Colloid Transport Phenomena. New Jersey: John Wiley & Sons, Inc.
- Michiko Nakamura and Yusuko Wakamatu. (1970). Studies of Detergency on Various Fabrics Soiled by Ferric Oxide. Bull. Kagoshima Pref. Jr. College, 21, 1–8.
- Milton J. Rosen. (2004). Surfactants and interfacial phenomena. New Jersey: John Wiley & Sons, Inc.
- Miyuki Akase, Teruo Tsunoda and Yuji Yoneyama. (2003). Detergency of Soil Particles Part3 : Comparision of Reflectance and X-ray fluorescence Method for Detergency Evaluation. Journal of Oleo Science, 52, 255–260.
- Myers, Drew. (2006). Surfactant science and technology. New Jersey: John Wiley & Sons, Inc.
- Orhan Özdemir, Mustafa Çınar, Eyüp Sabah, Fatma Arslan and Mehmet Sabri Çelik. (2007). Adsorption of anionic surfactants onto sepiolite. Journal of Hazardous Materials, 147, 625–632.
- Ou, Z., Yediler, A., He, Y., and Sun, T. (1996). Adsorption of linear alkylbenzene sulfonate (LAS) on soils. Chemosphere, 32 (5), 827-839.
- Pinhua Rao and Ming He. (2006). Adsorption of anionic and nonionic surfactant mixtures from synthetic detergents on soils. Chemosphere 63, 1214–1221.
- Richard M. Pashley and Marilyn E. Karaman. (2004). Applied Colloid and Surface Chemistry. West Sussex: John Wiley & Sons Ltd.
- Rodriguez-Cruz, M.S., Sanchez-Martin, M.J, and Sanchez-Camazano, M. (2005). A comparative study of adsorption of an anionic and a non-ionic surfactant by

- soils based on physicochemical and mineralogical properties of soils. *Chemosphere*, 61, 56–64.
- Roosmalen, M.J.E., Woerlee G.F., and Witkamp, G.J. (2004). Surfactants for particulate soil removal in dry-cleaning with high-pressure carbon dioxide. *J. of Supercritical Fluids*, 30, 97–109.
- Santanu Paria, C. Manohar and Kartic C. Khilar. (2003). Experimental Studies on Adsorption of surfactant onto cellulosic Surface and Its Relevance to Detergency. *Journal of The Institution of Engineers, Singapore*, 43, No. 2, 34–44.
- Santanu Paria, C. Manohar and Kartic C. Khilar. (2004). Effect of cationic surfactant on the adsorption characteristics of anionic surfactant on cellulose surface. *Colloids and Surfaces A: Physicochem. Eng. Aspects*, 232, 139–142.
- Santanu Paria and Kartic C. Khilar. (2004). A review on experimental studies of surfactant adsorption at the hydrophilic solid–water interface. *Advances in Colloid and Interface Science*, 110, 75– 95.
- Santanu Paria, C. Manohar and Kartic C. Khilar. (2005). Adsorption of anionic and non-ionic surfactants on a cellulosic surface. *Colloids and Surfaces A: Physicochem. Eng. Aspects*, 252, 221–229.
- Santanu Paria and Pak K. Yuet. (2007). Adsorption of Non-ionic Surfactants onto Sand and Its Importance in Naphthalene Removal. *Ind. Eng. Chem. Res.*, 46, 108-113.
- Santanu Paria. (2007). Surfactant-Enhanced Remediation of Organic Contaminated Soil and Water. *Accepted in Advances in Colloid and Interface Science*.
- Satish K. Goel. (2000). Phase Behavior and Detergency Study of Lauryl Alcohol Ethoxylates with High Ethylene Oxide Content. *Journal of Surfactants and Detergents*. 3, No. 2, 221–227.
- Sawicki, G.C. (2005). Impact of surfactant composition and surfactant structure on foam control performance. *Colloids and Surfaces*, 263, 226–232.

- Simončič, B., and Rozman, V. (2007). Wettability of cotton fabric by aqueous solutions of surfactants with different structures. Colloids and Surfaces, 292, 236–245.
- Srdjan M. Bulatovic. (2007). Handbook of Flotation Reagents Chemistry, Theory and Practice: Flotation of Sulfide Ores. Holland: Elsevier Science & Technology Books.
- Teruhisa Satsuki, Kenji Umehara and Yuji Yoneyama. (1992). Performance and Physicochemical Properties of α-Sulfo Fatty Acid Methyl Esters. Journal of Oleo Science, 69, 672–677.
- Tharwat F. Tadros. (2005). Applied Surfactants. Mörlenbach: WILEY-VCH Verlag GmbH & Co.
- Thomas M. Schmitt. (2001). Analysis of Surfactants. New York: Marcel Dekker, Inc.
- Wen Huei Lim and Salmiah Ahmad. (2002). Dishwashing Performance of Mixed Palm Stearin Sulfonated Methyl Esters and Polyoxyethylene Sorbitan Esters. Journal of Surfactants and Detergents, 5, 33–38.
- Wen Huei Lim and Salmiah Ahmad. (2004). Dishwashing Performance of Mixed Palm Stearin Sulfonated Methyl Esters—Nonylphenol Ethoxylate Alcohol. Journal of Surfactants and Detergents, 7, 53–58.
- Yusuke Ishikawa, Shintaro Orito and Masaru Oya. (2007). Statistical analysis of washing Efficiency for solid Particle Soil. Journal of Oleo Science, 56, 163–168.
- Zulina Abd Maurad, Razmah Ghazali, Parthiban Siwayanan, Zahariah Ismail, and Salmiah Ahmad. (2006). Alpha-Sulfonated Methyl Ester as an Active Ingredient in Palm-Based Powder Detergents. Journal of Surfactants and Detergents, 9, 161–167.

APPENDICES

Appendix A Zeta Potential Experiment

Zeta Potential Measurement

An amount of 1.5 mg of ferric oxide powder or 0.1 mg of fabric was added into a surfactant solution having different pH value and then the mixture was stirred at 30°C for 24 hours. The solution was then transferred to an electrophoretic cell of a zeta meter (Zeta Meter 3.0+ unit) equipped with a microscope module. After applying a suitable voltage according to the solution conductivity, the average zeta potential value of ferric oxide was obtained.

Table A1 Data for zeta potential measurement of ferric oxide at pH 5 and variable MES at 30°C. Weight of ferric oxide = 1.5 mg.

MES Concentration (%w/v)	0.002	0.005	0.008	0.011	0.014	0.017	0.02	0.05	0.075	
Zeta potential (-mV)	1	20.5	33.1	35.0	40.0	45.1	44.2	45.2	46.2	46.3
2	20.5	30.1	38.0	39.0	40.0	44.3	45.3	47.3	44.1	
3	20.5	30.2	36.0	38.0	41.2	44.2	45.2	46.2	41.7	
4	25.0	30.5	40.0	39.0	42.4	44.2	45.2	46.2	46.7	
5	23.0	29.5	37.5	38.0	40.0	45.0	46.0	45.0	40.4	
6	21.0	28.0	37.0	38.0	40.0	42.2	43.0	44.0	44.4	
7	24.5	20.0	33.5	39.0	40.0	43.6	44.7	45.1	49.2	
8	25.8	30.0	35.3	37.5	41.2	43.7	44.6	45.0	46.0	
9	15.0	31.2	35.5	39.5	41.7	44.0	44.0	45.0	46.3	
10	28.9	31.1	35.9	39.8	41.5	48.5	48.0	47.9	45.2	
11	30.0	32.0	35.9	40.1	41.9	53.0	60.0	61.1	45.7	
12	20.0	40.0	35.0	40.5	42.6	48.9	49.0	50.1	46.7	
13	20.0	29.7	35.1	40.0	42.0	48.7	49.0	50.0	43.4	
14	22.0	27.8	35.3	30.0	43.0	44.2	45.2	47.0	50.4	
15	23.5	40.5	35.5	39.4	41.0	42.2	43.2	43.0	45.0	
16	25.0	30.1	35.5	39.7	39.0	43.7	44.1	45.0	45.1	
17	25.0	30.6	34.0	39.7	40.0	53.0	52.0	53.0	40.7	
18	29.0	30.5	34.0	40.5	41.0	52.0	53.1	53.0	53.3	
19	29.0	30.3	33.0	40.5	40.0	51.4	52.4	53.0	49.9	
20	24.0	30.5	33.0	40.7	39.0	51.7	52.4	53.0	47.5	
21	22.0	29.5	33.0	40.3	40.0	53.0	54.5	53.0	49.8	
22	22.0	29.5	32.0	30.4	40.0	48.0	50.0	53.0	42.2	
23	24.0	29.8	35.0	40.4	42.1	47.0	48.0	49.7	48.0	
24	20.0	30.0	31.0	20.0	41.5	48.9	49.9	49.5	49.4	
25	24.0	30.5	31.0	30.0	38.0	42.0	45.0	49.7	50.7	
Average zeta potential (-mV)	23.37	30.60	34.88	37.60	40.97	46.86	47.96	48.84	46.32	

Table A1 (Continue)

MES Concentration (%w/v)	0.1	0.12	0.14	0.16	0.18	0.2	0.25	0.3	0.4	
Zeta potential (-mV)	1	52.0	60.2	66.6	53.8	61.3	59.0	63.9	69.4	79.0
2	55.0	55.3	79.8	82.0	94.0	84.0	67.2	77.4	77.8	
3	40.3	47.7	65.8	97.0	68.7	68.0	66.0	66.6	79.1	
4	47.5	61.0	61.1	88.0	78.4	69.0	60.0	68.9	79.7	
5	58.0	61.0	73.0	49.4	79.6	58.0	60.0	66.7	79.9	
6	58.0	66.0	58.1	56.8	76.3	66.0	68.7	65.0	78.6	
7	49.1	63.7	53.3	90.0	76.0	69.0	67.9	69.0	67.7	
8	46.9	65.0	62.1	82.0	63.4	48.0	63.9	67.4	66.3	
9	59.0	66.0	53.8	70.7	76.8	69.7	65.7	73.2	70.0	
10	56.0	71.7	70.3	67.7	54.3	56.7	57.8	70.0	70.0	
11	56.1	60.3	52.6	93.0	60.0	67.7	68.9	60.0	60.0	
12	50.1	46.0	55.2	69.9	55.2	54.4	70.0	63.5	70.0	
13	48.6	41.0	50.9	74.9	58.5	58.1	63.4	75.8	75.5	
14	48.5	41.6	63.5	69.0	76.5	70.1	55.2	80.0	75.7	
15	45.3	55.3	56.6	60.2	63.4	79.0	76.5	75.8	76.7	
16	48.2	65.2	45.0	76.1	55.2	68.6	74.2	63.5	63.5	
17	44.2	44.5	65.4	85.0	55.8	68.5	74.2	73.2	60.0	
18	48.6	48.1	47.7	80.0	78.4	70.1	58.5	60.8	60.0	
19	44.6	47.3	59.7	75.6	60.0	55.0	63.4	60.2	89.0	
20	44.2	48.1	61.9	74.4	61.2	89.0	76.5	60.1	60.0	
21	48.6	48.1	62.1	78.7	76.5	79.0	76.5	79.9	65.1	
22	44.5	47.3	60.8	57.3	74.2	78.1	67.9	80.0	64.3	
23	43.5	42.8	73.5	74.1	74.2	77.7	73.0	84.0	67.1	
24	48.2	48.1	52.3	73.3	54.3	60.0	79.0	77.0	71.1	
25	41.5	48.1	47.9	58.8	58.5	60.0	70.0	67.0	67.0	
Averagenzeta potential (-mV)	49.06	53.98	59.96	73.51	67.63	67.31	67.53	70.18	70.92	

Table A2 Data for zeta potential measurement of ferric oxide at pH 7 and variable MES at 30°C. Weight of ferric oxide = 1.5 mg.

MES Concentration (%w/v)	0.002	0.005	0.008	0.011	0.014	0.017	0.02	0.05	0.075	
Zeta potential (-mV)	1	32.7	57.0	47.0	48.9	41.0	66.0	50.1	54.5	70.0
	2	38.9	40.8	47.1	49.0	45.4	70.0	52.3	57.5	55.3
	3	44.5	57.0	47.3	47.6	64.0	79.0	51.0	57.4	53.1
	4	28.5	57.0	45.2	48.6	61.0	58.0	51.0	55.6	55.8
	5	39.7	66.0	46.8	68.1	56.4	46.1	53.4	54.7	54.1
	6	44.5	35.0	46.7	46.9	51.0	45.2	54.5	58.6	54.6
	7	37.0	46.7	49.0	49.7	59.0	46.1	51.5	55.6	56.1
	8	38.8	46.6	60.0	46.7	59.8	49.6	52.7	58.2	52.6
	9	42.3	57.0	40.0	40.0	52.3	51.0	57.2	57.4	51.5
	10	41.0	50.0	45.1	49.6	51.0	50.0	57.5	59.3	50.4
	11	43.9	35.0	45.5	49.6	62.0	48.9	57.1	58.4	57.1
	12	43.6	44.0	46.8	49.7	52.8	49.4	55.5	60.0	60.0
	13	37.0	44.1	47.3	48.9	51.3	46.1	53.2	70.0	60.0
	14	38.8	43.0	47.3	44.6	58.5	47.0	54.5	40.0	63.9
	15	42.2	40.3	47.3	50.0	58.4	47.4	55.5	80.0	57.0
	16	41.0	40.9	47.3	47.4	57.0	46.0	52.5	59.7	53.0
	17	43.9	50.0	50.3	47.6	56.0	48.7	51.5	57.7	59.0
	18	44.0	40.9	49.1	48.1	56.5	48.9	51.0	55.1	54.0
	19	43.6	47.0	42.2	46.4	53.8	68.0	51.0	44.3	57.0
	20	37.0	48.0	60.0	49.0	40.0	46.0	59.0	69.7	55.0
	21	38.7	44.7	48.0	60.0	41.0	49.0	50.0	69.9	60.0
	22	44.5	44.7	46.6	45.1	50.2	46.1	50.0	49.9	60.0
	23	32.7	35.9	47.3	44.3	52.3	49.0	52.0	60.0	62.0
	24	38.9	45.0	46.4	42.2	56.4	59.0	52.0	50.0	59.6
	25	32.8	45.7	45.3	47.6	51.0	49.0	54.7	57.0	59.6
Average zeta potential (-mV)	39.62	46.49	47.64	48.62	53.52	52.38	53.23	58.02	57.23	

Table A2 (Continue).

MES Concentration (%w/v)	0.1	0.12	0.14	0.16	0.18	0.2	0.25	0.3	0.4	
Zeta potential (-mV)	1	60.0	52.3	89.0	67.4	69.7	78.9	70.4	85.0	80.0
2	58.0	56.6	76.8	68.0	73.8	69.0	73.0	87.0	79.0	
3	58.0	49.8	85.0	76.1	62.1	65.0	80.0	87.0	78.7	
4	79.0	44.7	80.0	61.7	73.3	60.0	65.6	81.0	79.5	
5	57.0	97.0	84.0	87.0	66.8	67.0	60.3	74.7	79.7	
6	77.0	84.0	61.7	76.8	65.0	78.0	70.0	76.6	58.4	
7	68.6	66.6	67.5	87.0	69.0	75.0	76.0	75.9	69.0	
8	54.0	65.4	71.9	80.0	69.0	74.0	60.0	60.0	70.0	
9	55.7	61.0	66.4	85.0	68.0	75.0	67.2	75.8	71.0	
10	45.3	58.0	90.0	69.3	67.9	79.0	63.0	79.0	69.0	
11	48.2	79.2	68.2	70.1	74.7	70.0	75.0	80.0	69.0	
12	44.2	61.7	82.0	77.4	78.7	71.0	76.0	66.4	70.0	
13	48.6	61.7	68.0	69.2	68.6	79.7	79.0	66.5	76.0	
14	44.5	64.1	75.8	90.0	78.0	76.0	76.0	67.1	72.0	
15	43.5	75.1	63.5	65.0	70.0	62.0	72.1	67.7	75.0	
16	48.2	64.0	71.4	71.4	69.7	61.0	76.1	85.0	90.0	
17	41.5	64.0	72.8	71.0	71.9	78.0	79.4	85.0	87.0	
18	51.6	55.0	62.2	76.4	69.5	76.1	79.0	85.0	86.0	
19	62.1	54.0	61.7	95.0	67.0	78.3	72.0	84.0	81.0	
20	65.3	67.0	63.0	97.0	69.0	76.4	76.0	61.1	82.0	
21	64.2	54.0	90.0	97.0	77.0	70.0	78.0	59.5	81.0	
22	62.2	54.3	64.6	100.0	78.0	70.1	70.0	85.0	85.0	
23	67.7	72.4	64.4	87.0	76.8	60.1	76.7	84.0	87.0	
24	64.5	57.0	62.2	87.0	70.0	70.7	70.0	87.0	70.0	
25	64.3	54.7	60.0	87.0	70.5	60.0	76.0	65.7	77.7	
Average zeta potential (-mV)	57.33	62.94	72.08	79.95	70.96	71.21	72.67	76.44	76.92	

Table A3 Data for zeta potential measurement of ferric oxide at pH 9 and variable MES at 30°C. Weight of ferric oxide = 1.5 mg.

MES Concentration (%w/v)	0.002	0.005	0.008	0.011	0.014	0.017	0.02	0.05	0.075	
Zeta potential (-mV)	1	42.1	76.0	79.0	95.0	79.0	80.7	78.6	82.0	88.9
2	58.4	73.0	79.0	92.0	77.4	77.0	79.4	81.0	77.7	
3	60.0	70.0	71.0	93.0	79.0	80.8	79.8	84.0	80.0	
4	69.6	73.0	74.0	92.0	74.0	74.5	78.5	85.0	79.0	
5	51.0	71.0	83.0	99.0	84.0	85.2	77.8	87.6	79.6	
6	51.5	78.0	71.0	88.0	82.0	82.0	77.5	86.3	75.5	
7	54.0	66.4	86.0	70.0	86.0	76.0	86.0	83.7	80.5	
8	54.0	78.7	74.0	70.0	71.0	84.0	86.0	85.1	83.3	
9	54.1	75.1	76.0	79.0	77.7	80.0	85.0	82.5	78.8	
10	56.3	75.0	84.0	70.0	76.6	82.9	87.0	82.0	78.5	
11	51.5	73.0	84.0	79.0	81.0	89.4	86.0	85.0	72.9	
12	51.5	75.3	86.0	78.7	74.6	84.6	85.0	90.1	75.5	
13	58.3	77.0	76.0	95.0	82.0	86.2	89.0	89.0	77.8	
14	52.1	70.0	79.0	92.0	79.0	82.0	83.0	83.0	76.5	
15	58.4	72.0	79.0	92.0	79.8	80.0	82.3	81.4	75.5	
16	66.0	77.0	84.0	91.0	77.8	3.0	81.4	80.8	92.5	
17	79.0	71.0	80.0	90.0	78.0	81.4	88.3	78.4	93.5	
18	78.0	70.0	85.0	90.0	77.0	86.0	81.3	74.1	79.0	
19	63.4	71.0	86.0	80.0	80.0	82.0	81.3	74.3	85.0	
20	62.4	76.0	73.0	80.0	81.0	82.0	83.9	85.0	72.0	
21	69.9	71.0	79.0	80.0	72.0	81.0	90.4	87.0	81.0	
22	70.0	70.0	86.0	87.0	87.0	89.4	70.7	83.0	86.0	
23	74.0	76.0	87.0	91.0	70.0	89.4	76.8	88.0	81.0	
24	64.0	73.0	83.0	94.0	70.0	87.3	69.0	76.2	79.0	
25	64.0	73.0	76.0	70.0	80.0	86.5	82.0	84.0	82.3	
Average zeta potential (-mV)	60.54	73.26	80.00	85.51	78.24	79.73	81.84	83.14	80.45	

Table A3 (Continue).

MES Concentration (%w/v)	0.1	0.12	0.14	0.16	0.18	0.2	0.25	0.3	0.4	
Zeta potential (-mV)	1	86.0	86.3	93.2	80.0	89.2	89.0	90.0	89.2	90.0
2	81.0	81.3	81.4	81.0	87.0	80.0	82.0	87.1	90.0	
3	87.0	88.0	90.6	83.0	84.2	86.0	89.0	86.1	89.8	
4	86.0	85.4	86.4	83.6	84.0	87.0	86.0	85.7	88.9	
5	85.0	80.1	85.4	80.4	81.0	85.0	83.4	89.5	91.2	
6	86.0	83.6	89.0	86.0	88.7	85.0	85.1	87.3	93.0	
7	84.0	83.4	82.0	86.0	88.8	86.0	85.7	90.4	80.0	
8	84.0	81.2	85.0	87.4	90.1	89.0	83.0	90.2	89.0	
9	86.0	84.0	85.3	85.2	80.4	87.0	87.0	82.1	85.6	
10	87.0	86.0	76.4	82.1	70.0	85.0	90.0	81.1	86.0	
11	86.0	83.0	93.9	83.7	80.0	83.0	80.0	84.6	89.2	
12	81.0	85.0	85.8	90.0	84.3	89.0	80.0	85.7	82.4	
13	86.0	86.4	89.6	90.0	83.7	80.0	79.0	87.4	88.6	
14	85.0	87.0	85.6	91.0	85.0	87.0	78.7	83.0	90.4	
15	86.0	83.6	87.8	92.0	82.0	89.0	95.0	87.0	80.0	
16	84.0	89.2	89.0	91.0	81.0	85.0	78.7	88.0	82.0	
17	82.0	83.7	80.4	86.6	83.0	88.0	77.7	80.0	90.0	
18	88.0	83.0	93.2	86.7	81.0	84.0	96.0	86.3	89.0	
19	70.0	82.0	93.2	86.3	82.0	83.0	89.0	80.2	85.7	
20	79.0	87.4	93.0	95.0	83.0	87.0	88.1	82.3	85.3	
21	87.0	83.6	81.0	95.0	84.0	86.0	88.3	84.5	84.6	
22	89.0	83.4	80.0	95.2	85.0	87.0	88.1	84.5	87.1	
23	81.0	81.7	80.0	81.5	87.0	87.0	89.5	82.0	84.6	
24	85.0	80.5	77.8	93.5	87.0	90.0	90.9	90.0	87.7	
25	80.0	83.1	79.9	90.1	79.0	81.0	90.0	89.8	89.3	
Average zeta potential (-mV)	84.04	84.08	85.80	87.29	83.62	85.80	86.01	85.76	87.18	

Table A4 Data for zeta potential measurement of ferric oxide at pH 11 and variable MES at 30°C. Weight of ferric oxide = 1.5 mg.

MES Concentration (%w/v)	0.002	0.005	0.008	0.011	0.014	0.017	0.02	0.05	0.075	
Zeta potential (-mV)	1	65.8	90.0	101.0	107.0	80.3	83.6	85.3	83.2	95.1
2	62.8	84.0	85.0	98.0	80.1	81.7	84.2	84.2	95.3	
3	58.8	90.0	93.0	95.0	90.5	85.5	83.1	83.2	85.6	
4	69.5	88.0	100.0	81.0	85.4	85.6	82.4	85.4	85.3	
5	55.1	90.0	83.0	100.0	85.0	87.3	83.4	85.4	72.5	
6	68.7	79.0	89.0	98.0	82.0	90.4	84.1	83.1	85.4	
7	55.6	87.0	94.0	93.0	81.2	83.6	82.7	81.2	95.6	
8	62.9	77.0	106.0	95.3	81.2	80.2	81.6	83.6	96.6	
9	64.4	94.0	78.0	98.4	82.4	80.3	90.1	85.2	83.1	
10	62.3	77.0	85.0	98.3	82.6	83.7	85.0	81.0	81.3	
11	69.0	92.0	109.0	98.4	89.8	87.1	84.0	98.0	81.1	
12	56.3	72.0	96.0	98.1	88.7	87.1	82.3	98.0	85.5	
13	62.5	78.0	87.0	99.1	82.1	84.1	86.4	85.0	88.8	
14	68.5	85.0	90.0	99.1	86.0	83.6	82.1	83.0	88.9	
15	64.4	87.0	100.0	90.0	81.0	83.6	81.9	72.0	89.0	
16	62.8	84.0	92.0	95.0	82.0	80.0	82.9	95.0	90.0	
17	58.9	85.0	93.1	92.0	85.7	90.0	83.8	72.1	89.9	
18	59.0	84.0	88.6	98.0	85.3	90.0	83.0	77.8	90.1	
19	55.1	90.0	89.4	70.0	85.6	82.0	85.0	78.3	81.5	
20	62.3	84.0	89.5	110.0	80.0	86.4	80.0	87.5	95.3	
21	62.8	77.0	86.9	96.0	89.0	86.3	79.9	88.1	99.5	
22	65.9	79.0	84.0	100.0	80.0	87.8	79.8	79.8	99.8	
23	62.9	88.0	83.6	91.3	86.4	87.9	78.9	81.3	84.0	
24	64.4	77.0	87.5	91.8	88.7	81.2	79.8	70.0	85.0	
25	62.5	78.0	84.1	93.4	71.2	80.0	77.6	98.0	77.0	
Average zeta potential (-mV)	62.53	83.84	90.99	95.45	83.69	84.76	82.77	83.98	88.05	

Table A4 (Continue).

MES Concentration (%w/v)	0.1	0.12	0.14	0.16	0.18	0.2	0.25	0.3	0.4	
Zeta potential (-mV)	1	77.0	77.1	76.4	91.0	94.1	89.1	74.1	86.4	87.0
2	74.0	77.2	74.5	91.0	94.5	89.7	84.3	87.0	90.0	
3	80.0	79.1	83.2	93.0	79.9	89.3	87.1	88.0	100.0	
4	80.5	77.8	75.9	93.4	84.0	89.8	89.1	87.2	100.0	
5	80.3	76.3	91.2	93.6	94.0	98.8	87.1	87.3	100.0	
6	80.4	74.5	91.2	83.0	84.0	98.6	89.1	87.8	100.0	
7	83.2	80.0	95.2	81.0	95.0	98.1	81.0	86.9	98.3	
8	108.0	85.0	94.7	85.0	79.9	110.0	90.0	98.7	98.7	
9	100.0	98.0	95.3	82.0	87.0	87.2	109.0	97.1	97.8	
10	98.0	90.4	91.0	83.0	85.0	87.6	98.0	95.3	85.0	
11	95.1	8.6	78.0	85.0	83.0	89.0	95.0	95.6	87.0	
12	95.0	100.0	78.0	98.1	82.0	82.0	85.0	100.0	88.1	
13	90.0	98.1	82.0	98.1	81.0	85.0	89.0	99.9	88.6	
14	100.0	98.2	86.2	100.0	82.0	86.0	88.3	99.8	87.4	
15	108.0	80.4	83.4	98.3	74.0	80.1	90.0	99.9	89.0	
16	109.0	90.3	85.0	98.7	79.0	80.5	99.9	83.0	87.0	
17	88.0	90.5	99.0	70.0	79.0	80.7	91.0	89.0	85.0	
18	83.0	91.6	100.0	98.1	80.0	80.3	91.4	84.0	87.0	
19	80.3	93.1	108.0	98.1	87.6	80.6	96.0	85.0	82.0	
20	89.4	95.6	108.0	98.3	89.8	82.9	93.0	81.0	81.0	
21	83.7	89.7	75.0	99.9	87.6	88.7	95.0	70.0	89.0	
22	81.9	88.7	85.0	99.8	89.9	95.4	98.0	81.0	79.1	
23	87.4	96.4	100.0	100.0	99.1	95.3	88.6	70.5	79.3	
24	85.4	98.0	99.0	108.0	89.2	95.4	89.0	81.0	95.4	
25	80.1	99.0	99.0	110.0	88.9	83.0	81.3	98.0	93.9	
Average zeta potential (-mV)	88.71	85.34	89.37	93.46	85.98	88.92	90.37	88.78	90.22	

Table A5 Data for zeta potential measurement of ferric oxide at pH 5 and variable AE at 30°C. Weight of ferric oxide = 1.5 mg.

AE Concentration (%w/v)	0.002	0.014	0.02	0.1	0.16	0.18	0.2	0.25	0.3	0.4
Zeta potential (-mV)	20.2	36.3	41.3	40.0	48.0	50.2	52.5	53.0	55.0	45.0
2	20.5	38.7	41.6	40.1	47.0	49.3	52.0	53.0	56.0	45.3
3	18.0	35.3	41.9	42.1	49.0	48.0	52.0	53.5	48.0	50.2
4	19.0	39.1	42.0	43.2	48.0	52.0	52.0	53.4	55.5	70.0
5	20.6	36.3	42.0	38.0	48.0	52.0	51.0	53.1	52.9	70.1
6	15.6	37.0	42.0	39.0	48.0	52.5	51.6	54.8	53.8	50.0
7	14.8	37.0	43.1	38.7	48.5	51.6	52.0	54.7	54.8	62.0
8	25.0	37.0	43.9	38.7	48.3	51.5	53.2	54.1	54.6	55.0
9	20.0	40.0	40.4	38.6	48.5	51.3	52.5	54.6	54.6	56.0
10	20.0	40.0	40.8	39.5	48.4	54.0	52.0	54.2	54.3	54.3
11	21.0	40.0	40.4	38.4	48.5	53.0	50.0	54.9	55.0	55.4
12	22.0	35.0	42.0	36.0	48.7	50.7	49.7	55.0	55.3	62.0
13	21.2	35.0	41.2	36.0	45.0	48.0	49.9	56.0	55.8	54.6
14	21.1	35.0	41.6	39.1	47.0	46.0	49.3	54.0	60.0	54.5
15	20.5	36.3	48.0	39.4	42.0	50.4	49.4	52.0	62.0	69.0
16	20.0	36.5	44.0	39.6	43.0	49.5	49.2	51.0	62.0	50.0
17	20.0	38.0	43.0	39.7	45.0	55.8	50.4	51.0	62.0	55.3
18	20.0	30.0	43.0	30.0	48.6	45.8	50.5	53.0	56.0	56.1
19	21.0	30.0	42.0	33.0	49.1	50.1	50.4	53.1	59.0	52.0
20	16.0	29.8	42.0	37.0	50.0	50.8	50.1	53.2	56.1	51.4
21	18.0	29.7	41.0	36.0	50.5	50.6	50.9	53.5	50.3	67.1
22	17.0	38.3	41.0	39.3	50.5	58.0	53.2	53.1	80.0	67.2
23	16.5	38.6	41.3	39.8	42.5	55.0	52.0	52.5	58.5	54.0
24	17.4	38.0	41.8	40.0	46.8	52.0	52.0	52.6	56.2	53.0
25	18.1	38.7	41.4	42.0	46.4	53.4	53.1	52.8	55.6	53.1
Average zeta potential (-mV)	19.33	36.22	42.11	38.53	47.41	51.26	51.24	53.44	56.93	56.50

Table A6 Data for zeta potential measurement of ferric oxide at pH 7 and variable AE at 30°C. Weight of ferric oxide = 1.5 mg.

AE Concentration (%w/v)	0.002	0.014	0.02	0.1	0.16	0.18	0.2	0.25	0.3	0.4	
Zeta potential (-mV)	1	22.0	36.0	45.0	40.0	50.0	53.0	53.0	54.0	57.0	54.0
2	25.0	37.3	46.0	42.0	53.0	53.1	55.6	60.0	56.0	56.0	
3	24.0	40.0	43.0	40.1	52.0	53.5	55.1	70.0	54.0	53.0	
4	25.1	48.0	47.0	40.3	59.0	53.6	55.3	73.0	69.0	54.0	
5	26.0	43.0	42.0	40.4	39.0	54.5	55.0	77.0	60.0	55.0	
6	24.2	44.0	48.0	40.3	30.0	54.6	55.0	44.0	60.0	56.0	
7	22.4	42.1	46.0	40.4	60.0	54.8	55.0	48.0	59.1	53.0	
8	21.5	36.0	44.0	40.1	33.0	67.0	55.0	33.0	58.5	53.5	
9	24.0	47.0	43.2	40.1	36.0	54.4	54.0	58.0	58.4	56.0	
10	25.4	30.0	44.8	40.4	50.0	54.5	54.0	59.0	58.3	53.6	
11	25.0	30.0	40.0	41.0	53.0	54.1	54.3	52.0	58.6	50.1	
12	28.0	29.0	40.0	41.5	52.0	54.8	54.5	55.3	58.4	50.5	
13	20.0	43.0	46.0	41.5	50.2	54.3	54.1	56.4	59.0	60.0	
14	26.1	41.0	43.0	41.3	50.5	52.0	54.1	56.3	59.0	58.0	
15	25.4	41.0	44.1	41.3	50.1	52.3	54.3	65.0	59.0	58.6	
16	25.2	42.3	43.2	42.0	50.3	52.4	54.6	56.0	54.0	58.4	
17	24.0	40.4	44.0	42.0	50.8	52.5	54.8	56.4	54.5	58.3	
18	22.0	40.3	48.0	42.0	50.6	53.0	55.0	56.3	56.0	70.0	
19	22.5	40.7	47.0	43.2	50.4	53.6	58.0	57.0	56.5	60.1	
20	26.1	49.0	39.0	43.4	50.8	55.0	59.0	57.1	56.3	60.1	
21	24.0	38.0	50.0	43.7	50.4	55.0	59.0	50.0	65.0	72.0	
22	28.0	40.6	46.0	39.0	51.0	55.4	59.0	50.0	56.3	77.0	
23	24.1	40.1	48.0	38.0	51.4	55.4	60.0	60.4	55.0	48.5	
24	27.0	40.0	48.1	39.5	51.6	55.8	50.0	60.0	40.0	47.4	
25	20.0	40.0	47.4	39.4	51.2	55.3	69.0	68.0	40.0	60.4	
Average zeta potential (-mV)	24.28	39.95	44.91	40.92	49.05	54.56	55.87	57.29	56.72	57.34	

Table A7 Data for zeta potential measurement of ferric oxide at pH 9 and variable AE at 30°C. Weight of ferric oxide = 1.5 mg.

AE Concentration (%w/v)	0.002	0.014	0.02	0.1	0.16	0.18	0.2	0.25	0.3	0.4	
Zeta potential (-mV)	1	35.0	40.0	46.0	43.0	47.9	56.3	57.3	60.3	60.0	62.5
2	35.0	40.3	47.0	43.5	52.3	58.0	58.0	60.0	60.0	63.2	
3	36.0	43.0	48.0	43.5	52.3	56.3	58.0	60.5	60.2	64.6	
4	37.0	43.2	48.0	67.0	52.5	56.3	35.0	64.0	60.3	65.3	
5	37.0	43.6	47.0	70.0	52.5	58.0	72.0	59.3	60.1	67.2	
6	37.1	43.9	48.0	38.1	52.6	58.0	70.3	58.0	62.3	69.0	
7	37.3	43.6	48.3	43.5	53.3	57.5	45.0	57.3	69.0	80.0	
8	37.2	43.4	46.0	43.2	53.5	57.3	40.0	57.8	67.0	80.0	
9	37.6	44.0	46.3	47.0	55.0	57.1	61.2	59.0	67.0	83.0	
10	37.5	44.3	47.4	40.0	56.0	59.2	61.3	59.6	66.3	36.0	
11	37.6	44.2	47.8	38.0	59.7	60.1	62.0	59.4	65.0	66.0	
12	37.4	47.0	47.3	34.1	55.2	60.0	62.5	59.0	65.3	62.0	
13	35.2	40.5	47.4	45.3	50.9	60.2	66.0	63.0	60.3	63.0	
14	35.3	43.0	48.2	45.4	56.6	57.3	65.4	62.5	50.0	60.0	
15	36.0	40.0	48.6	45.3	53.8	69.6	55.8	62.6	50.5	65.0	
16	40.0	36.0	48.3	47.3	58.1	57.0	67.6	63.4	55.0	64.0	
17	32.0	38.0	48.4	47.4	62.1	40.0	67.9	63.5	56.0	62.5	
18	36.3	36.0	48.3	47.4	53.0	40.0	67.9	67.0	58.4	66.3	
19	38.2	38.2	48.3	44.0	53.3	45.0	45.0	63.0	59.3	62.0	
20	43.0	35.3	48.7	45.3	52.0	45.3	50.2	63.6	62.0	60.0	
21	35.2	35.7	45.3	45.5	55.4	70.3	58.6	63.4	62.3	56.0	
22	33.2	35.3	48.6	48.0	53.6	59.5	59.0	64.0	62.5	55.3	
23	35.6	36.0	44.0	48.0	53.0	58.1	43.0	60.5	63.6	58.5	
24	35.0	37.0	45.1	43.0	52.5	58.6	70.0	60.3	65.0	70.3	
25	37.0	33.2	45.1	44.2	52.5	59.1	70.0	60.0	80.0	71.2	
Average zeta potential (-mV)	36.55	40.19	47.26	45.88	53.98	56.56	58.76	61.24	61.90	64.52	

Table A8 Data for zeta potential measurement of ferric oxide at pH 11 and variable AE at 30°C. Weight of ferric oxide = 1.5 mg.

AE Concentration (%w/v)	0.002	0.014	0.02	0.1	0.16	0.18	0.2	0.25	0.3	0.4	
Zeta potential (-mV)	1	40.0	43.0	50.0	50.0	55.0	60.0	63.0	63.0	70.0	65.0
2	43.0	46.0	50.3	50.0	56.3	60.0	62.0	63.5	70.2	66.3	
3	43.2	46.0	50.1	50.3	56.5	60.0	62.5	63.5	69.0	64.3	
4	43.2	46.3	52.0	59.0	56.5	60.1	62.5	63.5	66.0	69.0	
5	43.6	46.2	50.5	60.0	56.5	61.0	62.1	63.5	62.5	69.7	
6	44.2	46.8	49.8	50.3	60.0	61.0	60.0	64.0	64.3	69.8	
7	44.3	46.9	48.3	51.0	60.2	62.0	60.0	64.7	66.0	68.5	
8	46.5	46.9	48.2	51.2	63.0	62.5	60.0	65.3	65.0	68.4	
9	46.4	46.9	48.1	52.3	60.2	60.3	60.0	65.4	64.3	64.3	
10	40.0	46.9	48.6	51.5	60.3	60.1	63.0	65.6	65.1	63.5	
11	40.2	45.4	48.4	51.3	65.0	60.3	60.5	65.5	65.1	66.0	
12	40.3	45.3	48.7	50.5	61.0	60.6	62.4	67.0	65.7	67.0	
13	41.0	45.7	48.3	50.5	61.2	60.9	61.2	59.9	65.3	64.0	
14	42.0	45.4	42.0	51.3	61.1	60.9	61.7	60.1	63.0	58.0	
15	41.1	45.2	42.3	50.0	58.0	62.0	61.9	60.3	59.0	59.9	
16	41.2	46.0	42.7	49.8	58.3	62.0	61.6	60.5	59.9	59.9	
17	40.3	48.0	42.4	45.0	55.0	55.0	67.0	63.1	59.8	59.9	
18	40.3	48.1	46.0	48.3	59.0	58.0	70.0	64.6	59.9	69.0	
19	40.1	48.4	46.3	48.3	60.0	70.0	65.5	64.7	66.5	67.0	
20	40.3	40.0	49.0	48.5	56.3	60.0	61.3	64.6	66.3	68.6	
21	44.0	43.0	60.0	60.0	58.5	78.0	66.0	64.5	58.0	65.0	
22	37.0	42.0	50.0	70.0	58.4	48.3	66.0	65.0	70.0	71.3	
23	37.0	42.0	53.0	55.0	57.6	49.0	70.0	66.5	66.0	71.1	
24	42.0	42.1	58.0	61.0	57.3	70.0	70.0	67.0	67.0	71.2	
25	40.0	42.7	65.0	66.0	58.0	70.3	60.4	66.3	64.6	63.0	
Average zeta potential (-mV)	41.65	45.25	49.52	53.24	58.77	61.29	63.22	64.06	64.74	65.99	

Table A9 Data for zeta potential measurement of cotton fiber at 30°C. Weight of cotton fiber= 0.1 mg, Volume of suspension = 25 ml

pH solution	1.50	2.10	3.03	4.10	5.01	6.30	7.05	8.01	9.02	10.10	11.02
Zeta potential (-mV)											
1	8.0	5.8	-3.7	-7.5	-13.4	-15.1	-21.2	-21.0	-23.5	-22.7	-24.7
2	7.2	5.9	-3.7	-7.8	-13.5	-15.2	-20.2	-21.0	-23.4	-25.3	-24.9
3	7.1	4.0	-3.8	-7.4	-13.2	-14.7	-18.2	-22.7	-23.0	-24.5	-24.2
4	6.9	4.5	-3.9	-7.7	-13.5	-14.5	-18.5	-21.3	-23.0	-24.5	-24.2
5	7.5	5.0	-3.4	-7.0	-13.0	-15.3	-18.2	-21.3	-23.8	-23.5	-24.9
Average zeta potential (-mV)	7.3	5.0	-3.7	-7.5	-13.3	-15.0	-19.3	-21.5	-23.3	-24.1	-24.6

Table A10 Data for zeta potential measurement of blended cotton/polyester fiber at 30°C. Weight of cotton fiber= 0.1 mg,

Volume of suspension = 25 ml.

pH solution	1.50	2.10	3.03	4.10	5.01	6.15	7.05	8.01	9.02	10.10	11.02
Zeta potential (-mV)											
1	3.4	1.2	-8.9	-17.5	-25.1	-30.0	-44.5	-49.7	-51.3	-49.3	-50.3
2	3.0	1.3	-8.5	-18.9	-25.0	-31.2	-44.5	-48.6	-51.4	-47.3	-50.1
3	3.0	1.5	-7.3	-18.8	-25.5	-31.3	-44.3	-46.0	-51.9	-49.3	-50.0
4	2.8	1.3	-7.0	-17.9	-25.8	-31.1	-44.3	-52.3	-52.0	-50.3	-49.5
5	4.0	1.4	-7.0	-19.0	-24.5	-31.1	-44.3	-50.0	-48.9	-50.8	-50.3
Average zeta potential (-mV)	3.2	1.3	-7.7	-18.4	-25.2	-30.9	-44.4	-49.3	-51.1	-49.4	-50.0

Table A11 Data for zeta potential measurement of polyester fiber at 30°C. Weight of cotton fiber= 0.1 mg,

Volume of suspension = 25 ml.

pH solution	1.5	2.03	3.00	4.09	5.15	6.03	7.30	8.01	9.02	10.10	11.02
Zeta potential (-mV)											
1	2.2	1.1	-11.1	-31.2	-50.04	-59.8	-64.3	-66.5	-68.1	-69.3	-69.9
2	2.0	1.2	-11.0	-31.0	-50.06	-59.9	-64.3	-66.5	-68.1	-69.0	-69.9
3	1.9	1.0	-11.1	-31.0	-50.03	-59.9	-64.4	-66.4	-68.2	-69.1	-69.9
4	2.7	1.1	-11.3	-29.9	-50.02	-59.9	-64.2	-66.6	-68.0	-69.2	-69.8
5	1.5	1.2	-11.0	-31.4	-50.02	-60.0	-64.5	-66.8	-68.3	-69.1	-69.8
Average zeta potential (-mV)	2.1	1.1	-11.1	-30.9	-50.0	-59.9	-64.3	-66.6	-68.1	-69.1	-69.9

Appendix B Adsorption Isotherm Experiment

Table B1 Data for MES adsorption on cotton fabric at surfactant solution pH 5 and 30°C. Weight of cotton fabric = 0.5g, Volume of solution 20 ml.

Initial Concentration (%w/v)	Equilibrium Concentration (%w/v)	Adsorption density mg/m ²
0.002	0.000530	0.135922
0.005	0.002554	0.226167
0.008	0.003858	0.382987
0.011	0.005106	0.544984
0.014	0.007068	0.640962
0.017	0.008802	0.758021
0.020	0.009522	0.968840
0.050	0.033680	1.509015
0.075	0.058746	1.502913
0.100	0.083672	1.509755
0.120	0.103626	1.514008
0.140	0.123186	1.554693
0.160	0.143606	1.515858
0.180	0.163446	1.530652
0.200	0.183291	1.544984
0.250	0.233723	1.505068
0.300	0.283560	1.520092
0.400	0.383201	1.553269

Table B2 Data for MES adsorption on cotton fabric at surfactant solution pH 7 and 30°C. Weight of cotton fabric = 0.5g, Volume of solution 20 ml.

Initial Concentration (%w/v)	Equilibrium Concentration (%w/v)	Adsorption density mg/m ²
0.002	0.000558	0.133333
0.005	0.002680	0.214517
0.008	0.004008	0.369117
0.011	0.005040	0.551086
0.014	0.007374	0.612668
0.017	0.009016	0.738234
0.020	0.011090	0.823856
0.050	0.036069	1.288118
0.075	0.060406	1.349422
0.100	0.085820	1.311142
0.120	0.106186	1.277300
0.140	0.125326	1.356819
0.160	0.145166	1.371613
0.180	0.166046	1.290245
0.200	0.186008	1.293759
0.250	0.235211	1.367456
0.300	0.285291	1.360059
0.400	0.384659	1.418496

Table B3 Data for MES adsorption on cotton fabric at surfactant solution pH 9 and 30°C. Weight of cotton fabric = 0.5g, Volume of solution 20 ml.

Initial Concentration (%w/v)	Equilibrium Concentration (%w/v)	Adsorption density mg/m ²
0.002	0.000554	0.133703
0.005	0.002664	0.215996
0.008	0.004552	0.318816
0.011	0.005392	0.518539
0.014	0.007208	0.628017
0.017	0.009672	0.677577
0.020	0.011794	0.758761
0.050	0.038672	1.047434
0.075	0.063666	1.047989
0.100	0.088670	1.047619
0.120	0.108966	1.020250
0.140	0.128806	1.035044
0.160	0.148586	1.055386
0.180	0.169146	1.003606
0.200	0.188466	1.066482
0.250	0.238983	1.018641
0.300	0.288632	1.051123
0.400	0.388731	1.041953

Table B4 Data for MES adsorption on cotton fabric at surfactant solution pH 11 and 30°C. Weight of cotton fabric = 0.5g, Volume of solution 20 ml.

Initial Concentration (%w/v)	Equilibrium Concentration (%w/v)	Adsorption density mg/m ²
0.002	0.000576	0.131632
0.005	0.002772	0.206010
0.008	0.004786	0.297180
0.011	0.005742	0.486177
0.014	0.008048	0.550347
0.017	0.009926	0.654092
0.020	0.012506	0.692926
0.050	0.041857	0.752936
0.075	0.067126	0.728063
0.100	0.092382	0.704374
0.120	0.112226	0.718816
0.140	0.131906	0.748405
0.160	0.152046	0.735460
0.180	0.172086	0.731761
0.200	0.192229	0.718539
0.250	0.242058	0.734392
0.300	0.292003	0.739421
0.400	0.392053	0.734844

Table B5 Data for MES adsorption on blend polyester/cotton fabric at surfactant solution pH 5 and 30°C. Weight of blend polyester/cotton fabric = 0.5g, Volume of solution 20 ml.

Initial Concentration (%w/v)	Equilibrium Concentration (%w/v)	Adsorption density mg/m ²
0.002	0.001140	0.110080
0.005	0.003738	0.161536
0.008	0.005457	0.325504
0.011	0.006795	0.538240
0.014	0.008510	0.702720
0.017	0.010659	0.811648
0.020	0.012498	0.960256
0.050	0.039799	1.305728
0.075	0.064312	1.368064
0.100	0.089554	1.337088
0.120	0.109027	1.404544
0.140	0.129076	1.398272
0.160	0.149437	1.352064
0.180	0.169223	1.379456
0.200	0.189087	1.396864
0.250	0.239465	1.348480
0.300	0.289073	1.398656
0.400	0.389082	1.397504

Table B6 Data for MES adsorption on blend polyester/cotton fabric at surfactant solution pH 7 and 30°C. Weight of blend polyester/cotton fabric = 0.5g, Volume of solution 20 ml.

Initial Concentration (%w/v)	Equilibrium Concentration (%w/v)	Adsorption density mg/m ²
0.002	0.001130	0.111360
0.005	0.003808	0.152602
0.008	0.005255	0.351360
0.011	0.006657	0.555904
0.014	0.009210	0.613120
0.017	0.011312	0.728064
0.020	0.013190	0.871680
0.050	0.040340	1.236480
0.075	0.065771	1.181312
0.100	0.090242	1.249024
0.120	0.110335	1.237120
0.140	0.130340	1.236480
0.160	0.150470	1.219840
0.180	0.169810	1.304320
0.200	0.190179	1.257088
0.250	0.240080	1.269760
0.300	0.290450	1.222400
0.400	0.390001	1.279872

Table B7 Data for MES adsorption on blend polyester/cotton fabric at surfactant solution pH 9 and 30°C. Weight of blend polyester/cotton fabric = 0.5g, Volume of solution 20 ml.

Initial Concentration (%w/v)	Equilibrium Concentration (%w/v)	Adsorption density mg/m ²
0.002	0.001140	0.110080
0.005	0.003854	0.146688
0.008	0.004956	0.389632
0.011	0.007457	0.453504
0.014	0.009145	0.621440
0.017	0.011832	0.661504
0.020	0.013420	0.842240
0.050	0.042341	0.980352
0.075	0.067001	1.023872
0.100	0.092070	1.015040
0.120	0.112018	1.021696
0.140	0.131836	1.044992
0.160	0.152045	1.018240
0.180	0.171920	1.034240
0.200	0.191601	1.075072
0.250	0.241325	1.110464
0.300	0.291345	1.107840
0.400	0.391459	1.093312

Table B8 Data for MES adsorption on blend polyester/cotton fabric at surfactant solution pH 11 and 30°C. Weight of blend polyester/cotton fabric = 0.5g, Volume of solution 20 ml.

Initial Concentration (%w/v)	Equilibrium Concentration (%w/v)	Adsorption density mg/m ²
0.002	0.001310	0.088320
0.005	0.003856	0.146432
0.008	0.006136	0.238592
0.011	0.008273	0.349056
0.014	0.010351	0.467072
0.017	0.012875	0.528000
0.020	0.015404	0.588288
0.050	0.044621	0.688512
0.075	0.069750	0.672000
0.100	0.094459	0.709248
0.120	0.114595	0.691840
0.140	0.134681	0.680832
0.160	0.154230	0.738560
0.180	0.174638	0.686336
0.200	0.194571	0.694886
0.250	0.244320	0.727040
0.300	0.294348	0.723456
0.400	0.394601	0.691072

Table B9 Data for MES adsorption on polyester fabric at surfactant solution pH 5 and 30°C. Weight of polyester fabric = 0.5g, Volume of solution 20 ml.

Initial Concentration (%w/v)	Equilibrium Concentration (%w/v)	Adsorption density mg/m ²
0.002	0.001540	0.0736
0.005	0.004476	0.0838
0.008	0.007224	0.1242
0.011	0.009068	0.3091
0.014	0.011414	0.4138
0.017	0.013828	0.5075
0.020	0.015748	0.6803
0.050	0.043400	1.0560
0.075	0.068200	1.0880
0.100	0.092980	1.1232
0.120	0.112720	1.1648
0.140	0.132610	1.1824
0.160	0.152640	1.1776
0.180	0.172640	1.1776
0.200	0.192760	1.1584
0.250	0.242801	1.1519
0.300	0.292509	1.1986
0.400	0.392727	1.1637

Table B10 Data for MES adsorption on polyester fabric at surfactant solution pH 7 and 30°C. Weight of polyester fabric = 0.5g, Volume of solution 20 ml.

Initial Concentration (%w/v)	Equilibrium Concentration (%w/v)	Adsorption density mg/m ²
0.002	0.001500	0.0800
0.005	0.004696	0.0486
0.008	0.007290	0.1136
0.011	0.009296	0.2726
0.014	0.011680	0.3712
0.017	0.014016	0.4774
0.020	0.016080	0.6272
0.050	0.044280	0.9152
0.075	0.068980	0.9632
0.100	0.094020	0.9568
0.120	0.113960	0.9664
0.140	0.133740	1.0016
0.160	0.153560	1.0304
0.180	0.173920	0.9728
0.200	0.193620	1.0208
0.250	0.243572	1.0284
0.300	0.293456	1.0470
0.400	0.393764	0.9977

Table B11 Data for MES adsorption on polyester fabric at surfactant solution pH 9 and 30°C. Weight of polyester fabric = 0.5g, Volume of solution 20 ml.

Initial Concentration (%w/v)	Equilibrium Concentration (%w/v)	Adsorption density mg/m ²
0.002	0.001480	0.0832
0.005	0.004766	0.0374
0.008	0.007550	0.0720
0.011	0.009348	0.2643
0.014	0.011096	0.4646
0.017	0.014666	0.3734
0.020	0.016720	0.5248
0.050	0.044953	0.8075
0.075	0.069540	0.8736
0.100	0.094710	0.8464
0.120	0.114760	0.8384
0.140	0.134640	0.8576
0.160	0.154755	0.8392
0.180	0.174580	0.8672
0.200	0.194619	0.8610
0.250	0.244730	0.8433
0.300	0.294889	0.8177
0.400	0.394678	0.8516

Table B12 Data for MES adsorption on polyester fabric at surfactant solution pH 11 and 30°C. Weight of polyester fabric = 0.5g, Volume of solution 20 ml.

Initial Concentration (%w/v)	Equilibrium Concentration (%w/v)	Adsorption density mg/m ²
0.002	0.001416	0.0934
0.005	0.004902	0.0157
0.008	0.007506	0.0790
0.011	0.009580	0.2272
0.014	0.011978	0.3235
0.017	0.014320	0.4288
0.020	0.017360	0.4224
0.050	0.046600	0.5440
0.075	0.071540	0.5536
0.100	0.096722	0.5245
0.120	0.116820	0.5088
0.140	0.136711	0.5262
0.160	0.156814	0.5098
0.180	0.176716	0.5254
0.200	0.196580	0.5472
0.250	0.246888	0.4979
0.300	0.296716	0.5254
0.400	0.396599	0.5442

Table B13 Data for MES adsorption on ferric oxide at surfactant solution pH 5 and 30°C. Weight of ferric oxide = 0.25g, Volume of solution 20 ml.

Initial Concentration (%w/v)	Equilibrium Concentration (%w/v)	Adsorption density mg/m ²
0.002	0.001738	0.015012
0.005	0.004108	0.051228
0.008	0.006346	0.094989
0.011	0.007692	0.189978
0.014	0.007276	0.386159
0.017	0.009582	0.426016
0.020	0.011004	0.516640
0.050	0.028840	1.215219
0.075	0.052420	1.296770
0.100	0.074980	1.436899
0.120	0.092820	1.560948
0.140	0.111000	1.665470
0.160	0.129880	1.729792
0.180	0.150260	1.707968
0.200	0.169860	1.730940
0.250	0.219600	1.745872

Table B14 Data for MES adsorption on ferric oxide at surfactant solution pH 7 and 30°C. Weight of ferric oxide = 0.25g, Volume of solution 20 ml.

Initial Concentration (%w/v)	Equilibrium Concentration (%w/v)	Adsorption density mg/m ²
0.002	0.001840	0.009154
0.005	0.004252	0.042923
0.008	0.006072	0.110725
0.011	0.007462	0.203187
0.014	0.008338	0.325169
0.017	0.009464	0.432793
0.020	0.010490	0.546159
0.050	0.029280	1.189950
0.075	0.052160	1.311701
0.100	0.074960	1.438047
0.120	0.095580	1.402441
0.140	0.113280	1.534530
0.160	0.133200	1.539124
0.180	0.152840	1.559799
0.200	0.172940	1.554056
0.250	0.223200	1.539124

Table B15 Data for MES adsorption on ferric oxide at surfactant solution pH 9 and 30°C. Weight of ferric oxide = 0.25g, Volume of solution 20 ml.

Initial Concentration (%w/v)	Equilibrium Concentration (%w/v)	Adsorption density mg/m ²
0.002	0.0014062	0.034102
0.005	0.0040946	0.051997
0.008	0.006562	0.082584
0.011	0.007358	0.209160
0.014	0.006496	0.430955
0.017	0.008376	0.495276
0.020	0.009636	0.595205
0.050	0.029420	1.181910
0.075	0.051660	1.340416
0.100	0.074040	1.490883
0.120	0.094060	1.489734
0.140	0.113460	1.524192
0.160	0.132040	1.605743
0.180	0.151900	1.613783
0.200	0.171860	1.616080
0.250	0.223100	1.544867

Table B16 Data for MES adsorption on ferric oxide at surfactant solution pH 11 and 30°C. Weight of ferric oxide = 0.25g, Volume of solution 20 ml.

Initial Concentration (%w/v)	Equilibrium Concentration (%w/v)	Adsorption density mg/m ²
0.002	0.0019656	0.001976
0.005	0.004802	0.011371
0.008	0.0074488	0.031655
0.011	0.009554	0.083044
0.014	0.010972	0.173898
0.017	0.01278	0.242355
0.020	0.01506	0.283704
0.050	0.039820	0.584637
0.075	0.060800	0.815506
0.100	0.084460	0.892462
0.120	0.105260	0.846518
0.140	0.123880	0.925772
0.160	0.141320	1.072793
0.180	0.162420	1.009620
0.200	0.183480	0.948744
0.250	0.232200	1.022254

Table B17 Data for AE adsorption on ferric oxide at surfactant solution pH 5 and 30°C. Weight of ferric oxide = 0.25g, Volume of solution 20 ml.

Initial Concentration (%w/v)	Equilibrium Concentration (%w/v)	Adsorption density mg/m ²
0.002	0.0016356	0.041855
0.005	0.0042690	0.083963
0.008	0.0070210	0.112448
0.011	0.0094230	0.181134
0.014	0.0107950	0.368126
0.017	0.0117150	0.607035
0.020	0.0134210	0.755664
0.050	0.0390600	1.256569
0.075	0.0636950	1.298492
0.100	0.0887900	1.287581
0.200	0.1887000	1.297918
0.300	0.2881223	1.364273
0.400	0.3890640	1.256109

Table B18 Data for AE adsorption on ferric oxide at surfactant solution pH 7 and 30°C. Weight of ferric oxide = 0.25g, Volume of solution 20 ml.

Initial Concentration (%w/v)	Equilibrium Concentration (%w/v)	Adsorption density mg/m ²
0.002	0.0019970	0.000345
0.005	0.0047046	0.033930
0.008	0.0074157	0.067113
0.011	0.0092170	0.204795
0.014	0.0103330	0.421192
0.017	0.0115240	0.628973
0.020	0.0131770	0.783690
0.050	0.0398750	1.162958
0.075	0.0647300	1.179612
0.100	0.0900550	1.142283
0.200	0.1896500	1.188801
0.300	0.2900540	1.142398
0.400	0.3901270	1.134013

Table B19 Data for AE adsorption on ferric oxide at surfactant solution pH 9 and 30°C. Weight of ferric oxide = 0.25g, Volume of solution 20 ml.

Initial Concentration (%w/v)	Equilibrium Concentration (%w/v)	Adsorption density mg/m ²
0.002	0.0019808	0.002205
0.005	0.0046995	0.034515
0.008	0.0074286	0.065631
0.011	0.0087480	0.258665
0.014	0.0104880	0.403388
0.017	0.0117860	0.598880
0.020	0.0132690	0.773123
0.050	0.0402000	1.125628
0.075	0.0652300	1.122182
0.100	0.0905600	1.084279
0.200	0.1900800	1.139411
0.300	0.2904578	1.096017
0.400	0.3904765	1.093869

Table B20 Data for AE adsorption on ferric oxide at surfactant solution pH 11 and 30°C. Weight of ferric oxide = 0.25g, Volume of solution 20 ml.

Initial Concentration (%w/v)	Equilibrium Concentration (%w/v)	Adsorption density mg/m ²
0.002	0.0019840	0.001838
0.005	0.0046792	0.036847
0.008	0.0064220	0.181249
0.011	0.0085950	0.276238
0.014	0.0094780	0.519397
0.017	0.0115820	0.622312
0.020	0.0125300	0.858004
0.050	0.0415000	0.976310
0.075	0.0662950	0.999856
0.100	0.0913650	0.991816
0.200	0.1910500	1.027997
0.300	0.2909741	1.036715
0.400	0.3911761	1.013513

Table B21 Data for AE adsorption on cotton fabric at surfactant solution pH 5 and 30°C. Weight of cotton fabric = 0.5g, Volume of solution 20 ml.

Initial Concentration (%w/v)	Equilibrium Concentration (%w/v)	Adsorption density mg/m ²
0.002	0.001850	0.0240
0.005	0.002787	0.3541
0.008	0.003419	0.7330
0.011	0.004602	1.0237
0.014	0.006937	1.1301
0.017	0.009552	1.1917
0.020	0.012533	1.1947
0.050	0.042501	1.1998
0.100	0.092541	1.1934
0.200	0.192626	1.1798
0.300	0.292534	1.1946
0.400	0.392562	1.1901

Table B22 Data for AE adsorption on cotton fabric at surfactant solution pH 7 and 30°C. Weight of cotton fabric = 0.5g, Volume of solution 20 ml.

Initial Concentration (%w/v)	Equilibrium Concentration (%w/v)	Adsorption density mg/m ²
0.002	0.001896	0.0166
0.005	0.002832	0.3469
0.008	0.003535	0.7144
0.011	0.005058	0.9507
0.014	0.007671	1.0126
0.017	0.010543	1.0331
0.020	0.013545	1.0328
0.050	0.043578	1.0275
0.100	0.093612	1.0221
0.200	0.193622	1.0205
0.300	0.293851	0.9838
0.400	0.393546	1.0326

Table B23 Data for AE adsorption on cotton fabric at surfactant solution pH 9 and 30°C. Weight of cotton fabric = 0.5g, Volume of solution 20 ml.

Initial Concentration (%w/v)	Equilibrium Concentration (%w/v)	Adsorption density mg/m ²
0.002	0.001911	0.0142
0.005	0.002878	0.3395
0.008	0.004041	0.6334
0.011	0.006497	0.7205
0.014	0.009114	0.7818
0.017	0.011998	0.8003
0.020	0.015107	0.7829
0.050	0.044915	0.8136
0.100	0.094896	0.8166
0.200	0.194799	0.8322
0.300	0.294782	0.8349
0.400	0.394887	0.8181

Table B24 Data for AE adsorption on cotton fabric at surfactant solution pH 11 and 30°C. Weight of cotton fabric = 0.5g, Volume of solution 20 ml.

Initial Concentration (%w/v)	Equilibrium Concentration (%w/v)	Adsorption density mg/m ²
0.002	0.001954	0.0074
0.005	0.002889	0.3378
0.008	0.005231	0.4430
0.011	0.007945	0.4888
0.014	0.010823	0.5083
0.017	0.013768	0.5171
0.020	0.016662	0.5341
0.050	0.046716	0.5254
0.100	0.096682	0.5309
0.200	0.196737	0.5221
0.300	0.296563	0.5499
0.400	0.396727	0.5237

Table B25 Data for AE adsorption on Blend cotton/polyester fabric at surfactant solution pH 5 and 30°C. Weight of Blend cotton/polyester fabric = 0.5g, Volume of solution 20 ml.

Initial Concentration (%w/v)	Equilibrium Concentration (%w/v)	Adsorption density mg/m ²
0.002	0.0018635	0.017477
0.005	0.0036357	0.174628
0.008	0.0060231	0.253041
0.011	0.0078520	0.402944
0.014	0.0102370	0.481664
0.017	0.0130470	0.505984
0.020	0.0162450	0.480640
0.050	0.0460730	0.502662
0.100	0.0961388	0.494235
0.200	0.1959045	0.524224
0.300	0.2958570	0.530304
0.400	0.3959849	0.513928

Table B26 Data for AE adsorption on blend cotton/polyester fabric at surfactant solution pH 7 and 30°C. Weight of blend cotton/polyester fabric = 0.5g, Volume of solution 20 ml.

Initial Concentration (%w/v)	Equilibrium Concentration (%w/v)	Adsorption density mg/m ²
0.002	0.00183191	0.021516
0.005	0.00377123	0.157283
0.008	0.00623241	0.226252
0.011	0.00832332	0.342615
0.014	0.01096931	0.387928
0.017	0.01373754	0.417595
0.020	0.01684356	0.404024
0.050	0.04655978	0.440348
0.100	0.09656926	0.439135
0.200	0.19648421	0.450021
0.300	0.29660231	0.434904
0.400	0.39632174	0.470817

Table B27 Data for AE adsorption on blend cotton/polyester fabric at surfactant solution pH 9 and 30°C. Weight of blend cotton/polyester fabric = 0.5g, Volume of solution 20 ml.

Initial Concentration (%w/v)	Equilibrium Concentration (%w/v)	Adsorption density mg/m ²
0.002	0.001834810	0.021144
0.005	0.004098732	0.115362
0.008	0.006300131	0.217583
0.011	0.008576512	0.310206
0.014	0.011298023	0.345853
0.017	0.014284023	0.347645
0.020	0.017045903	0.378124
0.050	0.047048105	0.377843
0.100	0.096912947	0.395143
0.200	0.196748013	0.416254
0.300	0.296828741	0.405921
0.400	0.396823475	0.406595

Table B28 Data for AE adsorption on blend cotton/polyester fabric at surfactant solution pH 11 and 30°C. Weight of blend cotton/polyester fabric = 0.5g, Volume of solution 20 ml.

Initial Concentration (%w/v)	Equilibrium Concentration (%w/v)	Adsorption density mg/m ²
0.002	0.001874052	0.016121
0.005	0.003941240	0.135521
0.008	0.006482950	0.194182
0.011	0.009030323	0.252119
0.014	0.011848562	0.275384
0.017	0.014534882	0.315535
0.020	0.017449242	0.326497
0.050	0.047103480	0.370755
0.100	0.097092305	0.372185
0.200	0.197102200	0.370918
0.300	0.297024110	0.380914
0.400	0.397012740	0.382369

Table B29 Data for AE adsorption on polyester fabric at surfactant solution pH 5 and 30°C. Weight of polyester fabric = 0.5g, Volume of solution 20 ml.

Initial Concentration (%w/v)	Equilibrium Concentration (%w/v)	Adsorption density mg/m ²
0.002	0.001956	0.004068
0.005	0.003543	0.134720
0.008	0.005647	0.217568
0.011	0.008137	0.264725
0.014	0.011101	0.268054
0.017	0.014032	0.274434
0.020	0.016981	0.279149
0.050	0.046820	0.294036
0.100	0.096764	0.299214
0.200	0.196784	0.297365
0.300	0.296773	0.298373
0.400	0.396752	0.300324

Table B30 Data for AE adsorption on polyester fabric at surfactant solution pH 7 and 30°C. Weight of polyester fabric = 0.5g, Volume of solution 20 ml.

Initial Concentration (%w/v)	Equilibrium Concentration (%w/v)	Adsorption density mg/m ²
0.002	0.001943	0.005270
0.005	0.003562	0.132963
0.008	0.005692	0.213407
0.011	0.008507	0.230513
0.014	0.011446	0.236153
0.017	0.014441	0.236616
0.020	0.017340	0.245955
0.050	0.047381	0.242164
0.100	0.097373	0.242903
0.200	0.197327	0.247157
0.300	0.297373	0.242894
0.400	0.397345	0.245492

Table B31 Data for AE adsorption on polyester fabric at surfactant solution pH 9 and 30°C. Weight of polyester fabric = 0.5g, Volume of solution 20 ml.

Initial Concentration (%w/v)	Equilibrium Concentration (%w/v)	Adsorption density mg/m ²
0.002	0.001995	0.000462
0.005	0.003516	0.137217
0.008	0.005770	0.206195
0.011	0.008729	0.209986
0.014	0.011741	0.208877
0.017	0.014753	0.207767
0.020	0.017684	0.214147
0.050	0.047760	0.207120
0.100	0.097662	0.216181
0.200	0.197692	0.213407
0.300	0.297773	0.205908
0.400	0.397745	0.208507

Table B32 Data for AE adsorption on polyester fabric at surfactant solution pH 11 and 30°C. Weight of polyester fabric = 0.5g, Volume of solution 20 ml.

Initial Concentration (%w/v)	Equilibrium Concentration (%w/v)	Adsorption density mg/m ²
0.002	0.001913	0.008044
0.005	0.003576	0.131669
0.008	0.005981	0.186667
0.011	0.008916	0.192695
0.014	0.011975	0.187240
0.017	0.014879	0.196117
0.020	0.017922	0.192141
0.050	0.048038	0.181415
0.100	0.098104	0.175312
0.200	0.198042	0.181045
0.300	0.297969	0.187795
0.400	0.398035	0.181692

Appendix C Surface tension Measurement

Table C1 Surface tension of MES.

Concentration (%w/v)	IFT(mN/m)			average
0.001	42.78	42.75	42.74	42.76
0.002	41.59	41.62	41.64	41.62
0.004	40.79	40.74	40.81	40.78
0.006	39.85	39.90	39.87	39.87
0.008	38.39	38.36	38.40	38.38
0.010	37.80	37.77	37.75	37.77
0.020	37.52	37.55	37.61	37.56
0.040	37.20	37.19	37.15	37.18
0.060	37.01	37.04	37.05	37.03
0.080	36.89	36.91	36.88	36.89
0.100	36.71	36.79	36.75	36.75
0.200	36.45	36.51	36.55	36.50
0.400	36.15	36.19	36.21	36.18
0.600	35.97	36.01	35.95	35.98
0.800	35.79	35.82	35.74	35.78
1.000	35.51	35.6	35.52	35.54

Table C2 Surface tension of AE.

Concentration (%w/v)	IFT (mN/m)			average
0.001	70.59	70.36	70.65	70.464
0.002	65.81	65.51	64.54	65.29
0.003	57.34	56.35	57.85	57.18
0.004	46.37	46.88	45.55	46.27
0.005	44.23	43.66	43.23	43.71
0.006	41.42	41.29	40.20	40.97
0.007	38.75	37.03	38.81	38.20
0.008	37.39	37.2	37.37	37.32
0.009	36.3	35.92	36.03	36.08
0.010	34.64	33.89	33.6	33.00
0.020	32.84	32.89	33.28	32.69
0.030	32.75	32.75	32.58	32.19
0.040	31.85	32.44	32.28	32.46
0.050	32.26	32.63	32.49	30.99
1.000	31.01	31.39	30.58	30.99

Appendix D Detergency Experiment

Appendix D1 %Detergency from cotton by using MES surfactant at different surfactant concentration.

Surfactant Conc. (%w/v)	Sample No.	Soiled swatch after washing	Soiled swatch before washing	unsoiled swatch	%Detergency	Average %Detergency
0	1	78.48	76.89	88.14	14.1333	10.1429
	2	75.64	74.80	87.65	6.5370	
	3	79.20	78.23	88.17	9.7586	
0.0300	1	77.34	75.92	86.70	13.1725	13.2547
	2	78.87	77.89	86.79	11.0112	
	3	78.44	76.91	86.73	15.5804	
0.0750	1	78.56	75.48	89.10	22.6138	22.0938
	2	79.00	75.12	88.83	28.3005	
	3	77.18	75.17	88.25	15.3670	
0.2000	1	81.08	76.39	88.26	39.5114	38.5021
	2	81.13	76.45	88.71	38.1729	
	3	80.87	76.32	88.35	37.8221	
0.2500	1	81.18	76.1500	86.7800	47.3189	41.7072
	2	81.72	76.3700	86.7900	51.3436	
	3	79.23	76.5100	86.7900	26.4591	
0.5000	1	81.42	76.3300	88.5700	41.5850	41.3570
	2	81.56	76.2800	89.5000	39.9395	
	3	81.51	76.0300	88.9100	42.5466	

Table D2 %Detergency from cotton by using MES surfactant at different surfactant concentration at pH 5.

Surfactant Conc. (%w/v)	Sample No.	Soiled swatch after washing	Soiled swatch before washing	unsoiled swatch	%Detergency	Average %Detergency
0	1	77.40	76.76	87.83	5.7814	8.5390
	2	73.93	72.70	87.70	8.2000	
	3	77.08	75.70	87.56	11.6358	
0.0100	1	78.02	76.26	88.60	14.2626	11.7099
	2	77.85	76.44	89.07	11.1639	
	3	78.89	78.04	86.80	9.7032	
0.0300	1	77.08	75.92	86.67	10.7907	12.6156
	2	79.03	77.79	86.88	13.6414	
	3	78.23	76.91	86.75	13.4146	
0.0750	1	78.16	75.68	89.20	18.3432	23.0254
	2	79.35	75.42	88.73	29.5267	
	3	76.58	73.17	89.25	21.2065	
0.2500	1	80.28	76.05	86.78	39.4222	40.1995
	2	81.72	76.87	86.79	48.8911	
	3	77.23	72.61	86.92	32.2851	
0.5000	1	80.32	76.43	86.57	38.3629	40.0230
	2	82.06	77.18	88.50	43.1095	
	3	80.31	75.03	88.71	38.5965	

Table D3 %Detergency from cotton by using MES surfactant at different surfactant concentration at pH 7.

Surfactant Conc. (%w/v)	Sample No.	Soiled swatch after washing	Soiled swatch before washing	unsoiled swatch	%Detergency	Average %Detergency
0	1	78.48	76.89	88.14	14.1333	10.1429
	2	75.64	74.80	87.65	6.5370	
	3	79.20	78.23	88.17	9.7586	
0.0100	1	79.15	77.65	86.6	16.7598	23.4226
	2	79.76	77.82	86.98	21.1790	
	3	80.82	78.03	86.66	32.3291	
0.0300	1	79.32	76.62	86.05	28.6320	23.8357
	2	77.62	74.92	86.13	24.0856	
	3	77.92	75.84	86.91	18.7895	
0.0750	1	81.13	76.39	89.18	37.0602	39.0424
	2	81.09	75.41	88.56	43.1939	
	3	79.61	73.95	89.30	36.8730	
0.2500	1	80.47	74.79	86.4800	48.5885	46.0218
	2	81.26	77.00	87.1500	41.9704	
	3	80.84	75.22	87.0500	47.5063	
0.5000	1	82.89	77.82	89.2600	44.3182	47.6897
	2	81.72	76.04	88.6400	45.0794	
	3	82.86	75.77	88.9800	53.6715	

Table D4 %Detergency from cotton by using MES surfactant at different surfactant concentration at pH 9.

Surfactant Conc. (%w/v)	Sample No.	Soiled swatch after washing	Soiled swatch before washing	unsoiled swatch	%Detergency	Average %Detergency
0	1	75.98	74.17	87.81	13.2698	14.1198
	2	77.09	75.69	87.94	11.4286	
	3	77.37	75.12	87.86	17.6609	
0.0100	1	79.37	77.35	86.49	22.1007	16.2988
	2	78.68	77.08	86.50	16.9851	
	3	78.54	77.66	86.63	9.8105	
0.0300	1	78.08	75.28	86.66	24.6046	24.2856
	2	78.98	77.21	86.49	19.0733	
	3	79.68	76.73	86.84	29.1790	
0.0750	1	79.79	73.31	89.22	40.7291	44.7075
	2	81.74	76.35	88.93	42.8458	
	3	82.50	76.04	88.82	50.5477	
0.2500	1	83.14	75.30	87.68	63.3279	61.0460
	2	82.94	75.45	87.75	60.8943	
	3	82.26	74.00	88.02	58.9158	
0.5000	1	84.54	77.79	88.81	61.2523	61.5167
	2	82.65	74.40	88.47	58.6354	
	3	83.57	73.03	89.33	64.6626	

Table D5 %Detergency from cotton by using MES surfactant at different surfactant concentration at pH 11.

Surfactant Conc. (%w/v)	Sample No.	Soiled swatch after washing	Soiled swatch before washing	unsoiled swatch	%Detergency	Average %Detergency
0	1	79.56	78.53	88.37	10.4675	13.9051
	2	76.61	74.65	87.19	15.6300	
	3	81.59	80.25	88.83	15.6177	
0.0100	1	80.08	78.35	86.49	21.2531	28.9000
	2	79.91	75.57	86.86	38.4411	
	3	79.51	76.75	86.97	27.0059	
0.0300	1	78.65	75.84	86.40	26.6098	28.1078
	2	76.80	74.43	86.53	19.5868	
	3	80.88	75.71	89.27	38.1268	
0.0750	1	80.51	74.48	87.02	48.0861	50.9534
	2	81.77	74.67	86.89	58.1015	
	3	81.18	75.92	87.19	46.6726	
0.2500	1	81.51	73.68	86.68	60.2308	62.7679
	2	82.02	73.74	87.92	58.3921	
	3	83.31	74.14	87.30	69.6809	
0.5000	1	83.95	75.75	88.79	62.8834	63.2548
	2	83.75	74.82	89.19	62.1434	
	3	84.32	75.93	88.89	64.7377	

Table D6 %Detergency from blend polyester/cotton by using MES surfactant at different surfactant concentration.

Surfactant Conc. (%w/v)	Sample No.	Soiled swatch after washing	Soiled swatch before washing	unsoiled swatch	%Detergency	Average %Detergency
0	1	74.26	71.42	85.39	20.3293	17.0793
	2	73.97	71.71	84.97	17.0437	
	3	73.42	71.49	85.41	13.8649	
0.0300	1	74.38	72.21	85.53	16.2913	19.5876
	2	74.85	71.61	85.39	23.5123	
	3	74.38	71.83	85.28	18.9591	
0.0750	1	75.87	72.14	85.88	27.1470	28.9234
	2	75.03	69.79	85.47	33.4184	
	3	75.86	72.38	85.66	26.2048	
0.2000	1	75.07	70.25	85.63	31.3394	37.0106
	2	76.03	71.41	85.32	33.2135	
	3	77.47	70.54	85.45	46.4789	
0.2500	1	76.92	70.08	85.03	45.7525	41.5747
	2	76.53	70.81	85.34	39.3668	
	3	76.52	70.71	85.38	39.6046	
0.5000	1	77.15	71.76	85.29	39.8374	42.7635
	2	78.34	71.09	85.72	49.5557	
	3	77.05	71.97	85.03	38.8974	

Table D7 %Detergency from blend polyester/cotton by using MES surfactant at different surfactant concentration at pH 5.

Surfactant Conc. (%w/v)	Sample No.	Soiled swatch after washing	Soiled swatch before washing	unsoiled swatch	%Detergency	Average %Detergency
0	16	72.58	69.78	85.10	18.2768	17.6461
	17	72.6	70.41	85.41	14.6000	
	18	72.68	69.42	85.67	20.0615	
0.0300	61	73.31	71.81	86.13	10.4749	19.6686
	62	74.24	71.65	86.73	17.1751	
	63	74.89	70.08	85.42	31.3559	
0.0750	64	74.87	70.08	85.92	30.2399	27.7534
	65	75.36	70.12	85.32	34.4737	
	66	74.65	71.97	86.42	18.5467	
0.2500	67	77.93	71.87	85.12	45.7358	36.5180
	68	76.74	72.00	85.72	34.5481	
	69	75.34	71.09	85.61	29.2700	
0.5000	70	76.32	71.09	86.59	33.7419	37.0488
	71	76.27	71.12	86.19	34.1739	
	72	78.21	71.76	86.68	43.2306	

Table D8 %Detergency from blend polyester/cotton by using MES surfactant at different surfactant concentration at pH 7.

Surfactant Conc. (%w/v)	Sample No.	Soiled swatch after washing	Soiled swatch before washing	unsoiled swatch	%Detergency	Average %Detergency
0	1	74.26	71.42	85.39	20.3293	17.0793
	2	73.97	71.71	84.97	17.0437	
	3	73.42	71.49	85.41	13.8649	
0.0300	49	75.56	72.12	85.00	26.7081	23.3687
	50	75.23	73.20	86.32	15.4726	
	51	75.21	71.32	85.25	27.9253	
0.0750	52	76.74	71.24	85.43	38.7597	29.5700
	53	74.87	72.30	85.68	19.2078	
	54	75.67	71.24	85.65	30.7425	
0.2500	55	76.98	71.45	85.14	40.3944	41.8743
	56	76.94	71.35	84.89	41.2851	
	57	78.01	73.04	84.35	43.9434	
0.5000	58	78.05	72.47	85.12	44.1107	42.2781
	59	77.34	72.46	84.49	40.5653	
	60	77.26	71.83	84.71	42.1584	

Table D9 %Detergency from blend polyester/cotton by using MES surfactant at different surfactant concentration at pH 9.

Surfactant Conc. (%w/v)	Sample No.	Soiled swatch after washing	Soiled swatch before washing	unsoiled swatch	%Detergency	Average %Detergency
0	19	72.80	70.31	85.59	16.2958	17.6690
	20	73.19	70.72	85.38	16.8486	
	21	70.77	67.30	84.77	19.8626	
0.0300	37	74.78	70.08	85.56	30.3618	20.9499
	38	74.14	72.35	85.32	13.8011	
	39	73.85	71.26	85.12	18.6869	
0.0750	40	75.37	67.21	86.24	42.8797	32.1155
	41	75.21	70.34	85.55	32.0184	
	42	75.42	72.34	86.70	21.4485	
0.2500	43	78.80	71.35	87.01	47.5734	50.4625
	44	78.92	72.27	84.98	52.3210	
	45	78.74	72.36	84.75	51.4931	
0.5000	46	79.57	72.46	85.33	55.2448	52.7591
	47	80.05	72.57	85.51	57.8053	
	48	78.56	72.59	85.79	45.2273	

Table D10 %Detergency from blend polyester/cotton by using MES surfactant at different surfactant concentration at pH 11.

Surfactant Conc. (%w/v)	Sample No.	Soiled swatch after washing	Soiled swatch before washing	unsoiled swatch	%Detergency	Average %Detergency
0	22	73.34	69.53	85.91	23.2601	19.6222
	23	72.20	69.69	85.80	15.5804	
	24	72.89	69.82	85.15	20.0261	
0.0300	28	73.27	68.49	85.38	28.3008	28.6564
	29	74.32	70.25	85.43	26.8116	
	30	74.87	70.26	85.20	30.8568	
0.0750	31	75.45	69.21	85.65	37.9562	36.3317
	32	76.03	69.95	86.45	36.8485	
	33	74.98	69.13	86.24	34.1905	
0.2500	34	78.86	70.40	86.01	54.1960	56.9746
	35	79.02	69.99	86.31	55.3309	
	36	79.46	69.79	85.54	61.3968	
0.5000	25	78.26	68.93	85.97	54.7535	56.9849
	26	78.24	68.63	85.39	57.3389	
	27	78.74	67.98	86.26	58.8621	

Table D11 %Detergency from polyester by using MES surfactant at different surfactant concentration.

Surfactant Conc. (%w/v)	Sample No.	Soiled swatch after washing (A)	Soiled swatch before washing (B)	unsoiled swatch (C0)	%Detergency	Average %Detergency
0	1	73.61	70.15	84.93	23.4100	17.6994
	2	72.78	70.41	83.95	17.5037	
	3	72.31	70.62	84.49	12.1846	
0.0300	1	74.45	72.21	85.53	16.8168	20.8768
	2	74.87	71.61	85.39	23.6575	
	3	74.81	71.83	85.28	22.1561	
0.0750	1	75.67	72.14	85.88	25.6914	29.1812
	2	75.84	69.79	85.47	38.5842	
	3	75.47	72.38	85.66	23.2681	
0.2000	1	76.58	70.23	86.57	38.8617	38.4373
	2	76.31	70.14	86.45	37.8296	
	3	76.14	70.54	85.04	38.6207	
0.2500	1	76.83	70.08	85.03	45.1505	41.8308
	2	76.64	70.81	85.34	40.1239	
	3	76.61	70.71	85.38	40.2181	
0.5000	1	77.52	71.76	85.29	42.5721	41.9706
	2	78.04	71.09	85.72	47.5051	
	3	76.65	71.97	85.03	35.8346	

Table D12 %Detergency from polyester by using MES surfactant at different surfactant concentration at pH 5.

Surfactant Conc. (%w/v)	Sample No.	Soiled swatch after washing	Soiled swatch before washing	unsoiled swatch	%Detergency	Average %Detergency
0	1	73.27	70.59	84.60	19.1292	17.3290
	2	73.13	70.96	84.75	15.7360	
	3	72.39	70.07	83.62	17.1218	
0.0300	1	73.41	70.97	84.49	18.0473	19.9397
	2	74.54	71.77	84.51	21.7425	
	3	73.69	70.96	84.59	20.0293	
0.0750	1	74.56	70.61	84.99	27.4687	28.8140
	2	74.62	70.13	84.37	31.5309	
	3	74.57	70.75	84.67	27.4425	
0.2500	1	77.82	71.90	84.58	46.6877	37.7268
	2	75.74	71.23	84.81	33.2106	
	3	75.34	71.02	84.00	33.2820	
0.5000	1	75.82	71.27	83.00	38.7894	37.1819
	2	76.71	71.90	84.39	38.5108	
	3	76.13	72.00	84.06	34.2454	

Table D13 %Detergency from polyester by using MES surfactant at different surfactant concentration at pH 7.

Surfactant Conc. (%w/v)	Sample No.	Soiled swatch after washing	Soiled swatch before washing	unsoiled swatch	%Detergency	Average %Detergency
0	1	73.72	71.61	83.00	18.5250	17.0222
	2	73.18	71.71	84.37	11.6114	
	3	74.12	71.24	85.00	20.9302	
0.0300	1	74.34	70.80	84.81	25.2677	24.2454
	2	73.26	70.45	84.26	20.3476	
	3	74.48	70.74	84.53	27.1211	
0.0750	1	75.09	71.50	83.97	28.7891	30.9839
	2	75.04	70.68	83.78	33.2824	
	3	75.14	71.07	84.25	30.8801	
0.2500	1	76.94	71.54	83.94	43.5484	41.4869
	2	76.42	71.72	84.51	36.7475	
	3	77.02	71.23	84.34	44.1648	
0.5000	1	76.58	69.89	84.07	47.1791	41.2105
	2	76.23	70.08	84.53	42.5606	
	3	76.16	71.71	84.84	33.8919	

Table D14 %Detergency from polyester by using MES surfactant at different surfactant concentration at pH 9.

Surfactant Conc. (%w/v)	Sample No.	Soiled swatch after washing	Soiled swatch before washing	unsoiled swatch	%Detergency	Average %Detergency
0	1	72.56	70.89	84.99	11.8440	18.2917
	2	73.84	70.86	84.20	22.3388	
	3	73.46	70.65	84.23	20.6922	
0.0300	1	74.67	70.33	84.18	31.3357	24.3875
	2	74.01	70.52	84.11	25.6806	
	3	73.68	71.56	84.69	16.1462	
0.0750	1	75.15	70.04	84.00	36.6046	32.8809
	2	75.01	70.41	83.84	34.2517	
	3	74.52	70.93	83.85	27.7864	
0.2500	1	78.76	71.74	83.73	58.5488	51.2175
	2	76.81	71.61	83.21	44.8276	
	3	77.63	71.26	83.93	50.2762	
0.5000	1	78.57	71.14	84.48	55.6972	51.5800
	2	77.97	72.18	84.53	46.8826	
	3	78.64	72.00	84.73	52.1603	

Table D15 %Detergency from polyester by using MES surfactant at different surfactant concentration at pH 11.

Surfactant Conc. (%w/v)	Sample No.	Soiled swatch after washing	Soiled swatch before washing	unsoiled swatch	%Detergency	Average %Detergency
0	1	74.32	71.53	85.85	19.4832	20.0329
	2	75.27	71.59	85.83	25.8427	
	3	73.90	71.95	85.15	14.7727	
0.0300	1	74.97	72.03	83.08	26.6063	28.6089
	2	75.70	72.08	84.16	29.9669	
	3	75.53	72.16	83.68	29.2535	
0.0750	1	76.76	71.43	84.62	40.4094	37.9383
	2	76.42	71.06	84.05	41.2625	
	3	75.69	71.28	85.00	32.1429	
0.2500	1	78.75	70.28	85.12	57.0755	57.6620
	2	78.54	71.26	84.09	56.7420	
	3	78.76	70.79	84.26	59.1685	
0.5000	1	79.35	71.24	84.89	59.4139	57.6911
	2	78.23	71.31	84.24	53.5189	
	3	78.89	72.04	83.43	60.1405	

Table D16 %Detergency from cotton by using AE surfactant at different surfactant concentration.

Surfactant Conc. (%w/v)	Sample No.	Soiled swatch after washing	Soiled swatch before washing	unsoiled swatch	%Detergency	Average %Detergency
0	1	78.48	76.89	88.14	14.1333	10.1429
	2	75.64	74.80	87.65	6.5370	
	3	79.20	78.23	88.17	9.7586	
1.0000	1	79.51	77.73	88.36	16.7451	16.1878
	2	76.20	73.84	88.11	16.5382	
	3	79.48	77.79	88.85	15.2803	
2.0100	1	79.00	75.28	88.58	27.9699	19.8120
	2	78.37	76.26	88.32	17.4959	
	3	75.39	73.24	88.63	13.9701	
3.0100	1	78.53	74.90	88.29	27.1098	28.9129
	2	80.35	77.04	87.77	30.8481	
	3	80.61	77.47	88.38	28.7809	
5.0100	1	79.33	75.07	88.51	31.6964	30.0112
	2	80.20	77.38	88.08	26.3551	
	3	79.72	75.46	88.78	31.9820	

Table D17 %Detergency from cotton by using AE surfactant at different surfactant concentration at pH 5.

Surfactant Conc. (%w/v)	Sample No.	Soiled swatch after washing	Soiled swatch before washing	unsoiled swatch	%Detergency	Average %Detergency
0	1	77.40	76.76	87.83	5.7814	8.5390
	2	73.93	72.70	87.70	8.2000	
	3	77.08	75.70	87.56	11.6358	
0.0100	1	77.65	76.63	87.98	8.9868	9.8821
	2	77.57	76.37	87.80	10.4987	
	3	76.86	75.66	87.47	10.1609	
0.0500	1	74.68	72.12	88.86	15.2927	15.0124
	2	76.55	74.97	88.49	11.6864	
	3	75.36	72.44	88.61	18.0581	
0.0750	1	76.8	74.91	89.01	13.4043	15.3489
	2	74.71	71.97	89.10	15.9953	
	3	74.84	72.02	88.96	16.6470	
1.0000	1	77.65	75.58	87.56	17.2788	21.7530
	2	77.64	74.54	87.32	24.2567	
	3	77.12	74.10	86.83	23.7235	
2.0400	1	76.91	74.28	86.59	21.3647	21.9562
	2	76.56	75.31	87.23	10.4866	
	3	76.61	71.47	86.58	34.0172	
3.5000	1	79.57	77.29	87.88	21.5297	24.0908
	2	81.31	78.86	87.81	27.3743	
	3	78.95	76.05	88.46	23.3683	
5.0000	1	79.59	75.75	88.07	31.1688	24.0662
	2	80.33	78.20	87.96	21.8238	
	3	80.44	78.65	87.97	19.2060	

Table D18 %Detergency from cotton by using AE surfactant at different surfactant concentration at pH 7.

Surfactant Conc. (%w/v)	Sample No.	Soiled swatch after washing	Soiled swatch before washing	unsoiled swatch	%Detergency	Average %Detergency
0	1	78.48	76.89	88.14	14.1333	10.1429
	2	75.64	74.80	87.65	6.5370	
	3	79.20	78.23	88.17	9.7586	
0.0100	1	77.28	76.36	87.72	8.0986	11.5337
	2	77.10	74.71	87.43	18.7893	
	3	77.47	76.62	87.64	7.7132	
0.0500	1	77.44	75.66	88.68	13.6713	15.8493
	2	74.56	71.69	89.30	16.2976	
	3	75.40	72.51	88.95	17.5791	
0.0750	1	75.87	74.00	89.15	12.3432	15.7851
	2	75.85	72.92	89.16	18.0419	
	3	74.95	72.06	89.09	16.9701	
1.0000	1	76.87	74.93	87.45	15.4952	16.8014
	2	77.78	76.51	87.61	11.4414	
	3	78.77	76.32	86.76	23.4674	
2.0400	1	77.04	73.88	85.40	27.4306	26.4771
	2	75.86	73.49	86.96	17.5947	
	3	80.70	77.60	86.61	34.4062	
3.5000	1	79.13	76.30	88.11	23.9627	27.5521
	2	80.41	77.01	88.28	30.1686	
	3	79.11	75.61	87.88	28.5249	
5.0000	1	79.51	77.59	87.43	19.5122	29.0000
	2	81.36	78.69	87.37	30.7604	
	3	78.28	73.05	87.29	36.7275	

Table D19 %Detergency from cotton by using AE surfactant at different surfactant concentration at pH 9.

Surfactant Conc. (%w/v)	Sample No.	Soiled swatch after washing	Soiled swatch before washing	unsoiled swatch	%Detergency	Average %Detergency
0	1	75.98	74.17	87.81	13.2698	14.1198
	2	77.09	75.69	87.94	11.4286	
	3	77.37	75.12	87.86	17.6609	
0.0100	1	76.31	73.99	85.37	20.3866	17.7506
	2	77.39	75.20	87.26	18.1592	
	3	78.10	76.60	86.8	14.7059	
0.0500	1	77.92	75.24	89.21	19.1840	18.8761
	2	76.87	73.56	89.21	21.1502	
	3	77.25	74.99	88.86	16.2942	
0.0750	1	81.87	80.59	88.31	16.5803	19.2803
	2	82.27	80.39	88.39	23.5000	
	3	82.03	80.65	88.42	17.7606	
1.0000	1	76.47	74.76	87.06	13.9024	21.4651
	2	77.47	73.62	86.07	30.9237	
	3	77.32	75.23	85.91	19.5693	
2.0400	1	80.01	74.70	87.04	43.0308	31.5843
	2	80.48	79.23	87.66	14.8280	
	3	81.18	77.07	88.21	36.8941	
3.5000	1	81.14	77.42	87.76	35.9768	33.3424
	2	81.07	78.21	88.17	28.7149	
	3	81.16	77.16	88.48	35.3357	
5.0000	1	80.07	76.25	86.92	35.8013	35.0837
	2	82.24	79.58	87.65	32.9616	
	3	81.67	78.74	86.77	36.4882	

Table D20 %Detergency from cotton by using AE surfactant at different surfactant concentration at pH 11.

Surfactant Conc. (%w/v)	Sample No.	Soiled swatch after washing	Soiled swatch before washing	unsoiled swatch	%Detergency	Average %Detergency
0	1	79.56	78.53	88.37	10.4675	13.9051
	2	76.61	74.65	87.19	15.6300	
	3	81.59	80.25	88.83	15.6177	
0.0100	1	77.48	73.71	86.71	29.0000	21.5474
	2	77.50	75.96	88.51	12.2709	
	3	76.97	73.49	88.38	23.3714	
0.0500	1	79.27	76.67	89.39	20.4403	21.8365
	2	78.59	74.32	88.99	29.1070	
	3	77.63	75.44	89.16	15.9621	
0.0750	1	82.07	80.48	88.57	19.6539	22.3871
	2	82.24	80.39	88.37	23.1830	
	3	83.84	82.22	88.88	24.3243	
1.0000	1	77.28	74.16	86.27	25.7638	22.0683
	2	77.22	75.12	85.83	19.6078	
	3	76.95	74.40	86.64	20.8333	
2.0400	1	81.24	77.69	86.90	38.5451	38.5030
	2	79.77	74.92	88.00	37.0795	
	3	82.68	79.23	87.88	39.8844	
3.5000	1	81.83	77.48	87.85	41.9479	40.6387
	2	81.78	76.65	88.36	43.8087	
	3	80.96	76.61	88.64	36.1596	
5.0000	1	81.52	78.01	87.69	36.2603	41.4851
	2	82.62	79.03	87.25	43.6740	
	3	81.64	76.48	88.07	44.5211	

Table D21 %Detergency from blend polyester/cotton by using AE surfactant at different surfactant concentration.

Surfactant Conc. (%w/v)	Sample No.	Soiled swatch after washing	Soiled swatch before washing	unsoiled swatch	%Detergency	Average %Detergency
0	1	74.26	71.42	85.39	20.3293	17.0793
	2	73.97	71.71	84.97	17.0437	
	3	73.42	71.49	85.41	13.8649	
1.0000	1	74.91	71.71	85.36	23.4432	17.5543
	2	74.20	71.73	86.11	17.1766	
	3	73.48	71.80	85.75	12.0430	
2.0000	1	73.12	69.38	85.85	22.7080	19.3869
	2	72.17	69.36	85.33	17.5955	
	3	72.19	69.34	85.30	17.8571	
3.0000	1	74.65	69.90	85.31	30.8241	29.0296
	2	74.16	70.03	85.77	26.2389	
	3	74.53	69.87	85.39	30.0258	
5.0000	1	74.83	70.07	85.52	30.8091	30.4775
	2	74.90	69.47	85.08	34.7854	
	3	73.72	69.48	85.89	25.8379	

Table D22 %Detergency from blend polyester/cotton by using AE surfactant at different surfactant concentration at pH5.

Surfactant Conc. (%w/v)	Sample No.	Soiled swatch after washing	Soiled swatch before washing	unsoiled swatch	%Detergency	Average %Detergency
0	1	72.58	69.78	85.10	18.2768	17.6461
	2	72.60	70.41	85.41	14.6000	
	3	72.68	69.42	85.67	20.0615	
0.075	1	74.87	73.00	85.04	15.5316	19.2997
	2	74.15	71.92	85.98	15.8606	
	3	74.15	70.06	85.49	26.5068	
1.0000	1	74.37	72.93	85.52	11.4376	19.6338
	2	73.28	70.51	85.27	18.7669	
	3	75.67	71.42	86.23	28.6968	
2.0000	1	75.04	70.78	85.40	29.1382	24.6299
	2	74.26	70.49	86.96	22.8901	
	3	74.10	70.60	86.61	21.8613	
3.5000	1	74.13	70.30	85.27	25.5845	24.4570
	2	74.01	70.11	85.16	25.9136	
	3	73.81	70.61	85.24	21.8729	
5.0000	1	75.51	71.49	86.51	26.7643	24.4323
	2	74.76	70.39	86.04	27.9233	
	3	73.78	71.05	85.72	18.6094	

Table D23 %Detergency from blend polyester/cotton by using AE surfactant at different surfactant concentration at pH7.

Surfactant Conc. (%w/v)	Sample No.	Soiled swatch after washing	Soiled swatch before washing	unsoiled swatch	%Detergency	Average %Detergency
0	1	74.26	71.42	85.39	20.3293	17.0793
	2	73.97	71.71	84.97	17.0437	
	3	73.42	71.49	85.41	13.8649	
0.0750	1	74.81	71.97	85.01	21.7791	18.8310
	2	73.81	71.97	84.10	15.1690	
	3	74.94	72.02	86.96	19.5448	
1.0000	1	74.75	71.00	85.56	25.7555	19.9366
	2	74.44	72.53	85.32	14.9335	
	3	75.14	72.40	86.73	19.1207	
2.0000	1	75.31	72.48	86.59	20.0567	28.3566
	2	76.40	72.32	85.66	30.5847	
	3	76.60	71.36	86.58	34.4284	
3.5000	1	75.57	71.89	86.00	26.0808	28.6525
	2	76.51	71.87	85.43	34.2183	
	3	74.95	71.54	84.83	25.6584	
5.0000	1	75.59	71.58	85.16	29.5287	29.3286
	2	75.23	71.26	85.82	27.2665	
	3	75.81	71.54	85.23	31.1907	

Table D24 %Detergency from blend polyester/cotton by using AE surfactant at different surfactant concentration at pH9.

Surfactant Conc. (%w/v)	Sample No.	Soiled swatch after washing	Soiled swatch before washing	unsoiled swatch	%Detergency	Average %Detergency
0	1	72.80	70.31	85.59	16.2958	17.6690
	2	73.19	70.72	85.38	16.8486	
	3	70.77	67.30	84.77	19.8626	
0.0750	1	74.17	70.59	85.93	23.3377	19.6605
	2	73.47	70.39	85.24	20.7407	
	3	73.03	70.65	86.62	14.9029	
1.0000	1	74.67	71.76	85.06	21.8797	22.4800
	2	75.27	72.62	85.39	20.7518	
	3	74.12	70.23	85.91	24.8087	
2.0000	1	76.41	70.70	86.00	37.3203	32.7763
	2	75.38	70.23	85.00	34.8680	
	3	74.08	70.07	85.41	26.1408	
3.5000	1	76.04	71.42	85.35	33.1658	34.9081
	2	75.07	70.21	85.28	32.2495	
	3	76.26	70.23	85.57	39.3090	
5.0000	1	76.07	70.80	85.13	36.7760	34.4132
	2	75.42	70.53	85.80	32.0236	
	3	75.46	70.17	85.53	34.4401	

Table D25 %Detergency from blend polyester/cotton by using AE surfactant at different surfactant concentration at pH11.

Surfactant Conc. (%w/v)	Sample No.	Soiled swatch after washing	Soiled swatch before washing	unsoiled swatch	%Detergency	Average %Detergency
0	1	73.34	69.53	85.91	23.2601	19.6222
	2	72.20	69.69	85.80	15.5804	
	3	72.89	69.82	85.15	20.0261	
0.0750	1	75.07	71.77	85.57	23.9130	23.1228
	2	75.14	73.00	85.36	17.3139	
	3	75.74	72.00	85.29	28.1415	
1.0000	1	75.28	71.85	84.39	27.3525	24.8561
	2	75.62	72.78	85.83	21.7625	
	3	75.95	72.30	86.64	25.4533	
2.0000	1	77.04	72.51	86.90	31.4802	37.3176
	2	77.57	72.09	85.94	39.5668	
	3	78.00	72.13	86.48	40.9059	
3.5000	1	76.00	69.36	86.47	38.8077	38.5827
	2	76.35	69.21	86.36	41.6327	
	3	75.32	69.24	86.46	35.3078	
5.0000	1	76.02	69.97	85.36	39.3112	38.8404
	2	75.84	69.54	85.87	38.5793	
	3	75.85	69.53	85.89	38.6308	

Table D26 %Detergency from polyester by using AE surfactant at different surfactant concentration.

Surfactant Conc. (%w/v)	Sample No.	Soiled swatch after washing	Soiled swatch before washing	unsoiled swatch	%Detergency	Average %Detergency
0	1	73.72	71.61	83.00	18.5250	17.0222
	2	73.18	71.71	84.37	11.6114	
	3	74.12	71.24	85.00	20.9302	
1.0000	1	73.25	71.21	85.32	14.4578	17.1309
	2	73.70	70.70	85.64	20.0803	
	3	73.17	70.63	85.70	16.8547	
2.0000	1	73.88	70.64	85.80	21.3720	20.7359
	2	73.15	70.56	85.55	17.2782	
	3	74.45	70.98	85.71	23.5574	
3.0000	1	74.52	70.00	85.41	29.3316	30.0847
	2	75.42	70.95	85.58	30.5537	
	3	74.96	70.76	84.59	30.3688	
5.0000	1	75.06	70.75	84.91	30.4379	30.3475
	2	74.23	70.19	84.54	28.1533	
	3	75.09	70.43	84.79	32.4513	

Table D27 %Detergency from polyester by using AE surfactant at different surfactant concentration at pH5.

Surfactant Conc. (%w/v)	Sample No.	Soiled swatch after washing	Soiled swatch before washing	unsoiled swatch	%Detergency	Average %Detergency
0	1	73.27	70.59	84.60	19.1292	17.3290
	2	73.13	70.96	84.75	15.7360	
	3	72.39	70.07	83.62	17.1218	
0.075	1	74.35	70.63	84.16	27.4945	20.1609
	2	73.04	70.90	84.06	16.2614	
	3	73.01	70.69	84.56	16.7267	
1.0000	1	74.32	70.59	84.76	26.3232	21.7286
	2	72.28	70.46	84.69	12.7899	
	3	74.72	71.56	83.68	26.0726	
2.0000	1	73.03	70.43	83.89	19.3165	24.8897
	2	74.06	70.52	83.13	28.0730	
	3	74.21	70.59	83.86	27.2796	
3.5000	1	73.45	70.54	83.45	22.5407	24.9717
	2	74.04	70.40	83.36	28.0864	
	3	73.72	70.65	83.29	24.2880	
5.0000	1	75.21	70.83	83.43	34.7619	25.1978
	2	73.36	70.74	83.21	21.0104	
	3	73.28	70.62	84.04	19.8212	

Table D28 %Detergency from polyester by using AE surfactant at different surfactant concentration at pH7.

Surfactant Conc. (%w/v)	Sample No.	Soiled swatch after washing	Soiled swatch before washing	unsoiled swatch	%Detergency	Average %Detergency
0	1	73.72	71.61	83.00	18.5250	17.0222
	2	73.18	71.71	84.37	11.6114	
	3	74.12	71.24	85.00	20.9302	
0.075	1	74.21	71.62	85.12	19.1852	18.9299
	2	73.82	71.96	85.23	14.0090	
	3	74.48	71.12	85.36	23.5955	
1.0000	1	74.25	71.48	85.64	19.5621	20.5429
	2	74.54	71.98	85.73	18.6182	
	3	74.41	71.01	85.51	23.4483	
2.0000	1	74.34	71.58	84.67	21.0848	27.1790
	2	75.04	71.02	84.47	29.8885	
	3	75.23	71.00	84.84	30.5636	
3.5000	1	74.71	71.87	84.08	23.2596	28.3439
	2	75.41	71.91	83.45	30.3293	
	3	75.58	71.20	85.13	31.4429	
5.0000	1	75.71	71.21	85.20	32.1658	29.3768
	2	75.30	71.81	85.47	25.5490	
	3	75.69	71.59	85.07	30.4154	

Table D29 %Detergency from polyester by using AE surfactant at different surfactant concentration at pH9.

Surfactant Conc. (%w/v)	Sample No.	Soiled swatch after washing	Soiled swatch before washing	unsoiled swatch	%Detergency	Average %Detergency
0	1	72.56	70.89	84.99	11.8440	18.2917
	2	73.84	70.86	84.20	22.3388	
	3	73.46	70.65	84.23	20.6922	
0.075	1	73.07	70.46	84.76	18.2517	19.2212
	2	73.12	70.05	84.46	21.3046	
	3	73.30	70.87	84.29	18.1073	
1.0000	1	74.14	70.51	85.13	24.8290	23.1977
	2	74.53	70.84	85.24	25.6250	
	3	73.05	70.16	85.26	19.1391	
2.0000	1	76.40	70.54	85.74	38.5526	32.7293
	2	75.16	70.44	85.01	32.3953	
	3	74.01	70.24	84.08	27.2399	
3.5000	1	76.14	70.64	84.58	39.4548	34.5790
	2	75.80	71.15	84.95	33.6957	
	3	75.55	71.43	84.90	30.5865	
5.0000	1	76.05	71.84	84.60	32.9937	34.8426
	2	75.83	71.79	84.36	32.1400	
	3	76.50	71.56	84.10	39.3939	

Table D30 %Detergency from polyester by using AE surfactant at different surfactant concentration at pH11.

Surfactant Conc. (%w/v)	Sample No.	Soiled swatch after washing	Soiled swatch before washing	unsoiled swatch	%Detergency	Average %Detergency
0	1	74.32	71.53	85.85	19.4832	20.0329
	2	75.27	71.59	85.83	25.8427	
	3	73.90	71.95	85.15	14.7727	
0.075	1	75.03	71.90	84.39	25.0600	22.7330
	2	74.15	71.32	84.90	20.8395	
	3	74.08	71.19	84.15	22.2994	
1.0000	1	75.15	71.75	84.25	27.2000	25.7167
	2	75.18	71.89	84.34	26.4257	
	3	75.08	72.33	84.02	23.5244	
2.0000	1	77.03	72.21	85.03	37.5975	38.3555
	2	77.27	72.13	85.06	39.7525	
	3	77.24	72.45	85.15	37.7165	
3.5000	1	76.79	72.05	85.49	35.2679	39.8800
	2	77.65	72.89	85.78	36.9279	
	3	77.24	70.00	85.26	47.4443	
5.0000	1	76.05	70.13	85.14	39.4404	39.3977
	2	76.14	70.93	84.93	37.2143	
	3	76.10	70.43	84.08	41.5385	

Table D31 %Detergency from cotton by using LAS surfactant at different surfactant concentration.

Surfactant Conc. (%w/v)	Sample No.	Soiled swatch after washing	Soiled swatch before washing	unsoiled swatch	%Detergency	Average %Detergency
0	1	78.48	76.89	88.14	14.1333	10.1429
	2	75.64	74.80	87.65	6.5370	
	3	79.20	78.23	88.17	9.7586	
0.1016	1	78.64	76.87	87.66	16.4041	26.6870
	2	77.94	73.07	87.33	34.1515	
	3	78.72	75.02	87.56	29.5056	
0.3014	1	77.32	73.06	86.86	30.8696	30.4933
	2	77.69	73.56	87.61	29.3950	
	3	78.36	74.43	87.02	31.2153	
0.5000	1	79.87	74.25	87.93	41.0819	32.0015
	2	78.51	75.69	87.57	23.7374	
	3	79.46	75.54	88.11	31.1854	
1.0000	1	79.85	75.39	88.17	34.8983	33.4627
	2	80.81	77.44	87.92	32.1565	
	3	80.42	76.51	88.24	33.3333	
2.0000	1	78.34	75.21	87.11	26.3025	33.4747
	2	80.55	76.08	87.85	37.9779	
	3	79.87	74.34	89.64	36.1438	
3.0000	1	77.34	74.01	87.73	24.2711	34.0860
	2	78.87	75.43	87.28	29.0295	
	3	82.18	77.72	86.83	48.9572	
4.0000	1	76.67	72.15	86.86	30.7274	33.7375
	2	81.18	74.04	88.05	50.9636	
	3	79.25	77.21	87.66	19.5215	

Table D32 %Detergency from cotton by using LAS surfactant at different surfactant concentration at pH5.

Surfactant Conc. (%w/v)	Sample No.	Soiled swatch after washing	Soiled swatch before washing	unsoiled swatch	%Detergency	Average %Detergency
0	1	77.40	76.76	87.83	5.7814	8.5390
	2	73.93	72.70	87.70	8.2000	
	3	77.08	75.70	87.56	11.6358	
0.0400	1	82.16	79.78	88.80	26.3858	23.6955
	2	83.57	82.34	88.96	18.5801	
	3	83.85	82.16	88.63	26.1206	
0.1000	1	82.82	79.94	88.67	32.9897	26.3185
	2	83.67	82.46	88.42	20.3020	
	3	78.26	74.78	88.34	25.6637	
0.3000	1	76.34	73.13	88.55	20.8171	28.2743
	2	78.67	72.20	88.62	39.4032	
	3	76.96	73.09	88.82	24.6027	
0.5000	1	76.47	73.69	87.30	20.4262	28.2521
	2	77.18	72.24	87.20	33.0214	
	3	76.24	71.24	87.21	31.3087	

Table D33 %Detergency from cotton by using LAS surfactant at different surfactant concentration at pH7.

Surfactant Conc. (%w/v)	Sample No.	Soiled swatch after washing	Soiled swatch before washing	unsoiled swatch	%Detergency	Average %Detergency
0.0000	1	78.48	76.89	88.14	14.1333	10.1429
	2	75.64	74.80	87.65	6.5370	
	3	79.20	78.23	88.17	9.7586	
0.0400	1	80.03	78.88	88.43	12.0419	24.8979
	2	83.75	81.23	89.11	31.9797	
	3	82.03	79.11	88.63	30.6723	
0.1000	1	78.35	75.34	88.18	23.4424	28.8378
	2	77.93	72.79	87.30	35.4238	
	3	78.67	74.91	88.51	27.6471	
0.3000	1	77.67	73.62	88.74	26.7857	30.4854
	2	78.19	74.49	88.34	26.7148	
	3	79.25	73.42	88.78	37.9557	
0.5000	1	76.54	72.71	87.50	25.8959	30.4098
	2	77.96	73.71	87.54	30.7303	
	3	78.78	74.42	87.02	34.6032	

Table D34 %Detergency from cotton by using LAS surfactant at different surfactant concentration at pH9.

Surfactant Conc. (%w/v)	Sample No.	Soiled swatch after washing	Soiled swatch before washing	unsoiled swatch	%Detergency	Average %Detergency
0	1	75.98	74.17	87.81	13.2698	14.1198
	2	77.09	75.69	87.94	11.4286	
	3	77.37	75.12	87.86	17.6609	
0.0400	1	81.51	79.25	88.34	24.8625	25.9966
	2	82.40	78.84	88.67	36.2157	
	3	82.00	80.62	88.78	16.9118	
0.1000	1	78.05	74.06	88.20	28.2178	32.7381
	2	78.02	73.40	88.13	31.3646	
	3	79.17	73.07	88.86	38.6320	
0.3000	1	79.81	75.5	88.38	33.4627	32.9717
	2	78.66	73.02	88.56	36.2934	
	3	76.90	72.22	88.27	29.1589	
0.5000	1	78.13	74.54	87.56	27.5730	32.5651
	2	78.37	72.72	88.15	36.6170	
	3	77.17	71.98	87.47	33.5055	

Table D35 %Detergency from cotton by using LAS surfactant at different surfactant concentration at pH11.

Surfactant Conc. (%w/v)	Sample No.	Soiled swatch after washing	Soiled swatch before washing	unsoiled swatch	%Detergency	Average %Detergency
0	1	79.56	78.53	88.37	10.4675	13.9051
	2	76.61	74.65	87.19	15.6300	
	3	81.59	80.25	88.83	15.6177	
0.0400	1	83.80	80.55	88.51	40.8291	30.7637
	2	82.02	80.40	88.85	19.1716	
	3	83.09	80.51	88.50	32.2904	
0.1000	1	80.85	76.53	88.45	36.2416	38.7839
	2	79.74	73.19	88.31	43.3201	
	3	78.58	72.62	88.82	36.7901	
0.3000	1	79.36	72.83	88.67	41.2247	38.6488
	2	79.44	74.52	86.90	39.7415	
	3	79.34	74.95	87.50	34.9801	
0.5000	1	79.10	72.88	87.63	42.1695	39.0205
	2	78.85	73.73	87.50	37.1823	
	3	76.62	70.10	87.39	37.7097	

Table D36 %Detergency from blend polyester/cotton by using LAS surfactant at different surfactant concentration.

Surfactant Conc. (%w/v)	Sample No.	Soiled swatch after washing	Soiled swatch before washing	unsoiled swatch	%Detergency	Average %Detergency
0	1	74.26	71.42	85.39	20.3293	17.0793
	2	73.97	71.71	84.97	17.0437	
	3	73.42	71.49	85.41	13.8649	
0.100	1	76.00	71.13	85.23	34.5390	28.1139
	2	75.02	71.25	85.48	26.4933	
	3	75.09	71.85	85.75	23.3094	
0.300	1	75.80	71.47	85.12	31.7216	31.6242
	2	75.34	71.36	85.46	28.2270	
	3	76.05	71.00	85.46	34.9239	
0.500	1	76.13	71.12	85.65	34.4804	32.1360
	2	75.12	71.24	85.23	27.7341	
	3	76.03	71.26	85.21	34.1935	
1.000	1	76.41	72.01	85.35	32.9835	32.0093
	2	76.71	72.03	85.75	34.1108	
	3	75.94	72.06	85.47	28.9336	
2.000	1	76.87	72.89	85.41	31.7891	33.8258
	2	77.00	71.45	86.45	37.0000	
	3	76.97	72.41	86.36	32.6882	
3.000	1	76.16	70.06	86.00	38.2685	32.3644
	2	75.30	70.01	86.39	32.2955	
	3	74.70	70.45	86.47	26.5293	
4.000	1	76.42	70.46	86.12	38.0587	33.5120
	2	75.31	70.47	86.00	31.1655	
	3	75.26	70.82	85.00	31.3117	

Table D37 %Detergency from blend polyester/cotton by using LAS surfactant at different surfactant concentration at pH5.

Surfactant Conc. (%w/v)	Sample No.	Soiled swatch after washing	Soiled swatch before washing	unsoiled swatch	%Detergency	Average %Detergency
0	1	72.58	69.78	85.10	18.2768	17.6461
	2	72.6	70.41	85.41	14.6000	
	3	72.68	69.42	85.67	20.0615	
0.0400	1	74.16	72.45	86.12	12.5091	23.1186
	2	75.57	71.87	85.35	27.4481	
	3	75.85	71.89	85.36	29.3987	
0.1000	1	76.82	71.84	85.23	37.1919	26.0696
	2	75.67	71.85	85.45	28.0882	
	3	74.26	72.45	86.45	12.9286	
0.3000	1	76.34	72.48	85.34	30.0156	28.9078
	2	75.97	72.50	86.23	25.2731	
	3	76.96	72.60	86.47	31.4348	
0.5000	1	76.07	72.36	86.45	26.3307	28.3173
	2	77.08	72.25	86.15	34.7482	
	3	76.04	72.81	86.34	23.8729	

Table D38 %Detergency from blend polyester/cotton by using LAS surfactant at different surfactant concentration at pH7.

Surfactant Conc. (%w/v)	Sample No.	Soiled swatch after washing	Soiled swatch before washing	unsoiled swatch	%Detergency	Average %Detergency
0	1	74.26	71.42	85.39	20.3293	17.0793
	2	73.97	71.71	84.97	17.0437	
	3	73.42	71.49	85.41	13.8649	
0.0400	1	74.93	72.45	85.94	18.3840	24.7755
	2	75.75	72.36	85.97	24.9082	
	3	76.63	72.58	85.63	31.0345	
0.1000	1	76.35	72.49	85.78	29.0444	28.9450
	2	76.93	72.56	85.48	33.8235	
	3	75.67	72.48	85.79	23.9669	
0.3000	1	77.67	73.62	85.16	35.0953	31.2386
	2	76.19	71.06	85.45	35.6498	
	3	76.25	73.42	85.74	22.9708	
0.5000	1	76.14	72.71	85.72	26.3643	31.3414
	2	77.36	73.71	85.73	30.3661	
	3	76.48	71.05	85.61	37.2940	

Table D39 %Detergency from blend polyester/cotton by using LAS surfactant at different surfactant concentration at pH9.

Surfactant Conc. (%w/v)	Sample No.	Soiled swatch after washing	Soiled swatch before washing	unsoiled swatch	%Detergency	Average %Detergency
0	1	72.80	70.31	85.59	16.2958	17.6690
	2	73.19	70.72	85.38	16.8486	
	3	70.77	67.30	84.77	19.8626	
0.0400	1	76.51	71.89	86.74	31.1111	26.2028
	2	75.4	72.14	86.53	22.6546	
	3	76.00	72.45	86.74	24.8425	
0.1000	1	77.05	72.41	86.55	32.8147	31.1946
	2	77.02	72.48	86.13	33.2601	
	3	76.17	72.36	86.21	27.5090	
0.3000	1	76.91	72.69	86.32	30.9611	33.3301
	2	77.66	73.09	86.34	34.4906	
	3	77.24	72.56	86.11	34.5387	
0.5000	1	77.13	73.00	85.49	33.0665	33.0813
	2	76.37	71.48	85.46	34.9785	
	3	76.17	71.98	85.41	31.1988	

Table D40 %Detergency from blend polyester/cotton by using LAS surfactant at different surfactant concentration at pH11.

Surfactant Conc. (%w/v)	Sample No.	Soiled swatch after washing	Soiled swatch before washing	unsoiled swatch	%Detergency	Average %Detergency
0	1	73.34	69.53	85.91	23.2601	19.6222
	2	72.20	69.69	85.80	15.5804	
	3	72.89	69.82	85.15	20.0261	
0.0400	1	74.8	70.55	84.87	29.6788	29.1134
	2	74.05	70.40	84.78	25.3825	
	3	75.09	70.60	84.51	32.2789	
0.1000	1	77.85	72.30	84.56	45.2692	36.5673
	2	75.74	72.19	85.53	26.6117	
	3	77.48	72.62	85.47	37.8210	
0.3000	1	77.36	72.83	85.46	35.8670	36.0387
	2	77.44	72.52	85.13	39.0167	
	3	77.34	72.95	86.16	33.2324	
0.5000	1	76.90	72.88	84.11	35.7970	36.5267
	2	77.75	73.10	84.35	41.3333	
	3	75.12	70.10	85.57	32.4499	

Table D41 %Detergency from polyester by using LAS surfactant at different surfactant concentration.

Surfactant Conc. (%w/v)	Sample No.	Soiled swatch after washing	Soiled swatch before washing	unsoiled swatch	%Detergency	Average %Detergency
0	1	74.26	72.93	85.39	10.6742	14.1760
	2	73.97	71.37	85.76	18.0681	
	3	73.42	71.49	85.49	13.7857	
0.1000	1	76.65	72.90	85.19	30.5126	29.7756
	2	76.56	72.33	85.63	31.8045	
	3	76.30	72.94	85.38	27.0096	
0.3000	1	76.30	72.16	85.64	30.7122	31.6387
	2	76.92	72.70	85.97	31.8011	
	3	76.90	72.14	86.83	32.4030	
0.5000	1	76.11	72.65	86.92	24.2467	31.9461
	2	77.14	72.23	86.08	35.4513	
	3	77.36	72.21	86.46	36.1404	
1.0000	1	75.89	72.35	86.08	25.7830	31.9730
	2	76.67	71.75	86.86	32.5612	
	3	77.11	71.47	86.48	37.5750	

Table D42 %Detergency from polyester by using LAS surfactant at different surfactant concentration at pH5.

Surfactant Conc. (%w/v)	Sample No.	Soiled swatch after washing	Soiled swatch before washing	unsoiled swatch	%Detergency	Average %Detergency
0	1	73.27	70.59	84.60	19.1292	17.3290
	2	73.13	70.96	84.75	15.7360	
	3	72.39	70.07	83.62	17.1218	
0.0400	1	75.00	71.24	85.98	25.5088	27.8143
	2	75.50	71.89	84.56	28.4925	
	3	75.90	71.84	85.63	29.4416	
0.1000	1	76.83	71.74	85.56	36.8307	28.9548
	2	75.47	71.45	87.00	25.8521	
	3	74.65	71.03	86.00	24.1817	
0.3000	1	76.31	71.85	86.00	31.5194	32.5641
	2	76.65	71.84	86.13	33.6599	
	3	76.03	71.01	86.45	32.5130	
0.5000	1	76.54	72.06	85.46	33.4328	32.5376
	2	76.43	72.54	85.32	30.4382	
	3	77.01	72.88	85.12	33.7418	

Table D43 %Detergency from polyester by using LAS surfactant at different surfactant concentration at pH7.

Surfactant Conc. (%w/v)	Sample No.	Soiled swatch after washing (A)	Soiled swatch before washing (B)	unsoiled swatch (C0)	%Detergency	Average %Detergency
0	1	73.72	71.61	83.00	18.5250	17.0222
	2	73.18	71.71	84.37	11.6114	
	3	74.12	71.24	85.00	20.9302	
0.0400	1	75.67	72.41	84.96	25.9761	26.2508
	2	75.79	72.48	84.96	26.5224	
	3	75.60	72.25	85.01	26.2539	
0.1000	1	76.47	72.15	85.03	33.5404	31.1652
	2	76.39	72.22	85.02	32.5781	
	3	76.17	72.83	85.03	27.3770	
0.3000	1	77.28	72.42	85.16	38.1476	34.5071
	2	76.25	71.78	85.42	32.7713	
	3	76.25	71.64	85.78	32.6025	
0.5000	1	76.30	71.39	85.74	34.2160	34.8611
	2	76.47	71.40	85.23	36.6594	
	3	76.02	71.22	85.46	33.7079	

Table D44 %Detergency from polyester by using LAS surfactant at different surfactant concentration at pH9.

Surfactant Conc. (%w/v)	Sample No.	Soiled swatch after washing	Soiled swatch before washing	unsoiled swatch	%Detergency	Average %Detergency
0	1	72.56	70.89	84.99	11.8440	18.2917
	2	73.84	70.86	84.20	22.3388	
	3	73.46	70.65	84.23	20.6922	
0.0400	1	76.14	71.79	85.14	32.5843	28.6650
	2	75.61	71.65	85.25	29.1176	
	3	75.02	71.67	85.46	24.2930	
0.1000	1	75.86	71.25	85.37	32.6487	31.5156
	2	77.01	72.99	85.19	32.9508	
	3	75.96	72.22	85.14	28.9474	
0.3000	1	76.94	72.28	85.74	34.6211	34.6615
	2	76.84	72.37	85.36	34.4111	
	3	77.09	72.34	85.93	34.9522	
0.5000	1	77.03	72.78	85.13	34.4130	34.3395
	2	76.87	72.36	85.23	35.0427	
	3	76.47	72.08	85.16	33.5627	

Table D45 %Detergency from polyester by using LAS surfactant at different surfactant concentration at pH11.

Surfactant Conc. (%w/v)	Sample No.	Soiled swatch after washing	Soiled swatch before washing	unsoiled swatch	%Detergency	Average %Detergency
0	1	74.32	71.53	85.85	19.4832	20.0329
	2	75.27	71.59	85.83	25.8427	
	3	73.90	71.95	85.15	14.7727	
0.0400	1	75.71	71.10	85.42	32.1927	29.2882
	2	75.56	71.38	85.32	29.9857	
	3	74.78	71.13	85.34	25.6861	
0.1000	1	77.08	71.77	85.32	39.1882	36.4668
	2	75.40	71.03	86.56	28.1391	
	3	77.92	71.71	86.47	42.0732	
0.3000	1	76.47	71.69	86.71	31.8242	37.5791
	2	77.13	71.27	85.98	39.8368	
	3	77.71	71.68	86.36	41.0763	
0.5000	1	77.12	71.34	86.67	37.7038	37.8833
	2	77.05	71.46	86.48	37.2170	
	3	77.08	71.29	86.24	38.7291	

Table D46 %Detergency from cotton by using commercial detergent surfactant at different surfactant concentration.

Detergent Conc. (%w/v)	Sample No.	Soiled swatch after washing	Soiled swatch before washing	unsoiled swatch	%Detergency	Average %Detergency
0	1	78.48	76.89	88.14	14.1333	10.1429
	2	75.64	74.80	87.65	6.5370	
	3	79.20	78.23	88.17	9.7586	
0.0570	1	81.37	76.70	89.01	37.9366	36.0404
	2	82.28	78.06	88.32	41.1306	
	3	79.64	75.77	89.09	29.0541	
0.1000	1	82.09	77.35	87.74	45.6208	37.3541
	2	81.26	77.91	87.61	34.5361	
	3	79.89	75.57	89.11	31.9055	
0.4850	1	82.63	77.16	88.08	50.0916	53.0652
	2	82.82	76.48	87.95	55.2746	
	3	83.60	78.68	87.82	53.8293	
0.9940	1	81.61	75.88	87.36	49.9129	53.0761
	2	82.97	77.22	87.21	57.5576	
	3	82.62	77.32	87.56	51.7578	
2.5400	1	83.89	78.53	87.72	58.3243	53.2645
	2	81.64	76.12	87.83	47.1392	
	3	82.69	76.73	87.70	54.3300	
3.6350	1	82.01	76.45	85.90	58.8360	55.1046
	2	84.05	78.03	88.34	58.3899	
	3	81.42	75.51	87.80	48.0879	

Table D47 %Detergency from blend polyester/cotton by using commercial detergent surfactant at different surfactant concentration.

Detergent Conc. (%w/v)	Sample No.	Soiled swatch after washing	Soiled swatch before washing	unsoiled swatch	%Detergency	Average %Detergency
0	1	74.26	71.42	85.39	20.3293	17.0793
	2	73.97	71.71	84.97	17.0437	
	3	73.42	71.49	85.41	13.8649	
0.0500	1	75.78	73.00	85.34	22.5284	34.5410
	2	78.12	72.14	85.67	44.1981	
	3	77.53	73.25	84.85	36.8966	
0.1000	1	77.98	72.10	87.01	39.4366	39.9918
	2	78.97	73.10	86.50	43.8060	
	3	78.31	74.24	85.32	36.7329	
0.5000	1	78.89	72.14	85.14	51.9231	50.9974
	2	78.64	71.06	85.32	53.1557	
	3	78.32	71.89	85.31	47.9136	
1.0000	1	79.12	71.65	85.31	54.6852	50.4017
	2	78.25	71.85	85.35	47.4074	
	3	78.01	71.37	84.89	49.1124	
2.5000	1	79.61	71.54	84.67	61.4623	50.5143
	2	79.12	72.89	84.53	53.5223	
	3	77.27	73.00	84.68	36.5582	
3.6500	1	79.24	71.04	85.13	58.1973	50.9601
	2	77.32	69.78	85.51	47.9339	
	3	77.08	69.89	85.27	46.7490	

Table D48 %Detergency from polyester by using commercial detergent surfactant at different surfactant concentration.

Detergent Conc. (%w/v)	Sample No.	Soiled swatch after washing	Soiled swatch before washing	unsoiled swatch	%Detergency	Average %Detergency
0	1	74.16	71.67	84.39	19.5755	17.4650
	2	73.17	71.15	84.37	15.2799	
	3	74.02	71.81	84.41	17.5397	
0.0500	1	75.88	71.83	84.32	32.4259	35.0458
	2	76.12	71.49	84.13	36.6297	
	3	75.73	71.31	83.56	36.0816	
0.1000	1	76.78	71.77	84.59	39.0796	40.1954
	2	76.87	71.98	84.74	38.3229	
	3	77.61	72.32	84.57	43.1837	
0.5000	1	78.19	72.66	85.15	44.2754	50.2836
	2	78.74	72.39	84.57	52.1346	
	3	78.82	72.20	84.36	54.4408	
1.0000	1	79.22	72.77	84.52	54.8936	49.5273
	2	77.25	71.32	83.32	49.4167	
	3	77.01	71.60	83.82	44.2717	
2.5000	1	78.31	71.85	83.73	54.3771	51.5451
	2	77.12	71.59	84.23	43.7500	
	3	78.57	71.32	84.15	56.5082	
3.6500	1	78.24	71.04	83.89	56.0311	51.1344
	2	75.32	69.78	83.39	40.7054	
	3	78.68	71.20	84.40	56.6667	

Appendix E Contact angle Measurement

Table E1 Data for contact angle of MES on blended cotton/polyester fabric at 30°C.

MES Concentration (% w/v)	pH 5	pH 7	pH 9	pH 11
	Contact angle (degree)			
0.001	51.02	51.56	53.31	53.18
0.002	49.65	50.53	51.02	51.63
0.005	43.57	44.26	45.37	46.87
0.008	30.25	31.13	32.14	32.44
0.011	23.45	24.49	25.62	26.46
0.014	19.63	20.07	21.45	22.65
0.017	19.59	20.66	21.72	22.56
0.02	19.72	20.58	21.67	22.13
0.05	19.67	19.79	21.09	21.07
0.1	18.74	18.89	19.87	20.26
0.2	18.63	18.71	19.37	19.56

Table E2 Data for contact angle of MES on polyester fabric at 30°C.

MES Concentration (% w/v)	pH 5	pH 7	pH 9	pH 11
	Contact angle (degree)			
0.001	51.72	52.26	53.07	53.89
0.002	50.34	51.23	52.73	53.24
0.005	44.26	44.87	46.07	47.58
0.008	30.74	31.86	32.82	33.15
0.011	24.15	25.16	26.31	27.27
0.014	20.32	20.77	22.16	23.26
0.017	20.27	21.39	22.43	23.27
0.020	20.43	21.27	22.38	22.84
0.050	20.36	20.53	21.83	21.78
0.100	19.46	19.64	20.59	21.07
0.200	19.37	19.42	20.08	20.47

Table E3 Data for contact angle of AE on blended cotton/polyester fabric at 30°C.

AE Concentration (% w/v)	pH 5	pH 7	pH 9	pH 11
	Contact angle (degree)			
0.002	51.14	52.02	65.51	67.13
0.005	45.06	45.45	46.89	48.37
0.008	41.76	42.60	43.63	43.94
0.011	34.26	36.47	39.08	40.36
0.014	32.84	33.35	33.46	34.07
0.017	30.28	30.77	31.22	32.11
0.020	28.55	28.74	29.08	29.74
0.050	24.96	25.92	27.12	27.96
0.100	21.11	21.53	22.93	24.14
0.200	21.08	22.13	23.22	24.06
0.300	21.23	22.07	23.18	23.63
0.400	21.22	21.76	22.87	23.54

Table E4 Data for contact angle of AE on polyester fabric at 30°C.

AE Concentration (% w/v)	pH 5	pH 7	pH 9	pH 11
	Contact angle (degree)			
0.002	61.47	62.83	65.34	65.45
0.005	52.59	54.94	57.32	60.06
0.008	47.45	48.15	48.69	51.23
0.011	42.28	44.24	45.99	46.25
0.014	40.67	40.91	41.43	41.71
0.017	36.36	37.68	38.25	39.55
0.02	31.88	34.14	34.57	34.96
0.05	29.34	29.62	29.61	29.98
0.1	23.94	24.78	25.62	26.42
0.2	23.13	24.05	24.95	25.87
0.3	23.82	24.14	24.81	26.35
0.4	23.52	24.06	24.09	25.76

CIRRICULUM VITAE

Name: Mr. Phumphattanapong Sang-in

Date of Birth: January 11, 1984

Nationality: Thai

University Education:

2003-2007 Bachelor Degree of Engineering in Petrochemical and Polymeric Material, Faculty of Engineering and Industrial Technology, Silpakorn University, Nakornprathom, Thailand.

Working Experience:

2003 Position: Student trainee

Company name: Thai Oil Public Company Limited