

REFERENCES

- Agoudjil, N. and Benkacem, T. (2007) Synthesis of porous titaniumdioxide membranes. Desalination, 206, 531-537.
- Agustina, T. E., Ang, H. M. ,and Vareek, V. K. (2005) A review of synergistic effect of hotocatalysis and ozonation on wastewater treatment. Journal of Photochemistry and Photobiology C: Photochemistry Reviews, 6, 264–273.
- Ahn, K. H., Park, Y. B. ,and Park, D. W. (2003) Kinetic and mechanistic study on the chemical vapor deposition of titanium dioxide thin films by in situ FT-IR using TTIP. Surface and Coatings Technology, 171, 198–204.
- Anpo, M., Shima, T., Kodama, S. ,and Kubokawa, Y. (1987) Photocatalytic hydrogenation of propyne with water on small-particle titania: Size quantization effects and reaction intermediates. Journal of Physical Chemistry, 91, 4305–4310.
- Asahi, R., Morikawa, T., Ohwaki, T., Aoki, K. ,and Taga, Y. (2001) Visible-Light Photocatalysis in Nitrogen-Doped Titanium Oxides, Science, 293, 269-271.
- Astley, O.M, Chanliaud, E., Donald, A.M. ,and Gidley, M.J. (2001) Structure of Acetobacter cellulose composites in the Hydrated State. International Journal of Biological Macromolecules, 29, 193-202.
- Bahnemann, D. (2004) Photocatalytic Water Treatment: Solar Energy Applications. Solar Energy, 77(5), 445-459.
- Bansal, P., Singh, D. ,and Sud, D. (2010) Photocatalytic degradation of azo dye in aqueous TiO₂ suspension: Reaction pathway and identification of intermediates products by LC/MS. Separation and Purification Technology, 72(3), 357-365.
- Bianchi, C.L., Cappelletti, G., Ardizzone, S., Gialanella, S., Naldoni, A., Oliva, C. ,and Pirola, C. (2009) N-doped TiO₂ from TiCl₃ for photodegradation of air pollutants. Catalysis Today, 144(1-2), 31-36.
- Bielecki, S., Krystynowicz, A., Turkiewicz, M. ,and Kalinowska H. (2005) Bacterial Cellulose. In: Polysaccharides and Polyamides in the Food Industry, A. Steinbüchel, S.K. Rhee (Eds.), Wiley-VCH Verlag, Weinheim, Germany, 31–85.

- Blake D.M., Maness P.C., Huang Z., Wolfrum E.J., Huang J. ,and Jacoby W.A. (1999) Application of the photocatalytic chemistry of titanium dioxide to disinfection and the killing of cancer cells. Separation and Purification Methods, 28(1) 1-50.
- Chae, S. Y., Park, M. K., Lee, S. K., Kim, T.V., Kim, S.K. ,and Lee, W.I. (2003) Preparation of Size-Controlled TiO₂ Nanoparticles and Derivation of Optically Transparent Photocatalytic Films. Chemistry of Materials, 15, 3326-3331.
- Chatterjee, D., Dasgupta, S. ,and Rao, N. N. (2006) Visible light assisted photodegradation of halocarbons on the dye modified TiO₂ surface using visible light. Solar Energy Materials and Solar Cells, 90(7-8), 1013-1020.
- Chawla, P.R., Bajaj, I.B., Survase, S.A. ,and Singhal, R.S. (2009) Fermentative Production of Microbial Cellulose: Fermentative Production and Applications Cellulose. Food Technology and Biotechnology, 47(2), 107–124.
- Childs, L. P. and Ollis, D. (1980) Is photocatalysis catalytic ?. Journal of Catalysis , 66, 383-390.
- Chong, M.N.n, Jin, B., Chow, C.W.K. ,and Saint, C. (2010) Recent developments in photocatalytic water treatment technology: A review. Water Research, 44(10), 2997-3027.
- Chuangchote, S., Jitputti, J., Sagawa, T. ,and Yoshikawa, S. (2009) Photocatalytic Activity for Hydrogen Evolution of Electrospun TiO₂ Nanofibers. ACS Applied Materials & Interfaces, 1(5), 1140–1143.
- Czaja, W., Krystynowicz, A., Bielecki, S. ,and Brown Jr., R.M. (2006) Microbial cellulose – The natural power to heal wounds. Biomaterials, 27, 145–151.
- Czaja, W., Romanovicz, D., ,and Brown Jr., R. M. (2004) Structural investigation of microbial cellulose produced in stationary and agitated culture. Cellulose, 11, 403-411.
- Dindar, B. and Icli, S. (2001) Unusual photoreactivity of zinc oxide irradiated by concentrated sunlight. Journal of Photochemistry and Photobiology A: Chemistry, 140, 263–268.

- Erkov, V.G., Devyatova, S.F., Molodstova, E.L., Malsteva, T.V. ,and Yanovskii, U.A. (2000) Si-TiO₂ interface evolution at prolonged annealing in low vacuum or N₂O ambient. Applied Surface Science, 166, 51-56.
- Fox, M.A. and Dulay, M.T. (1993). Heterogeneous Photocatalysis. Chemical Reviews, 93, 341-357.
- Fujishima, A., Rao, T.N. ,and Tryk, D.A. (2000) Titanium dioxide photocatalysis. Journal of Photochemistry and Photobiology C: Photochemistry Reviews, 1(1), 1-21.
- Gaya, U.I. and Abdullah, A.H. (2008) Heterogeneous photocatalytic degradation of organic contaminants over titanium dioxide: A review of fundamentals, progress and problems. Journal of Photochemistry and Photobiology C: Photochemistry Reviews, 9(1), 1-12.
- Geyer, U., Heinze, T., Stein, A., Klemm, D., Marsch. S., Schumann, D. ,and Schmauder, H. P. (1994) Formation , Derivatization and Applications of Bacterial Cellulose. International Journal of Biological Macromolecules, 16, 343-347.
- Gladfelter, W L., Fictorie, C. P. ,and Evans, J. F. (1994) Kinetic and mechanistic study of the chemical vapor deposition of titanium dioxide thin films using tetrakis-(isopropoxy)-titanium(IV). Journal of Vacuum Science & Technology A, 12, 1108-1113.
- Guan, W., Wang, Y., Xu, F. ,and Guan, Y. (2008) Poly(phthalazine ether sulfone ketone) as novel stationary phase for stir bar sorptive extraction of organochlorine compounds and organophosphorus pesticides. Journal of Chromatography A, 1177, 28-35.
- Henriksson, M., Berglund, L.A, Isaksson, P., Lindström, T ,and Nishino, T. (2008) Cellulose nanopaper structures of high toughness. Biomacromolecules, 9, 1579–1585.
- Herrera, F. , Lopez, A. , Mascolo, G. , Albers, P. ,and Kiwi, J. (2001) Catalytic decomposition of the reactive dye UNIBLUE A on hematite. modelling of the reactive surface. Water Research, 35, 750 – 760.

- Herrmann, J.M. (1999) Heterogeneous photocatalysis: fundamentals and applications to the removal of various types of aqueous pollutants. Catalysis Today, 53(1), 115-129.
- Hestrin, S. and Schramm, M. (1954) Synthesis of cellulose by Acetobacter xylinum. Biochemical Journal, 58, 345-352.
- Hoffmann, M. R., Martin, S. T., Choi, W. Y. ,and Bahnemann, D. W. (1995) Environmental applications of semiconductor photocatalysis. Chemical Reviews, 95, 69–96.
- Hu, W., Chen, S., Zhou, B. ,and Wang, H. (2010) Facile synthesis of ZnO nanoparticles based on bacterial cellulose. Materials Science and Engineering: B, 170, 88-92.
- Iguchi, M., Mitsuhashi, S., Ichimura, K., Nishi, Y., Uryu, M., Yamanaka, S. ,and Watanabe, K. (1988) US Patent 4742164
- Ihara, T., Miyoshi, M., Iriyama, Y., Matsumoto, O. ,and Sugihara, S. (2003) Visible-light-active titanium oxide photocatalyst realized by an oxygen-deficient structure and by nitrogen doping. Applied Catalysis B: Environmental, 42(4), 403-409.
- Im, J.S., Yun, S.M. ,and Lee, Y.S. (2009) Investigation of multielemental catalysts based on decreasing the band gap of titania for enhanced visible light photocatalysis. Journal of Colloid and Interface Science, 336(1), 183-188.
- Im, J. S., Bai, B.C., In, S. J. ,and Lee, Y. S. (2010) Improved photodegradation properties and kinetic models of a solar-light-responsive photocatalyst when incorporated into electrospun hydrogel fibers. Journal of Colloid and Interface Science, 346, 216–221.
- Jacoby, W.A., Blake, D.M., Fennell, J.A., Boulter, J.E., Vargo, L.A.M., George,M.C. ,and Dolberg, S.K. (1996) Heterogeneous Photocatalysis for Control of Volatile Organic Compounds in Indoor Air. Journal of the Air and Waste Management Association, 46(9) 891-898.
- Janus, M., Tryba, B., Inagaki, M. ,and Morawski, A.W. (2004) New preparation of a carbon-TiO₂ photocatalyst by carbonization of n-hexane deposited on TiO₂. Applied Catalysis B: Environmental, 52(1), 61-67.

- Jonas, R. and Farah L.F. (1998) Production and application of microbial cellulose. Polymer Degradation and Stability, 59(1-3), 101-106.
- Kathirvelu, S., D'Souza,, L. ,and Dhurai, B. (2008) Nanotechnology applications in textiles. Indian Journal of Science and Technology, 1(5), 1-10.
- Kim, B., Kim. D., Cho. D. ,and Cho, S. (2003) Bactericidal effect of TiO₂ photocatalyst on selected food-borne pathogenic bacteria. Chemosphere, 52(1), 277-281.
- Kim, D. S. and Kwak, S.Y. (2007) The hydrothermal synthesis of mesoporous TiO₂ with high crystallinity, thermal stability, large surface area, and enhanced photocatalytic activity. Applied Catalysis A: General, 323, 110–118.
- Kitano, M., Matsuoka, M., Ueshima, M. ,and Anpo, M. (2007) Recent developments in titanium oxide-based photocatalysts. Applied Catalysis A: General, 325(1), 1-14.
- Kiwi, J., Meilert, K.T. ,and Laub, D. (2005) Photocatalytic self-cleaning of modified cotton textiles by TiO₂ clusters attached by chemical spacers. Journal of Molecular Catalysis A: Chemical, 237, 101–108.
- Klemm, D., Schumann, D., Udhhardt, U. ,and Marsch, S. (2001) Bacterial synthesized cellulose — artificial blood vessels for microsurgery. Progress in Polymer Science, 26(9), 1561-1603.
- Klimisch, H.J., Deckardt, K., Gembardt, C., Hildebrand, B., Kuttler, K. ,and Roe, F.J. (1997) Long-term inhalation toxicity of N-vinylpyrrolidone-2 vapours. Studies in rats. Food and Chemical Toxicology, 35, 1061-1074.
- Konstantinou, I.K. and Albanis, T.A. (2003) Photocatalytic transformation of pesticides in aqueous titanium dioxide suspensions using artificial and solar light: intermediates and degradation pathways. Applied Catalysis B: Environmental, 42(4), 319-335.
- Kraeutler, B. and Bard, A. J. (1978) Heterogeneous photocatalytic decomposition of saturated carboxylic acids on titanium dioxide powder. Decarboxylative route to alkanes. Journal of the American Chemical Society, 100, 5985–599.

- Kwon, C. H., Shin, H., Kim, J. H., Choi, W. S. ,and Yoon, K. H. (2004) Degradation of methylene blue via photocatalysis of titanium dioxide. Materials Chemistry and Physics, 86, 78–82.
- Legnani, C., Vilania, C., Calil, V.L., Barud, H.S., Quirino, W.G., Achete, C.A., Ribeiro, S.J.L. ,and Cremona, M. (2008) Bacterial cellulose membrane as flexible substrate for organic light emitting devices. Thin Solid Films, 517(3), 1016-1020.
- Li, D., Haneda, H., Labhsetwar, N. K., Hishita, S. ,and Ohashi, N. (2005) Visible-light-driven photocatalysis on fluorine-doped TiO₂ powders by the creation of surface oxygen vacancies Chemical Physics Letters, 401, 579-584.
- Li, X., Chen, S., Hu, W., Shi, S., Shen, W. ,and Zhang, X. (2009) In situ synthesis of CdS nanoparticles on bacterial cellulose nanofibers. Carbohydrate Polymer, 76, 509–512.
- Linsebigler, A.L., Lu, G., ,and Yates, J. T., Jr. (1995) Photocatalysis on TiO₂ Surfaces: Principles, Mechanisms and Selected Results Chemical Reviews, 95, 735-758.
- Liu, J.M., Huang, D.G., Liao, S.J., Dang, Z. ,and Petrik, L. (2006) Preparation of visible-light responsive N–F-codoped TiO₂ photocatalyst by a sol–gel-solvothermal method. Journal of Photochemistry and Photobiology A: Chemistry, 184(3). 282-288.
- Malato, S., Blanco, J., Vidal, A., ,and Richter, C. (2002) Photocatalysis with Solar Energy at a Pilot-Plant Scale: An Overview. Applied Catalysis B: Environmental, 37 (1), 1-15.
- Maneerung, T., Tokura, S. ,and Rujiravanit, R. (2008) Impregnation of silver nanoparticles into bacterial cellulose for antimicrobial wound dressing. Carbohydrate Polymers, 72, 43-51.
- Meilert K.T. , Laub D. ,and Kiwi J. (2005) Photocatalytic self-cleaning of modified cotton textiles by TiO₂ clusters attached by chemical spacers. Journal of Molecular Catalysis A: Chemical, 237, 101–108.
- Mills, A. and Hunte, S.L. (1997) An overview of semiconductor photocatalysis. Journal of Photochemistry and Photobiology A: Chemistry, (108), 1-35.

- Nishi Y., Uryu M., Yamanaka S., Watanabe K., Kitamura N., Iguchi M. ,and Mitsuhashi S. (1990) The structure and mechanical properties of sheets prepared from bacterial cellulose. Journal of Materials Science, 25, 2997–3001.
- Pekakis, P. A., Xekoukoulotakis, N.P. ,and Mantzavinos, D. (2006) Treatment of textile dyehouse wastewater by TiO₂ photocatalysis. Water Research, 40(6), 1276-1286.
- Pelton, R., Geng, X. ,and Brook, M. (2006) Photocatalytic paper from colloidal TiO₂-fact or fantasy. Advances in Colloid and Interface Science, 127(1), 43-53.
- Qiu, Y. and Yu, J. (2008) Synthesis of titanium dioxide nanotubes from electrospun fiber templates. Solid State Communications, 148, 556-558
- Rao, V., Rajeshwar, K., Verneker, V. P. ,and DuBow, J. (1980) Photosynthetic Production of H₂ and H₂O₂ on Semiconducting Oxide Grains in Aqueous Solutions. Journal of Physical Chemistry, 84, 1987-1991.
- Reife, A. and Freeman, H. S. (1996) Environmental chemistry of dyes and pigments, Wiley, Canada.
- Robert, D., Piscópo, A., Heintz, O., ,and Weber, J. V. (1999) Photocatalytic detoxification with TiO₂ supported on glass-fibre by using artificial and natural light. Catalysis Today, 54, 291–296.
- Rush, J. D. and Bielski, B. H. J. (1985) Pulse radiolytic studies of the reactions of HO₂/O₂ with Fe(II)/Fe(III) ions. The reactivity of HO₂/O₂ ? with ferric ions and its implication on the occurrence of the Haber-Weiss reaction. Journal of Chemical Physics, 89, 23, 5062-5066.
- Sathish, M., Viswanath, R.P. ,and Gopinath, C.S. (2009) N, S-co-doped TiO₂ nanophotocatalyst: synthesis, electronic structure and photocatalysis. Journal of Nanoscience and Nanotechnology, 9(1), 423-432.
- Shoda, M. and Sugano, Y. (2005). Recent advances in bacterial cellulose production, Biotechnology and Bioprocess Engineering, 10, 1–8.
- Sleiman, M., Conchon, P., Ferronato, C. ,and Chovelon, J. M. (2007) Iodosulfuron degradation by TiO₂ photocatalysis: Kinetic and reactional pathway investigations. Applied Catalysis: B, 71, 279–290.

- Sohrabi, M. R. and Ghavami, M. (2010) Comparison of Direct Yellow 12 dye degradation efficiency using UV/semiconductor and UV/ H₂O₂/semiconductor systems. Desalination, 252, 157–162.
- Sun, D., Yang, J. ,and Wang, X. (2009) Bacterial cellulose/TiO₂ hybrid nanofibers prepared by the surface hydrolysis method with molecular precision. Nanoscale, 2, 287-292.
- Sunada, K., Watanabe, T. ,and Hashimoto, K. (2003) Studies on photokilling of bacteria on TiO₂ thin film. Journal of Photochemistry and Photobiology A: Chemistry, 156(1-3), 227-233.
- Tetsuro, K., Toshiaki, O, Mitsunobu. I., Hiroaki T. ,and Seishiro I. (2003) Photocatalytic activity of rutile-anatase coupled TiO₂ particles prepared by a dissolution–reprecipitation method. Journal of Colloid and Interface Science, 267, 377–381
- Vulliet, E., Emmelin, C., Chovelon, J. M., Guillard, C. ,and Herrmann, J. M. (2002) Photocatalytic degradation of sulfonylurea herbicides in aqueous TiO₂. Applied Catalysis B: Environmental, 38(2), 127-137.
- Xie, Y., Li, Y. ,and Zhao, X. (2007) Low-temperature preparation and visible-light-induced catalytic activity of anatase F-N-codoped TiO₂. Journal of Molecular Catalysis A: Chemical, 227, 119-126.
- Xu, N., Shi, Z., Fan, Y., Dong, J., Shi, J. ,and Hu, M.Z. (1999) Effects of Particle Size of TiO₂ on Photocatalytic Degradation of Methylene Blue in Aqueous Suspensions. Industrial & Engineering Chemistry Research, 38(2), 373–379.
- Yamanaka, S., Watanabe, K., Kitamura, N., Iguchi, M., Mitsuhashi, S., Nishi Y. ,and Uryu M. (1989) The structure and mechanical properties of sheets prepared from bacterial cellulose. Journal of Materials Science, 24, 1573-4803.
- Yoshinaga, F., Tonouchi, N., ,and Watanabe, K. (1997) Research progress in production of bacterial cellulose by aeration and agitation culture and its application as a new industrial material. Bioscience Biotechnology & Biochemistry, 61, 219-224.

Zhang, Z., Wang, C.C., Zakaria, R. ,and Ying, J.Y. (1998) Role of Particle Size in Nanocrystalline TiO₂-Based Photocatalysts. The Journal of Physical Chemistry B, 102(52), 10871–10878.

APPENDIX

Table 1 Average fibers diameter of surface of pure bacterial cellulose and TiO₂ impregnated bacterial cellulose prepared at different molar ratio

Molar ratio of TTIP: H ₂ O in EtOH	Average fibers diameter (nm)
0 (pure BC)	37.2 ± 11.8
0.031	19.2 ± 5.6
0.063	23.9 ± 6.0
0.125	73.9 ± 20.6
0.250	82.0 ± 66.2
0.500	118.7 ± 41.3
1.000	129.4 ± 34.6
2.000	281.0 ± 75.8

Table 2 Average fibers diameter of cross section of pure bacterial cellulose and TiO₂ impregnated bacterial cellulose prepared at different molar ratio

Molar ratio of TTIP: H ₂ O in EtOH	Average fibers diameter (nm)
0 (pure BC)	37.2 ± 11.8
0.031	22.8 ± 6.1
0.063	30.0 ± 8.7
0.125	37.4 ± 18.3
0.250	45.9 ± 21.9
0.500	59.3 ± 35.0
1.000	60.8 ± 35.0
2.000	99.9 ± 70.9

Table 3 The content of the synthesized TiO₂ in bacterial cellulose

Molar ratio of TTIP: H ₂ O in EtOH	% Average of TiO ₂ in BC
0.031	6.45 ± 0.42
0.063	11.89 ± 0.58
0.125	16.73 ± 1.75
0.250	19.56 ± 1.23
0.500	32.88 ± 0.11
1.000	39.38 ± 1.10
2.000	48.44 ± 1.59

Table 4 Absorbance of MB solution (0.5%w/v) containing TiO₂ impregnated bacterial cellulose prepared at different molar ratio under irradiation of UV light for different time

Time (Min)	Molar ratio	0	0.031	0.063	0.125	0.5	2
0	Vial No.1	0.906	0.265	0.354	0.185	0.565	0.710
	Vial No.2	0.907	0.377	0.344	0.135	0.399	0.729
	Vial No.3	0.909	0.254	0.287	0.128	0.489	0.753
5	Vial No.1	0.893	0.185	0.342	0.157	0.510	0.681
	Vial No.2	0.895	0.332	0.333	0.123	0.366	0.700
	Vial No.3	0.902	0.229	0.275	0.113	0.415	0.722
10	Vial No.1	0.870	0.165	0.339	0.130	0.463	0.660
	Vial No.2	0.875	0.272	0.315	0.107	0.342	0.675
	Vial No.3	0.886	0.230	0.257	0.090	0.388	0.692
20	Vial No.1	0.821	0.124	0.315	0.102	0.400	0.611
	Vial No.2	0.831	0.183	0.275	0.084	0.295	0.621
	Vial No.3	0.851	0.197	0.216	0.066	0.328	0.629
30	Vial No.1	0.764	0.091	0.281	0.068	0.355	0.564
	Vial No.2	0.777	0.160	0.244	0.057	0.250	0.564
	Vial No.3	0.808	0.147	0.199	0.039	0.285	0.563
60	Vial No.1	0.494	0.044	0.217	0.015	0.154	0.361
	Vial No.2	0.550	0.083	0.201	0.007	0.128	0.293
	Vial No.3	0.645	0.087	0.138	0.002	0.142	0.274
90	Vial No.1	0.248	0.035	0.176	0.001	0.024	0.214
	Vial No.2	0.334	0.052	0.172	0.001	0.040	0.078
	Vial No.3	0.491	0.059	0.117	0.001	0.054	0.040
120	Vial No.1	0.056	0.028	0.144	0.000	0.000	0.068
	Vial No.2	0.171	0.026	0.140	0.001	0.002	0.001
	Vial No.3	0.347	0.032	0.095	0.000	0.008	0.000

Table 5 Absorbance of MB solution (0.5%w/v) containing TiO₂ impregnated bacterial cellulose prepared at different molar ratio none irradiation of UV light for different time

Time (Min)	Molar ratio	0	0.031	0.063	0.125	0.5	2
0	Vial No.1	0.911	0.407	0.277	0.149	0.398	0.734
	Vial No.2	0.91	0.276	0.407	0.240	0.405	0.778
	Vial No.3	0.914	0.285	0.302	0.238	0.332	0.725
5	Vial No.1	0.91	0.375	0.248	0.148	0.393	0.732
	Vial No.2	0.909	0.264	0.407	0.224	0.403	0.773
	Vial No.3	0.913	0.268	0.301	0.228	0.332	0.719
10	Vial No.1	0.909	0.361	0.247	0.144	0.387	0.729
	Vial No.2	0.908	0.259	0.406	0.218	0.399	0.773
	Vial No.3	0.912	0.256	0.301	0.221	0.330	0.717
20	Vial No.1	0.908	0.354	0.242	0.138	0.384	0.729
	Vial No.2	0.907	0.255	0.404	0.215	0.395	0.771
	Vial No.3	0.911	0.248	0.299	0.220	0.328	0.715
30	Vial No.1	0.908	0.348	0.241	0.136	0.377	0.726
	Vial No.2	0.907	0.250	0.403	0.212	0.391	0.766
	Vial No.3	0.91	0.238	0.298	0.216	0.324	0.711
60	Vial No.1	0.906	0.340	0.239	0.127	0.367	0.721
	Vial No.2	0.905	0.242	0.401	0.199	0.382	0.763
	Vial No.3	0.908	0.227	0.297	0.197	0.314	0.706
90	Vial No.1	0.906	0.329	0.237	0.122	0.358	0.715
	Vial No.2	0.904	0.239	0.401	0.194	0.366	0.761
	Vial No.3	0.908	0.209	0.296	0.191	0.305	0.698
120	Vial No.1	0.906	0.320	0.236	0.116	0.352	0.712
	Vial No.2	0.904	0.233	0.400	0.187	0.362	0.732
	Vial No.3	0.908	0.199	0.294	0.187	0.300	0.693

Table 6 The average degradation MB efficiency (%) of TiO₂ impregnated bacterial cellulose prepared at different molar ratio under irradiation of UV light for different time

Min	Molar ratio of TTIP: H ₂ O in EtOH					
	0	0.031	0.063	0.125	0.5	2
0	0.00	0.00	0.00	0.00	0.00	0.00
5	1.07	10.30	0.52	5.73	10.55	3.47
10	3.23	21.44	7.50	22.82	16.82	7.29
20	7.94	40.18	17.68	41.40	28.77	14.89
30	13.67	52.70	35.71	61.45	37.69	22.26
60	37.74	72.60	43.55	85.65	68.50	56.93
90	60.56	79.57	52.66	95.65	89.17	83.89
120	78.93	87.10	61.43	95.86	98.23	95.07

Table 7 Colony forming unit counts (cfu/ml) of TiO₂ impregnated bacterial cellulose prepared at different molar ratios of TTIP: H₂O against *S. aureus*

Sample prepared from different Molar ratio of TTIP to water in EtOH	Plate No.			Average	S.D.
	1	2	3		
0.000	196	185	199	193.33	7.37
0.125	120	127	111	119.33	8.02
0.500	19	30	39	29.33	10.02
2.000	148	160	154	154.00	6.00

CURRICULUM VITAE

Name: Mr. Nattakammala Janpatch

Date of Birth: March 25, 1986

Nationality: Thai

University Education:

2004-2009 Bachelor Degree of Science in Chemistry, Faculty of Science and Technology, Thammasat University, Bangkok, Thailand

Proceedings:

Janpatch, N.; Tokura, S; and Rujiravanit, R. (2011, April 26th) Photocatalytic and Antibacterial Properties under UV Light of TiO₂ Impregnated Bacterial Cellulose. Proceedings of the 2nd Research Symposium on Petroleum, Petrochemicals, and Advanced Materials, and the 17th PPC Symposium on Petroleum, Petrochemicals, and Polymers, Queen Sirikit National Convention Center, Bangkok, Thailand.